

AMENDMENT NO. 3 JUNE 2023
TO
IS 17262 : 2022 TEXTILES — POLYESTER PARTIALLY ORIENTED YARN (POY)
— SPECIFICATION
(First Revision)

(Foreword, Para 4) — Substitute ‘Annex J’ for ‘Annex H’.

(Page 1, clause 1) — Renumber the existing clause as **1.1** and insert the following new clause after the **1.1**:

‘**1.2** This standard is not applicable to bio-degradable POY yarns.’

(Page 1, clause 3.6) — Delete and renumber the subsequent clauses.

[Page 4, Table 1, Sl No. (i) a, col (3)] — Substitute the following for existing:

‘250 dtex f48 or 250/48’.

[Page 4, Table 2, Sl No. (i), col (3)] — Substitute the following for existing:

‘50/14, 80/72, 126/34, 250/144, 400/68’

[Page 5, Table 3, Sl No. (i), col (4)] — Shift the present values a step below in front of the relevant values in col (3).

[Page 5, Table 3, Sl No. (i), col (5)] — Substitute ‘2.5’ for ‘1.5’.

[Page 5, Table 4, Sl No. (iv), col (3)] — Substitute ‘0.1 to 1.5’ for ‘0.2 to 1.3’.

[Page 5, Table 4, Sl No. (vi)] — Substitute the following for existing row:

vi)	Ultraviolet resistance, 144 h, Percent retained strength, <i>Min</i> (For UV resistant yarns only)	80	Annex H
-----	--	----	---------

(Page 6, clause 6.3.16) — Insert the following new clause after the **6.3.16**:

‘6.3.17 Wound in Waste

May be accepted if it can be corrected by stripping.’

(Page 8, clause 7.1) — Insert the following note under the clause:

‘NOTE — Package of weight between 1 to 4 kg may also be allowed as per agreement between buyer and seller’.

(Page 8, clause 8.1) — Insert the following note under the clause:

‘NOTE — The yarn manufacturer shall mark on the pallets/cartons whether the yarn is Disperse Dyeable [Conventional Dyeable (COD)/Stock Dyeable (STD)/Easy Dyeable (ED)], Cationic Dyeable (CD) or Easy Dyeable Cationic Dyeable (EDCD) for guidance of the multifold yarns or fabric manufacturers.’

Price Group 2

Amendment No. 3 to IS 17262 : 2022

(Page 9, Annex A) — Delete the following reference:

<i>IS No.</i>	<i>Title</i>
13162 (Part 2) : 1991	Geotextiles — Methods of test: Part 2 Determination of resistance to exposure of ultraviolet light and water (xenon arc type apparatus)

(Page 9, Annex A) — Substitute the following for the existing entries for IS 3456 : 1966, IS 6359 : 1971, IS 7703 (Part 5) : 1990, IS 16481 : 2016.

<i>IS No.</i>	<i>Title</i>
IS 3456 : 2022	Method for determination of water-soluble matter of textile materials (<i>first revision</i>)
IS 6359 : 2023	Method for conditioning of textiles (<i>first revision</i>)
IS 7703 (Part 5) : 1987	Methods of test for continuous filament polyester and polyamide flat yarn: Part 5 Unevenness percentage
IS 16481 : 2022	Textiles — Synthetic micro fibres for use in cement based matrix — Specification (<i>first revision</i>)

(Page 15, Annex G) — Insert the following Annex H after Annex G:

‘ANNEX H
[Table 4, Sl No. (vi)]

DETERMINATION OF RESISTANCE OF POY TO ULTRAVIOLET LIGHT

H-1 TEST SPECIMENS

The test specimens for tenacity shall be taken from the sample as specified in IS 7703 (Part 2).

H-2 TEST CONDITIONS

H-2.1 The test shall be carried out with fluorescent UV-B lamp (*see* IS 7903).

H-2.2 The duration of the test shall be 144 h (that is 6 days).

H-2.3 The test cycle shall be 8 h at 60 °C ± 3 °C with UV radiation alternating after 4 h at 50 °C ± 3°C with condensation.

H-2.4 Irradiation level throughout the test shall be maintained at 0.63 W/m² + 0.03 W/m².

H-3 TEST PROCEDURE

H-3.1 Determine the original average tenacity for at least 20 test specimens as per IS 7703 (Part 2) before exposure.

H-3.2 Expose the specimens alternately to ultraviolet light alone and to condensation in one respective cycle.

H-3.2.1 The type of fluorescent UV lamp, the timing of the UV exposure and the temperature of condensation shall be as specified in **H-2**.

H-3.3 Determine the average tenacity for at least 20 test specimens as per IS 7703 (Part 2) after UV exposure as given in **H- 3.2**.

Amendment No. 3 to IS 17262 : 2022

H-3.4 Determine the percent retention of original tenacity as follows:

$$\text{Retention of original tenacity, percent} = \frac{b}{a} \times 100$$

where

a = Average tenacity before UV exposure as obtained in **H-3.1**, and

b = Average tenacity after UV exposure as obtained in **H-3.3**.

NOTES

1 The UV source is an array of fluorescent lamps (with lamp emission concentrated in the UV range).

2 Condensation is produced by exposing the test surface to a heated, saturated mixture of air and water vapour, while the reverse side of the test specimen is exposed to the cooling influence of ambient room air.'

(Page 17, Annex H, *Heading*) — Substitute 'Annex J' for 'Annex H'.

(TXD 31)

Publication Unit, BIS, New Delhi, India