

AMENDMENT NO. 3 JANUARY 2026
TO
IS 17265 : 2023 TEXTILES — 100 PERCENT POLYESTER SPUN GREY AND
WHITE YARNS — SPECIFICATION
(*Second Revision*)

(Page 1, clause 3.5) — Substitute the following for the existing:

‘3.5 Multifold or Cabled Yarn — A yarn in which two or more folded yarns are twisted together in one or more operations.’

(Page 1, clause 3.7) — Substitute the following for the existing:

‘3.7 Folded or Plied Yarn — A yarn in which two or more single yarns are twisted together in one operations.’

[Page 5, clause 6.1, Last line (see also Amendment No. 1)] — Insert the following at the end:

‘The core spun yarn shall meet the physical and chemical requirements specified in Table 3 [SI No. (i), (ii), (vi), (vii), (viii) and (ix) only] and Table 4 depending upon whether the yarn is made from virgin fibers or recycled/blended fibres in addition to those specified in Table 5, Table 6, Table 7 and Table 8 (optional) and in 6.3 to 6.7 and 6.8 (optional).’

[Page 12, Table 3, SI No. (vii)] — Insert the following at the end:

SI No.	Characteristics	Requirements						Method of Test, Ref to
		Virgin Polyester Yarn			Recycled Polyester Yarn			
		Ring Spun	Air Jet	Air Vortex	Ring Spun	Air Jet	Air Vortex	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
‘viii)	Average single yarn tenacity for core spun yarn (RKM), g/tex, <i>Min</i>							IS 1670
	a) 37 tex or coarser (Up to 16s Ne)	40	-	-	38	-	-	
	b) 18.5 tex to below 37 tex (Above 16s Ne to up to 32s Ne)	38	-	-	36	-	-	
	c) 12 tex to below 18.5 tex (Above 32s Ne to up to 50s Ne)	37	-	-	35	-	-	
	d) 7.9 tex to below 12 tex (Above 50s Ne to up to 75s Ne)	36	-	-	34	-	-	
	e) Below 7.9 tex (Above 75s Ne)	34	-	-	32	-	-	
	CV, percent, <i>Max</i>							
	a) 37 tex or coarser (Up to 16s Ne)	10	-	-	10.5	-	-	

Amendment No. 3 to IS 17265 : 2023

‘SI No.	Characteristics	Requirements						Method of Test, Ref to
		Virgin Polyester Yarn			Recycled Polyester Yarn			
		Ring Spun	Air Jet	Air Vortex	Ring Spun	Air Jet	Air Vortex	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
	b) 18.5 tex to below 37 tex (Above 16s Ne to up to 32s Ne)	11	-	-	11.5	-	-	
	c) 12 tex to below 18.5 tex (Above 32s Ne to up to 50s Ne)	13	-	-	13.5	-	-	
	d) 7.9 tex to below 12 tex (Above 50s Ne to up to 75s Ne)	14	-	-	14.5	-	-	
	e) Below 7.9 tex (Above 75s Ne)	15	-	-	15.5	-	-	
ix)	Elongation for core spun yarn, average, percent, <i>Min</i>							IS 1670
	a) 37 tex or coarser (Up to 16s Ne)	14	-	-	14	-	-	
	b) 18.5 tex to below 37 tex (Above 16s Ne to up to 32s Ne)	13	-	-	13	-	-	
	c) 12 tex to below 18.5 tex (Above 32s Ne to up to 50s Ne)	12	-	-	12	-	-	
	d) 7.9 tex to below 12 tex (Above 50s Ne to up to 75s Ne)	11	-	-	11	-	-	
	e) Below 7.9 tex (Above 75s Ne)	10	-	-	10	-	-	
	CV, percent, <i>Max</i>							
	a) 37 tex or coarser (Up to 16s Ne)	8.0	-	-	9.0	-	-	
	b) 18.5 tex to below 37 tex (Above 16s Ne to up to 32s Ne)	9.5	-	-	10.5	-	-	
	c) 12 tex to below 18.5 tex (Above 32s Ne to up to 50s Ne)	11.0	-	-	11.5	-	-	
	d) 7.9 tex to below 12 tex (Above 50s Ne to up to 75s Ne)	12.0	-	-	13.0	-	-	
	e) Below 7.9 tex (Above 75s Ne)	13.5	-	-	14.5	-	-	

Amendment No. 3 to IS 17265 : 2023

[Page 12, Table 3, Notes (see also Amendment No. 1)] — Insert the following at the end:

‘5 Sl No. (vii) of Table 3 is not applicable for dyed yarns.’

[Page 15, clause **6.7**, sentence 2] — Delete.

[Page 17, Table 7, Sl No. (ii), (iii), (iv), col (2)] — Delete ‘optional’.