

AMENDMENT NO. 2 APRIL 2024

TO

**IS 17373 : 2020 GEOSYNTHETICS — GEOGRIDS USED IN REINFORCED SOIL
RETAINING STRUCTURES — SPECIFICATION**

(Page 2, clause 4) — Substitute the following for existing:

‘4 TYPES OF GEOGRIDS

Geogrids shall be of the following three types based on the tensile strength and aperture size:

- a) Type 1 — Polyester knitted or woven geogrids having tensile strength in machine direction up to 400 kN/m with aperture size in machine direction and cross machine direction from 10 mm to 50 mm.
- b) Type 2 — Polyester bonded geogrids having tensile strength in machine direction up to 200 kN/m with aperture size in machine direction from 50 mm to 1 000 mm and cross machine direction from 10mm to 150 mm.
- c) Type 3 — Polyester bonded geogrids having tensile strength in machine direction up to 1 300 kN/m with aperture size in machine direction from 50 mm to 1 000 mm and cross machine direction from 50 mm to 200 mm.’

(Page 7, Annex A) — Substitute the following for the existing entries for IS 13162 (Part 2) : 2010, IS 13321 (Part 1) : 1992 and IS 14739 : 2019:

<i>‘IS No.</i>	<i>Title</i>
IS 13162 (Part 2) : 1991	Geotextiles — Methods of test: Part 2 Determination of resistance to exposure of ultraviolet light and water (xenon-arc type apparatus)
IS 13321 (Part 2) : 2022/ISO 10318-2 : 2015	Geosynthetics: Part 2 Symbols and pictograms
IS 14739 : 2021/ISO 13431 : 1999	Geotextiles and geotextile-related products — Determination of tensile creep and creep rupture behavior (<i>first revision</i>)’

(TXD 30)

Price Group 1
Publication, BIS, New Delhi