

AMENDMENT NO. 5 DECEMBER 2025
TO
IS 17427 : 2020 WOODEN (TIMBER) PALLETS FOR PACKAGING, STORAGE
AND TRANSPORTATION — SPECIFICATION

[Page 4, informal table, Sl No. (ix)] — Substitute the following for the existing:

<i>Sl No.</i>	<i>Defects</i>	<i>Grade 1</i>	<i>Grade 2</i>
ix)	Moisture content	Maximum limit 20 percent for all components of timber pallets	Maximum limit 25 percent for deck boards and unlimited for stringers and blocks

(Page 4, clause 6.2, see also Amendment No. 1) — Substitute the following for the existing:

‘6.2 Limitation of Timber Defects for Expandable Pallets

The timber shall be seasoned and the moisture content shall not exceed 25 percent for expandable pallets. The moisture content of timber shall be determined by oven dry method or electrical moisture meter as per IS 11215.’

(Page 10, clause 13, see also Amendment No. 1 and Amendment No. 4) — Substitute the following for the existing:

“13 TEST PARAMETERS

13.1 For general applications, the tests as specified in Table 4 t shall be complied with.

Table 4 Test Parameters

(Clause 13.1)

Sl No.	Test (Test Measurement)	Handling Activity or Purpose of the Test	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Stacking test (static load)	Stacking	IS 6219
ii)	Bending test (stiffness/flexural strength)	Racking	IS 6219
iii)	Bottom deck bending tests (stiffness and flexural strength of the bottom deck boards between support points)	Racking, twin track conveyors	IS 6219
iv)	Shear impact test (inclined impact plane test) (shear test, shear resistance between top and bottom decks)	Distortion resistance	IS 6219
v)	Top deck edge impact test (incline plane test/leading edge impact test) (shunting resistance of the top leading edge deck-board)	Resistance to fork arm	IS 6219

Price Group 1

Amendment No. 5 to IS 17427 : 2020

Table 4 (Concluded)

Sl No.	Test (Test Measurement)	Handling Activity or Purpose of the Test	Method of Test, Ref to
(1)	(2)	(3)	(4)
vi)	Block impact test (incline plane test) (resistance of pallet blocks to eccentric impacts at the corners)	Resistance to fork tip	IS 6219
vii)	Corner drop test	Resistance to impact	IS 6219
viii)	Compression test for blocks or stringers	Any activity that compresses blocks or stringers including stacking	IS 6219
ix)	Fork lifting test	Lifting with forklift and pallet trucks	IS 6219
NOTE — For storage purpose, the tests listed at Sl No. (v), (vi) and (ix) are not recommended.			

13.2 Factor of safety for carrying out tests as per **13.1** shall be ‘2’ for expendable pallets and ‘4’ for non-expendable pallets in line with **5.2**.

13.3 Test load level and performance limits for carrying out tests as per **13.1** shall be as per latest version of ISO 8611-2 (nominal load tests).

13.4 Rated load value (nominal load value) for the pallet shall be calculated and reported based on the applicable tests mentioned in **13.1** and as per the method to calculate nominal load value in ISO 8611-2.”

(TED 24)

Publication, BIS, New Delhi