

AMENDMENT NO. 3 DECEMBER 2025
TO
IS 17483 (PART 2) : 2020 GEOSYNTHETICS — GEOCELLS — SPECIFICATION
PART 2 SLOPE EROSION PROTECTION APPLICATION

[Page 3, Table 1, Sl No. (xi) and (xii), see also Amendment No. 1] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
xi)	Standard oxidative induction time, minutes, <i>Min</i>	100	ISO 11357-6
	or		
	High pressure oxidative induction time, minutes, <i>Min</i>	400	ASTM D 5885