

AMENDMENT NO. 2 AUGUST 2025

TO

**IS 17566 : 2021 KEY LOCKS FOR SECURITY
EQUIPMENT — SPECIFICATION**

(Page 3, clause 8.3.1) — Substitute the following for the existing:

‘All parts of the lock shall have corrosion resistant properties capable of withstanding exposure for 72 h as per IS 9844 with sodium chloride concentration of 50 ($\pm$ 10g)/litre of distilled water, maintaining the solution concentration constant till the test is complete. Those part of key lock that would not be exposed when it is installed as intended, are to be covered or sealed during the test, keeping only keyhole/s exposed. During this test, the lock shall be operated once during each 24 h period.’

(MED 24)

Price Group 1

Publication, BIS, New Delhi