

AMENDMENT NO. 2 DECEMBER 2025
TO
IS 17569 : 2021 INSULATED CONTAINERS FOR FOOD
STORAGE — SPECIFICATION

(Page 3, clause 4.1) — Substitute the following for the existing:

‘The nominal capacity of insulated containers shall be up to 20 litres. The tolerance on the nominal capacity shall be +5 percent. No negative tolerance is permitted. The capacity shall be checked as given in 7.3’

(Page 3, clause 4.1, Note) — delete.

(Page 5, clause 7.1.2.2, line 8) — Insert the following at the end:

‘In case, the material used is PET (polyethylene terephthalate), the minimum thickness shall be 0.5 mm.’

[Page 5, clause 7.1.2.8 (see also Amendment No. 1)] — Insert the following at the end:

‘NOTE — In case the inner/outlet container is made of stainless steel, it shall conform to grades N1, N2 as per IS 15997/IS 6911 or grade 304 series as per IS 5522/ IS 6911 or 316/316L as per IS 6911.’

[Page 4, clause 7.9, Note (see also Amendment No. 1)] — Substitute the following for the existing:

NOTES

1 ‘In case of serving container (like casserole, see Fig .1), leakage test is not applicable.’

2 ‘In case the product is declared leak proof by the manufacturer, only then leakage test will be applicable’.

[Page 5, clause 9.1 (see also Amendment No. 1)] — Insert the following note at the end:

‘Non-peelable sticker can be used for marking all the above details except the brand name and ISI marking. The sticker shall comply with the requirements given in Annex G.’

[Page 8, Annex F (see also Amendment No. 1)] — Insert the following at the end:

ANNEX G

(Clause 9.1)

STICKER TEST METHOD WITH ACCEPTANCE CRITERIA

<i>Sl No.</i>	<i>Test</i>	<i>Test Duration</i>	<i>Sticker Test Method</i>	<i>Tools</i>	<i>Requirement</i>	<i>Acceptance Criteria</i>
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	Visual appearance	NA	Visual inspection under light	Inspection table/white light	Free from scratches/dirt/misprint	Visually sticker shall be found ok
ii)	Material type	NA	As per supplier certificate	None	—	As decided by the product manufacturer
iii)	Dimensions (L X W)	NA	Measurement of sticker	Scale	As per approved drawing	Shall meet the dimensions declared as per drawing

Price Group 2

Amendment No. 2 to IS 17569 : 2021

Table (Continued)

<i>Sl No.</i>	<i>Test</i>	<i>Test Duration</i>	<i>Sticker Test Method</i>	<i>Tools</i>	<i>Requirement</i>	<i>Acceptance Criteria</i>
(1)	(2)	(3)	(4)	(5)	(6)	(7)
iv)	Sticker thickness check	NA	3 different points	Micrometer	As per approved drawing	Shall meet the thickness declared as per drawing
v)	Manual peel test	30 s	Try peeling from edge using finger nail for 30 s	Finger nail	Sticker shall tear or get destructed. It shall not peel off cleanly-fully	Sticker shall tear or destruct. It should not peel off cleanly-fully
vi)	Blade lift test	30 s	Insert a thin blade under any one corner of sticker and attempt to lift-peel the sticker	Blade/paper cutter	Sticker shall not lift and leave any residue	Sticker shall not lift and tear
vii)	Kerosene test (chemical/ Solvent resistant test)	30 s	Apply chemical/solvent (Kerosene oil) on the sticker, rub and then try to lift the sticker	Cotton	No bubbling and print remain intact	Sticker found OK and print remains readable
viii)	Tape lift test (High adhesion tape 0.4 gauge)	10 min	Apply high standard adhesion tape 0.4 gauge on sticker and peel back 180°	Manually	Sticker should not peel off	Sticker should not peel off
ix)	Tape lift test (Paper tape low adhesion)	Few seconds	Apply Paper Tape with low adhesion on sticker and peel back 180°	Manually	No pull lifting and bubbling	No changes shall be observed in the sticker
x)	Water soak + Peel test	30 min	Soak applied sticker in water for 30 min and attempt to peel	Water bath	No delamination of sticker and no edge lifting	No delamination of sticker and edge lifting shall occur

Amendment No. 2 to IS 17569 : 2021

Table (Concluded)

<i>Sl No.</i>	<i>Test</i>	<i>Test Duration</i>	<i>Sticker Test Method</i>	<i>Tools</i>	<i>Requirement</i>	<i>Acceptance Criteria</i>
(1)	(2)	(3)	(4)	(5)	(6)	(7)
xi)	Soil test	24 h	apply mix soil (fine/dry partial soil) on sticker and keep under observation for 24 h	Manually	Sticker must tear or get destructed. Should not peel off cleanly-fully	Sticker must tear or get destructed. Should not peel off cleanly-fully
xii)	Detergent test	24 h	Apply soapy solution on sticker and keep under observation for 24 h	Detergent and cotton	No delamination and bubbling	No delamination and bubbling shall occur
xiii)	Hot water temperature test	24 h	Apply sticker on hot water bottle of 95° and keep under observation	Thermometer	No delamination and edge lifting	After 24 h no visual defect shall be observed
xiv)	Cold water temperature test	24 h	Apply sticker on cold water bottle at 5 degree and keep under observation	Deep freezer	No delamination and bubbling	No delamination and bubbling shall occur
xv)	Scrubber test	20 s	Rub with scrubber on sticker along with detergent for 20 s	Scrubber	No delamination and bubbling	No delamination and bubbling shall occur
NOTE — 15 Tests have been given out of which the sticker shall comply with tests given at Sl No. (i), (ii), (viii), (x), (xii), (xiii) and (xiv).						