

AMENDMENT NO. 1 JULY 2003
TO
IS 10131 : 1992 LINK CHAIN ENDS AND CHAIN BOWS
FOR BUCKET ELEVATORS — SPECIFICATION

(First Revision)

(Page 8, Annex A) — Substitute the following for the existing

ANNEX A
(Clauses 6.1 and 6.2)

**A-1 RECOMMENDED VALUE OF CASE DEPTH AND HARDNESS
FOR CHAIN ENDS**

<i>Nominal Chain Size, d_n</i>	<i>Case Depth</i>	<i>Tolerance on Case Depth</i>	<i>Surface Hardness, HRC</i>
mm	mm	mm	
12 to 28	$0.1 d_n$	$\pm 0.01 d_n$	58 to 62
30 to 42	$0.1 d_n$	$\pm 0.01 d_n$	
		$\pm 0.01 d_n$	

**A-2 RECOMMENDED VALUE OF FLAME/INDUCTION HARDENING
DEPTH AND HARDNESS FOR CHAIN BOWS**

Depth of hardening at seat = $0.1 d_1$ mm

Surface hardness at seal = 55 to 60 HRC