



AMENDMENT NO. 1 JANUARY 1987

TO

IS:10140-1982 SPECIFICATION FOR BANDSAW
BLADES FOR WOODWORKING

(Page 3, clause 5) - Substitute the following
for the existing clause:

'5. Material - The low alloy cold rolled steel strips
in hardened, tempered and polished condition having
the following composition:

For Narrow Bandsaws:

Carbon	-	0.7 percent, Min
Sulphur	-	0.04 percent, Max
Phosphorus	-	0.04 percent, Max
Chromium	-	0.1 to 0.4 percent
Nickel	-	0.4 to 0.7 percent

For Wide Bandsaws:

Carbon	-	0.7 percent, Min
Sulphur	-	0.02 percent, Max
Phosphorus	-	0.02 percent, Max
Chromium	-	0.15 percent, Max
Nickel	-	1.8 to 2.5 percent

(ISC 45)

Reprography Unit, ISI, New Delhi, India