

**AMENDMENT NO. 1 MARCH 2002
TO
IS 10146 : 1982 SPECIFICATION FOR
POLYETHYLENE FOR ITS SAFE USE IN CONTACT
WITH FOODSTUFFS, PHARMACEUTICALS AND
DRINKING WATER**

(Page 6, clause 3.4) — Substitute the following for the existing matter:

3.4 Overall Migration — The material shall comply with the overall migration limits of 60 mg/l, *Max* of simulants and 10 mg/dm², *Max* of the surface of the material or article when tested by the method prescribed in IS 9845 : 1998†.

[Page 6, footnote with (†) mark] — Substitute the following for the existing footnote.

‘†Determination of overall migration of constituents of plastics materials and articles intended to come in contact with foodstuffs — Method of analysis (second revision) ’

(PCD 12)