

AMENDMENT NO. 1 JULY 2026
TO
IS 10153 : 2021 UTILIZATION OF FLY ASH — GUIDELINES
(First Revision)

(Page 1, clause 2) — Insert the following reference at the appropriate place:

<i>'IS No.</i>	<i>Title</i>
IS 16415 : 2015	Composite cement — Specification'

(Page 2, clause 5.1) — Substitute the following for the existing:

'Portland pozzolana cement (using fly ash as pozzolana) should be manufactured either by intergrinding Portland cement clinker, fly ash and gypsum or by intimately and uniformly blending Portland cement and fly ash in accordance with IS 1489 (Part 1). Composite cement (fly ash as pozzolana) should be manufactured by either intergrinding with clinker, slag and gypsum or by intimately and uniformly blending with ordinary Portland cement, gypsum and slag in accordance to IS 16415.'

(Page 2, clause 5.2) — Substitute the following for the existing:

'The intergrinding method does not involve any major addition to the plant and equipment already available at a cement factory. The blending process requires installation of a suitable blender or homogenizer. In India, Portland-pozzolana cement (using fly ash as pozzolana) is being produced over the past few years by the intergrinding process. Composite cement is being manufactured by both intergrinding and separate grinding and mixing process.'

(Page 2, clause 5.3, sentence 2) — Substitute the following for the existing:

'The Portland pozzolana cement (using fly ash as pozzolana) having its strength at par with that of ordinary Portland cement at 7 days and conforming to the other requirements of IS 1489 (Part 1) can be used in place of ordinary Portland cement in construction works and composite cement as per IS 16415.'

(Page 2, clause 6.2, sentence 1) — Substitute the following for the existing:

'The fly ash concrete mix is specially proportioned in order to attain required 28 days compressive strength optimally, equal to that of the corresponding mix of plain cement concrete and 28 days compressive strength of concrete as per IS 456.'