

**AMENDMENT NO. 1 APRIL 2003
TO
IS 10357 : 1990 GENERAL PURPOSE
FURNACE [GPF(N-660)] CARBON
BLACK — SPECIFICATION**

(First Revision)

[Page 1, Table 1. *Sl No.* (i), *col 2*] — Substitute 'Iodine adsorption' for 'Iodine absorption'.

(Page 1, clause **4.4**, line 5) — Substitute 'IRB No. 7' for 'IRB No. 6'.

(Page 2, clause **B-1.1**, line 6) — Substitute 'Industry Reference Black No. 7' for 'Industry Reference Black No. 6'.

(Page 3, clause **B-4.1**, line 1) — Substitute '30 minutes' for '15 and 30 minutes'.

(Page 3, clause **B-6.1**, line 3) — Substitute 'IRB No. 7' for 'IRB No. 6'.

(Page 3, Table 2) — Substitute the following for the existing:

**Table 2 Difference in Physical Properties of Vulcanizates Containing
GPF Carbon Black from IRB No. 7**

<i>(Clause B-6.1)</i>		
Cure Conditions	Tensile Strength <i>Min, MPa*</i>	300 Percent Modulus, MPa*
(1)	(2)	(3)
30 min at 145°C	-6.5	-4.95 to -1.95

*1 MPa = approximately 10.2 kgf/cm².

(PCD 13)