

AMENDMENT NO. 1 APRIL 2003
TO
IS 10358 : 1991 CARBON BLACK, SUPER ABRASION
FURNACE [SAF N-110] — SPECIFICATION
(First Revision)

(Page 5, clause C-1, line 6) — Substitute 'IRB No. 7' for 'Indian Reference Black No 6'

(Page 6, clause C-4, line 1) — Substitute '30 minutes' for '15 and 30 min'.

(Page 6, clause C-6.1, line 3) — Substitute 'IRB No 7' for 'IRB No 6'.

(Page 6, Table 2) — Substitute the following for the existing:

**Table 2 Difference in Physical Properties of Vulcanizates Containing
[SAF (N-110)] Carbon Black from IRB No. 7**

Sl No.	Cure Conditions	Tensile Strength Min, MPa*	300 Percent Modulus MPa*
(1)	(2)	(3)	(4)
1)	30 min at 145°C	-2.66	-4.65 to -1.65

*1 MPa = approximately 10.2 kgf/cm²

(PCD 13)