

AMENDMENT NO. 1 APRIL 2003
TO
IS 10387 : 1990 SEMI-REINFORCING FURNACE
[SRF-LM-NS(N-762) AND SRF-HM-NS (N-774)] CARBON
BLACK — SPECIFICATION

(*First Revision*)

(*Page 1, clause 5.4, line 4*) — Substitute 'IRB No. 7.' for 'IRB No. 6.'

[*Page 1, Table 1, Sl No.(i), col 2*] — Substitute 'Iodine Adsorption, as mg of Iodine/g of Carbon Black (ml/100 g of Carbon Black)' for 'Iodine adsorption, as mg of iodine, carbon black'.

[*Page 1, Table 1, Sl No. (ii)*] — Substitute 'Di butyl phthalate absorption ml/100g' for 'Dibutyl phthalate absorption'.

(*Page 2, clause B-1.1, line 6*) — Substitute 'IRB No. 7' for 'Industry Reference Black No. 6'.

(*Page 3, clause B-4.1, line 1*) — Substitute '30 minutes' for '15 and 30 minutes'.

(*Page 3, clause B-6.1, line 3*) — Substitute 'IRB No. 7' for 'IRB No. 6'.

(*Page 3, Table 2*) — Substitute the following for the existing:

Table 2 Difference in Physical Properties of Vulcanisates Containing SRF Carbon Black from IRB No. 7

Sl No.	Grade	Cure Conditions	Tensile Strength, Min, MPa*	300 Percent Modulus MPa*
(1)	(2)	(3)	(4)	(5)
i)	SRF-LM	30 min at 145 OC	-6.23	-7.25 to - 2.05
ii)	SRF-HM	30 min at 145 OC	-5.08	-6.05 to -3.05

*1 MPa = approximately 10.2 kgf/cm².