

AMENDMENT NO. 1 SEPTEMBER 1987
TO
IS : 9101-1979 METHODS OF SAMPLING
IRON ORE PELLETS

[In order to clarify the procedure of taking unit samples from a moving conveyor belt by manual method and also to specify the dimensions of increment scoop, the Methods of Sampling Sectional Committee responsible for the preparation of this standard, decided to issue the following amendment.]

(*Page 3, clause 0.6*) — Substitute the following for the existing clause:

'0.6 For the determination of size distribution of iron ore pellets, sieves conforming to IS : 460 (Part 1)-1985* and IS : 460 (Part 2)-1985† shall be used. When such sieves are not available, other equivalent standard sieves as judged by the aperture may be used.'

(*Page 3, foot-note with '*' mark*) — Substitute the following for the existing foot-note:

***Specification for test sieves: Part 1 Wire cloth test sieves (*third revision*).**

†Specification for test sieves: Part 2 Perforated plate test sieves (*third revision*).

(*Page 4, clause 2.4*) — Substitute the following for the existing clause:

'2.4 The quantity of pellets collected by one or more operations of sampling device from the conveyor (unit sample is larger than the increment specified in Table 3).'

(*Page 4, clause 2.9, line 1*) — Delete the words '**for the Lot**'.

(*Page 5, clause 2.10*) — Substitute the following for the existing clause:

'2.10 The sample collected from a sub-lot or from the composite sample of a lot (see 2.9) for determining the physical characteristics of a lot or sub-lot.'

(*Page 5, Table 1, under col 'D', against '2.5 kg'*) — Substitute '**150**' for '**155**'.

(*Page 8, clause 4.2.5, Note*) — Substitute the following for the existing Note:

'NOTE — When a sampling scoop of 2.5 kg size is used for manual sampling in the above manner on a moving conveyor belt by thrusting the scoop in the pellet stream, a unit sample of 25 kg shall be drawn by taking successive increments across the stream. In such cases, the number of unit samples shall be adjusted in such a way as to get the minimum mass of gross sample.'

(Page 10, clause 4.4.2, third sentence) — Add the following at the end of the sentence:

‘by other means’.

(Page 11, clause 5.2.1, first sentence) — Delete the words within the bracket.

(Page 14, Table 6) — Substitute the following for the existing table:

TABLE 6 INCREMENT SCOOP DIMENSIONS, THICKNESS OF LAYERS AND SIZE OF INCREMENT

(Clause 5.3.1)

MAXIMUM PARTICLE SIZE mm	THICKNESS OF LAYER mm	INCREMENT SCOOP DIMENSIONS				SIZE OF INCREMENT (g)
		<i>a</i>	<i>b</i>	<i>c</i>	<i>d</i>	
(1)	(2)	(3)	(4)	(5)	(6)	(7)
10.0	30 to 40	60	35	60	50	250
5.0	25 to 35	50	30	50	40	150
3.5	20 to 30	40	25	40	30	75
2.0	15 to 25	35	20	35	30	50
1.0	10 to 20	30	15	30	25	25
0.25	5 to 10	15	10	15	12	5

NOTE — *a, b, c, d* are the dimensions of bottom length, height, width and top length of increment scoop respectively.

(Page 14, clause 6.2.1, third sentence, line 1) — Substitute the following for the existing line:

‘This crushed sample fraction along with the uncrushed fraction under 10 mm size shall be mixed and from’.

(Page 17, clause 7.3, line 8 and last line) — Substitute ‘Under 6.3 mm’ for ‘6.3 mm and below’.

(Page 17, clause 7.4, line 8) — Substitute ‘Under 6.3 mm’ for ‘6.3 mm and below’.

(Page 18, clause 8.1.1) — Substitute the following for the existing clause:

‘8.1.1 The method for determination of moisture content shall be in accordance with the procedure given in IS : 11690-1986 Methods of moisture determination of iron ore lot.’

(SMDC 4)