

AMENDMENT NO. 1 FEBRUARY 2018
TO
IS 9113 : 2012 TEXTILES — JUTE SACKING — GENERAL
REQUIREMENTS

(Second Revision)

(Page 7, Annex E, clauses E-3, E-4, E-4.1, E-4.2 and E-4.3) — Substitute the following for the existing clauses:

E-3 Sample Size of Bags

For freedom from defects, length, width, ends/dm, picks/dm, number of stitch/dm, mass per bag and moisture regain, 7 bags shall be selected at random from each bale selected as per E-2. The total number of bags to be tested from each lot for these requirements is given in col 5 of Table 4.

Table 4 Sample Size and Acceptance Number
(Clauses E-2, E-3, E-4.1, and E-4.3)

Sl No.	No. of Bales in the Lot	No. of Bales in the Sample	For Number of Stitches/dm, Ends/dm, Picks/dm, Moisture Regain		
			No. of Bags from Each Bale	Total Number of Bags in Sample	Acceptance Number
(1)	(2)	(3)	(4)	(5)	(6)
i)	Up to 25	5	7	35	5
ii)	26 to 90	8	7	56	6
iii)	91 to 300	12	7	84	8
iv)	301 to 500	18	7	126	10

NOTE — If the number of bales in a consignment exceeds 500, the same shall be split into number of lots each comprising maximum of 500 bales. Joined bags shall also be drawn during sampling of bags for visual inspection and breaking strength test.

E-4 CRITERIA FOR CONFORMITY

E-4.1 Criteria for Conformity for Freedom from Defects

Each bag selected in the sample shall be tested for freedom from defects. A

Amendment No. 1 to IS 9113 : 2012

bag shall be termed as defective, if it contains two or more major defects (*see* Annex C). A lot shall be considered conforming to this requirement, if the number of defectives is less than or equal to the acceptance number given in col 6 of Table 4. Acceptance numbers given in Table 4 are on the basis of an AQL of 4.0 percent.

E-4.2 Criteria for Conformity for Length and Width

The dimension of at least 90 percent of the bags under test is in accordance with the requirement specified. Out of the remaining bags (10 percent, *Max*), dimension of not a single bag is below specified nominal value by more than 2.0 cm and 1.0 cm in case of length and width, respectively.

E-4.3 Criteria for Conformity for Ends/dm, Picks/dm, Number of Stitches/dm and Moisture Regain

The lot which meets requirements of **E-4.1** and **E-4.2** shall be tested for ends/dm, picks/dm, number of stitches/dm and moisture regain as per the plan. A bag shall be termed as defective, if it fails to meet any one or more of these requirements. The lot shall be considered as conforming to the requirements of ends/dm, picks/dm, number of stitches/dm and moisture regain, if the total number of defectives found in the sample is less than or equal to the corresponding acceptance number given in col 6 of Table 4.

E-4.4 Criteria for Conformity for Mass per Bag

The lot, which meets the above requirements, shall then be tested for mass of bag. The lot shall be declared as conforming to this requirements, if

- a) the average corrected value of mass per bag as obtained for sampled bags under test is not less than nominal value specified.
- b) the corrected mass of at least 80 percent of bags under test is in accordance with requirement specified.
- c) out of remaining bags (20 percent, *Max*), all bags may have corrected mass above the specified limit, but corrected mass of not more than 10 percent of sampled bags under test is below the specified value by more than 12 percent of specified nominal value.'

(TXD 03)