

AMENDMENT NO. 2 MARCH 2026
TO
IS 9168 : 2018 AUTOMOTIVE VEHICLE — ALL RUBBER FLAPS FOR
PNEUMATIC TYRES — SPECIFICATION
(Second Revision)

(Page 1, clause 2) — Substitute the following for the existing:

‘2 REFERENCES

The standards given below contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards:

<i>IS No.</i>	<i>Title</i>
IS 3400 (Part 1) : 2021/ ISO 37 : 2017	Methods of test for vulcanized rubber: Part 1 Tensile stress-strain properties (<i>fourth revision</i>)
IS 3400 (Part 2/Sec 4) : 2022/ISO 48-4 : 2018	Methods of test for rubber, vulcanized or thermoplastic: Part 2 Determination of hardness, Section 4 Indentation hardness by durometer method (shore hardness) (<i>second revision</i>)
IS 3400 (Part 4) : 2012/ ISO 188 : 2011	Methods of test for vulcanized rubber: Part 4 Accelerated ageing and heat resistance (<i>third revision</i>)
IS 15633 : 2022	Automotive vehicles — Pneumatic tyres for passenger car vehicle — Diagonal and radial ply — Specification (<i>first revision</i>)’

[Page 2, clause 5.2 (see also Amendment No. 1)] — Substitute the following for the existing:

‘5.2 Hardness

The shore hardness of the unused finished flap before heat ageing shall lie between 45 and 65, when measured by Shore Type ‘A’ durometer. The hardness shall be measured at or on test piece cut from centre of the flap as per test method given in IS 3400 (Part 2/Section 4).’

(TED 07)

Price Group 1
Publication, BIS, New Delhi