

AMENDMENT NO. 1 AUGUST 2026
TO
IS 9267 : 2021 TEXTILES — TUBULAR NYLON WEBBING FOR AEROSPACE
PURPOSES — SPECIFICATION
(*First Revision*)

(Page 1, clause 3.1) — Substitute the following for the existing:

‘3.1 The nylon 6,6 yarn shall be used for the manufacturing of the webbing and it should be bright, light and heat resistant and of high tenacity. The universal count of single yarn shall be 93 tex $\pm$ 10 percent (840 denier $\pm$ 10 percent). The twist in the final yarn shall be not less than 100 turns per metre. Chrome dyes shall not be used since they have a tendency to deteriorate the life of the nylon webbing [see IS 4472 (Part 3)].’

(Page 2, Table 1) — Substitute the following for the existing:

‘Table 1 Physical Requirements of Tubular Nylon Webbing

(Clauses 5.1 and 5.3)

Sl No.	Characteristics	Requirements						Method of Test, Ref to
		Type 1	Type 2	Type 3	Type 4	Type 5	Type 6	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
i)	Width, mm (<i>see</i> Note 1)	13.0	14.5	16.0	19.0	22.0	22.5	IS 1954
ii)	Length, m/spool	350 to 360	280 to 290	225 to 235	170 to 180	135 to 145	110 to 120	IS 1954
iii)	Thickness, mm, <i>Max</i>	2.3	2.3	2.5	3.0	3.0	3.0	IS 7702
iv)	Ends in full width, <i>Min</i>	111	137	89	109	121	159	IS 1963
v)	Picks per cm, <i>Min</i>	10	10	10	10	10	10	IS 1963
vi)	Mass g/m, (<i>see</i> Note 2) <i>Max</i>	16	19	24	31	42	53	IS 1964
vii)	Minimum number of folds in final yarn:							Visual
	a) Warp	1	1	2	2	2	2	
	b) Weft	1	1	2	2	1	2	
viii)	Breaking strength on 20 mm strip, kgf (kN), <i>Min</i>	460 (4.5)	680 (6.7)	1 020 (10.0)	1 045 (10.2)	1 400 (13.8)	1 815 (17.8)	IS 1969 (Part 1)
ix)	Shrinkage, warpway, percent, <i>Max</i>	2	2	2	2	2	2	IS 2977
NOTES 1 A tolerance of $\pm$ 1.5 mm shall apply to the width of the webbing. 2 A relaxation of + 5 percent in mass shall be permitted for dyed webbings.								

(TXD 13)

Price Group 1
Publication, BIS, New Delhi