

AMENDMENT NO. 2 FEBRUARY 2010
TO
IS 9271 : 2004 UNPLASTICIZED POLYVINYL CHLORIDE
(UPVC) SINGLE WALL CORRUGATED PIPES FOR
DRAINAGE — SPECIFICATION

(*First Revision*)

(Page 2, Table 1) — Substitute the following for the existing table:

Table 1 Dimensions of Corrugated Single Wall Pipes
(Clause 7)

Sl No.	Nominal Outside Diameter of Pipe, d_n mm	Tolerance mm	Inside Diameter of Pipes, d_i Min mm
(1)	(2)	(3)	(4)
i)	40	± 0.5	32
ii)	50	± 0.5	40
iii)	65	± 0.5	55
iv)	80	± 0.5	72
v)	100	± 0.5	88
vi)	125	± 0.5	112
vii)	160	$\begin{cases} +0.5 \\ -1.0 \end{cases}$	144
viii)	200	$\begin{cases} +0.5 \\ -1.0 \end{cases}$	178
ix)	250	$\begin{cases} +0.5 \\ -1.0 \end{cases}$	225
x)	294	$\begin{cases} +0.5 \\ -1.0 \end{cases}$	258
xi)	315	± 1.0	280
xii)	355	± 1.0	315
xiii)	400	± 1.2	360
xiv)	455	± 1.2	401
xv)	500	± 1.5	450

Amend No. 2 to IS 9271 : 2004

(Page 3, clause 7.4.1, line 8) — Delete ‘Perforations should not be made by punching method’.

(Page 3, clause 7.4.3) — Substitute the following for the existing:

‘The depth of corrugations shall be 3 percent, *Min* of nominal outside diameter (d_n).’

(Page 3, clause 8.6, line 2) — Substitute ‘splitting, cracking or kinking’ for ‘splitting or cracking’.

(CED 50)