

AMENDMENT NO. 1 MAY 2002
TO
IS 9288 : 1979 SPECIFICATION FOR CYANURIC
CHLORIDE

(Page 4, clause 2.2) — Insert the following new clause after 2.2:

2.3 Particle Size — Not more than 2.0 percent by mass of the material shall be retained on 250 micron IS Sieve [IS 460 (Part 1) : 1985] and not more than 8.0 percent by mass of material shall be retained on 150 micron IS Sieve when tested in accordance with method given in A-5.

(Page 8, clause A-4.1.1) — Insert the following new clause after A-4.1.1:

A-5 PARTICLE SIZE

Transfer 25.0 g of the sample to the designated sieve and replace the lid. Start sieving gently by banging on a pad of latex foam or similar material. Brush the residue gently with a camel hair brush to ensure that any remaining soft aggregates are broken down, calculate and report the percentage retained on each sieve.

NOTE — Safety precautions as detailed for this test must be followed strictly. The test must be carried out in a fuming cupboard and rubber gloves, respirator and plastic apron must be worn. Base and sides of fuming cupboard must be lined with paper before commencing the test. After completion of test, transfer residue and the material passing through the sieves to a beaker containing about 1.5 litre of 10 percent sodium hydroxide solution. Mix well and allow to stand overnight in the fuming cupboard. Finally pour down the waste in sink followed by flow of cold water. Wipe the lining paper with a cloth soaked in 10 percent sodium hydroxide solution and screw up the paper in an outside dust bin.

A-5.1 Calculation

$$\% \text{ Retained on 250 micron sieve} = 4 \times X$$

where

X = g of sample retained on 250 micron sieve and

$$\% \text{ Retained on 150 micron sieve} = 4 \times (X + Y)$$

where

X = g of sample retained on 250 micron sieve, and

Y = g of sample retained on 150 micron sieve.

(PCD 11)