

AMENDMENT NO. 1 DECEMBER 2022
TO
IS 9308 (PART 3) : 2020 SPECIFICATION FOR MECHANICALLY
EXTRACTED COIR FIBRES
PART 3 DECORTICATED COIR FIBRE
(Second Revision)

(Page 5, Annex D) — Substitute the following for the existing:

‘ANNEX D
(Clauses 5.4 and 7.2)

METHOD FOR DETERMINATION OF MOISTURE CONTENT IN BRISTLE FIBRE

D-1 APPARATUS

D-1.1 Conditioning Oven — With forced ventilation, provided with positive valve control and capable of maintaining a temperature of 100 °C to 110 °C.

D-1.2 Weighing Balance — Capability to weigh bristle coir fibre with an accuracy of 0.5 g.

D-1.3 Desiccator

D-2 PROCEDURE

D-2.1 Remove about 50 g of coir fibre from the test sample (*see 9.1.4.1*) and weigh it correct to the nearest 0.5 g. Place the test specimen in the conditioning oven and dry for one hour at a temperature of 100 °C ± 2 °C and cool the specimen to room temperature in the desiccators and determine its weigh to the nearest 0.5 g. Dry for another 15 min and weigh to the nearest 0.5 g. Provided the loss in mass in drying of the test specimen, as disclosed by the first and second weighings, does not exceed 0.25 percent of the first mass. Take the second mass to be the dry mass of the test specimen. If the loss exceeds 0.25 percent, weigh the test specimen at 15 min intervals till the loss between two successive weighings is 0.25 percent or less.

D-2.2 Calculate the percentage of moisture content by the following formula:

$$\text{Moisture content, percent by mass} = \frac{(m_1 - m_2)}{m_1} \times 100$$

Where

m_1 = Mass of the original test specimen, and
 m_2 = Mass of the oven-dried test specimen.’