

AMENDMENT NO. 2 MAY 2002
TO
IS 9344 : 1979 DIMENSIONS OF TOROIDAL
STRIP-WOUND CORES OF MAGNETICALLY SOFT
MATERIAL

[This amendment is largely based on Amendment 1(1997) to IEC 60635(1978) issued by the International Electrotechnical Commission(IEC).]

(Page 5, Table 2) — Substitute the following for the existing table:

Table 2 Strip Thickness and Stacking Factor
(Clause 4.2)

Nominal Strip Thickness mm	Nominal Stacking Factor (α)	
	Nickel Iron and Cobalt Iron Alloys	Oriented Silicon Steel
(1)	(2)	3)
0.27 - 0.35	0.95	0.95
0.23	—	0.94
0.20	0.93	—
0.15	0.92	—
0.10	0.90	0.92
0.05	0.85	0.88
0.025(0.030)	0.80	0.82
0.015	0.70	—
0.01	0.62	—
0.006	0.50	—
0.003	0.35	—
NOTE — In the case of thick material 0.27 to 0.35 mm a range of thickness has been given because several grades of material are produced in different thickness.		

(LTD 13)