

AMENDMENT NO. 1 JULY 1978
TO
IS : 10 (Part III)-1974 SPECIFICATION FOR
PLYWOOD TEA-CHEST

PART III BATTENS

(Fourth Revision)

Alterations

(Page 4, clause 2.1, line 1) — Substitute ' IS : 707-1976*' for ' IS : 707-1968* '.

(Page 4, Note under clause 3.1) — Delete.

(Page 4, clause 4.1.1, line 1) — Substitute '[see IS : 10 (Part I)-1976†]' for '(see IS : 10-1970†)'.

(Page 4, foot-notes with marks '*' and '†') — Substitute the following for the existing foot-notes:

'*Glossary of terms applicable to timber technology and utilization (*second revision*).
†Specification for plywood tea-chests: Part I General (*fourth revision*).'

(Page 5, clause 4.1.1.1, line 1) — Substitute ' IS : 10 (Part I)-1976*' for ' IS : 10-1970* '.

(Page 5, foot-note with mark '*') — Substitute the following for the existing foot-note:

'*Specification for plywood tea-chests: Part I General (*fourth revision*).'

(Page 6, clause 5.1.1.2) — Substitute the following for the existing clause:

'5.1.1.2 *Insect holes* — Live insect holes shall not be permitted. Dead insect holes may be permitted up to a maximum of four per batten provided these are only pin holes (that is, maximum dia 2 mm) and provided these are well scattered such that these do not impair the strength of the batten. '

(Page 6, clause 6.1, last sentence) — Substitute the following for the existing sentence:

' However, for tea-chests of any size used for packing instant tea, all the battens may be finished with square ends and with chamferred edges. '

(*Page 9, Table 1, heading of col 4*) — Substitute the following for the existing heading:

‘SUB-SAMPLE FOR MOISTURE CONTENT’

(*Page 10, clause B-3.2*) — Substitute the following for the existing clause:

‘B-3.2 Test for Moisture Content—The number of battens to be tested for moisture content (*5.1.2*) is given in col 4 of Table 1. These shall be taken at random from those inspected under **B-3.1** and found conforming to visual and dimensional requirements. ’

(*Page 10, clause B-3.2.1*) — Substitute the following for the existing clause:

‘B-3.2.1 The individual test results for each batten shall be noted and from these test results, the average ($\bar{X}$) and the range (R) shall be calculated as follows:

$$\text{Average (} \bar{X} \text{)} = \frac{\text{The sum of test results}}{\text{Number of test results}}$$

Range (R) = ‘The difference between the maximum and the minimum values of the test results. ’

(*Page 10, Table 2*) — Delete.

Addenda

(*Page 6, clause 7*) — Add the following new clause after clause 7 and renumber clauses ‘ *7.1* and *7.2* ’ as ‘ *7.1.1* and *7.1.2* ’, respectively:

‘7.1 Type Test — For the determination of the suitability of species of timber, tests given under *7.1.1* and *7.1.2* shall be carried out. However, once the suitability and identity of a species is established, further testing of battens, manufactured from the same species in a particular lot, for these two requirements may not be necessary.

NOTE — However, in case where battens are being manufactured and supplied regularly, these tests shall be conducted periodically at least twice in a year. ’

(*Pages 7 and 8, Appendix A*) — Add mark ‘ † ’ against the species mentioned at SI No. 1, 2, 4, 5, 7, 11, 15, 16, 19, 20, 23, 24, 27, 28, 30, 33, 40, 42, 43, 45, 46, 47, 48, 49, 50 and 51.

(*Page 8, foot-note*) — Add the following new foot-note after the existing foot-note:

‘ †Species generally recommended for battens for tea-chests for export purposes. ’

(*Page 10, clause B-3.2.1*) — Add the following new clause after **B-3.2.1**:

B-3.2.2 A lot shall be declared conforming to the requirements of moisture content only if the value of the expression $(\bar{X} + 0.4 R)$ is less than or equal to the specified value.

NOTE — R is to be calculated if the number of test results is less than 10. In case the sample size is 10 or more, $\bar{R}$ based on the sub-groups of five samples each, is to be calculated and used in place of R .

(BDC 20)