

AMENDMENT NO. 2 OCTOBER 1997
TO
IS 177 : 1989 COTTON DRILLS — SPECIFICATION
(*Fourth Revision*)

[*Page 3, Table 2, Sl No. i(b), col 2*] — Delete the words '(see Note 2)'.

(*Page 3, Table 2, Note 2*) — Delete Note 2 and renumber the subsequent Note and its reference in col 2 against Sl No. i(c).

[*Page 3, Table 2, Sl No.(vii), col 2*] — Insert the words '(see Note 3)' in the end and incorporate Note 3 as under at the end of the table:

'3 In case of fabric dyed with mineral *Khaki* shade, the barium activity number shall be determined after stripping the dye. The specimens shall be extracted with chloroform for one hour in a Soxhlet apparatus. The samples shall be treated with 5% hydrochloric acid at boil maintaining material to liquid ratio as 1 : 50 till the entire dye is stripped off. The samples shall then be washed with water and then boiled in soap-soda (5 g/j - g/j) solution for 30 minutes. Test specimen shall then be dried and conditioned in standard atmosphere.'

(TX 02)