

AMENDMENT NO. 1 AUGUST 2017
TO
IS 383 : 2016 COARSE AND FINE AGGREGATE FOR
CONCRETE — SPECIFICATION

(Third Revision)

[Page 2, Table 1, Sl No. (i) (e)] — Delete.

[Page 2, Table 1, Sl No. (ii) (d)] — Insert the following new entry:

Sl No.	Type of Aggregate	Maximum Utilization		
		Plain Concrete Percent (3)	Reinforced Concrete Percent (4)	Lean Concrete (Less than M15 Grade), Percent (5)
(1)	(2)			
ii)	e) Bottom ash from thermal power plants	Nil	Nil	25

[Page 5, Table 3, Sl No. (iii)] — Substitute the following for the existing entry:

Sl No.	Characteristic	Requirement
(1)	(2)	(3)
iii)	Water soluble chloride content, percent, <i>Max</i>	0.04