

AMENDMENT NO. 1 MAY 2000
TO
IS 398 (PART 4) 1994 ALUMINIUM CONDUCTORS
FOR OVERHEAD TRANSMISSION PURPOSES
PART 4 ALUMINIUM ALLOY STRANDED CONDUCTORS
(ALUMINIUM-MAGNESIUM-SILICON TYPE) — SPECIFICATION
(*Third Revision*)

(*Foreword, last two sentences of para 4*) — Substitute the following for the existing:

'The maximum resistivity of 0.032 8 ohm.mm²/m at 20°C has been adopted for arriving at the calculated resistance of conductor.'

(*Page 1, clause 4.1*) — Substitute the following for the existing:

'4.1 Resistivity

For the purpose of this standard, the maximum value of resistivity of any single aluminium alloy wire which shall be used for calculation is 0.032 8 ohm.mm²/m at 20°C.'

(*Page 2, Table 1, col 5*) — Substitute '28.41' and '29.19' for '26.41' and '21.19' respectively.

(*Page 3, Table 2, col 6, Sl No.8*) — Substitute '0.229 8' for '0.229 0'.

(*Page 3, Table 2, col 6, Sl No. 14*) — Substitute '0.085 5' for '0.082 9'.

(*Page 3, clause 8.1*) — Substitute the following for the existing:

'8.1 Conductors Containing Up to Seven Wires

'There shall be no joints in any wire of a stranded conductor containing up to 7 wires except, those made in the base rod or wire before final drawing.'

(*Page 5, Annex A, col 2, title*) — Substitute 'kg/cm²' for 'G N/m²'.

(*Page 6, Annex A*) — Delete the table of 'Breakup details of revised AAAC Conductor.'

(ETD 37)