

AMENDMENT NO. 1 SEPTEMBER 2000
TO
IS 398 (PART 5) : 1992 ALUMINIUM CONDUCTOR
FOR OVERHEAD TRANSMISSION PURPOSES —
SPECIFICATION
PART 5 ALUMINIUM CONDUCTORS — GALVANIZED STEEL —
REINFORCED FOR EXTRA HIGH VOLTAGE (400 kV AND ABOVE)
(First Revision)

(Page 3, clause 10.5) — Add the following new clause:
'10.6 For the purpose of calculation of breaking load and resistance, stranding constants given in Table 5 are to be used.'

Table 5 Stranding Constant
(Clause 10.6)

No. of Wires in Conductor		Stranding Contant		
		Mass		Electrical Resistance
Aluminium	Steel	Aluminium	Steel	
(1)	(2)	(3)	(4)	(5)
42	7	43.6	7.032	0.025 15
54	7	55.458	7.035	0.026 38

(Page 4, Table 3, col 3) — Substitute '7/2.30' for '7/2.13'.

(ETD 37)