

AMENDMENT NO. 1 JUNE 2018
TO
IS 455 : 2015 PORTLAND SLAG CEMENT —
SPECIFICATION

(Fifth Revision)

(Page 2, Table 1, Note, third sentence) — Insert the following after the third sentence:

‘However, in the case of cement having a minimum slag content of 50 percent, a maximum alkali content of 0.9 percent, expressed as sodium oxide ($\text{Na}_2\text{O} + 0.658 \text{ K}_2\text{O}$) is recommended.’