

AMENDMENT NO. 2 SEPTEMBER 2005
TO
IS 456 : 2000 PLAIN AND REINFORCED CONCRETE —
CODE OF PRACTICE
(Fourth Revision)

(Page 13, clause 5.2.1.1, line 1) — Substitute 'IS 3812 (Part 1)' for 'Grade 1 of IS 3812'.

(Page 13, clause 5.2.1.2 and corresponding Note) — Substitute the following for the existing:

'Silica fume conforming to IS 15388 may be used as part replacement of cement provided uniform blending with the cement is ensured.

NOTE — Silica fume is usually used in proportion of 5 to 10 percent of the cement content of a mix.'

(Page 13, Note under clause 5.2.1.3, line 5) — Substitute 'be' for 'range from being'.

(Page 25, clause 10.3.3, line 4) — Delete the word 'and'.

(Page 65, clause 34.2.4.2, line 1) — Substitute 'on' for 'or'.

[Page 65, clause 34.3.1(a), line 2] — Delete the words 'extending in each direction'.

(Page 66, clause 34.4.3, line 5) — Substitute 'not' for 'no'.

(Page 78, Annex A) — Substitute the following for the existing entries for IS 3812 : 1981:

<i>'IS No.</i>	<i>Title</i>
IS 3812 (Part 1) : 2003	Specification for pulverized fuel ash : Part 1 For use as pozzolana in cement, cement mortar and concrete (second revision)

(Page 79, Annex A) — Add the following at the end:

<i>'IS No.</i>	<i>Title</i>
IS 15388 : 2003	Specification for silica fume

Amend No. 2 to IS 456 : 2000

(Page 80, B-2.1.1, *informal table*) — Insert the following in the table:

M55
5.6

(Page 81, Table 21) — Insert the following row after the last row:

(1)	(2)	(3)	(4)
M55	17.5	13.0	1.5'

(Page 91, Table 26, Case No. 2, col 2) — Substitute 'One Short Edge Discontinuous' for 'One Short Edge Continuous'.

[Page 96, G-1.1(c), *formula*] — Substitute ' $M_{u,lim}$ ' for ' $M_{u'lim}$ '.

[Page 96, G-1.1(d), *last line*] — Substitute '38.1' for '39.1'.