

AMENDMENT NO. 1 NOVEMBER 2019

TO

**IS 516 (PART 5/SEC 1) : 2018 HARDENED CONCRETE —
METHODS OF TEST**

PART 5 NON-DESTRUCTIVE TESTING OF CONCRETE

**SECTION 1 ULTRASONIC PULSE VELOCITY
TESTING**

(First Revision)

(Page 4, Table 1) — Substitute the following for the existing table:

Table 1 Velocity Criteria for Concrete Quality Grading
(Clause 2.5.2)

Sl No.	Average Value of Pulse Velocity by Cross Probing	Concrete Quality Grading
	km/s	
(1)	(2)	(3)
i) For concrete ($\leq M 25$):		
a)	Below 3.5	Doubtful ¹⁾
b)	3.5 – 4.5	Good
c)	Above 4.5	Excellent
ii) For concrete ($> M 25$):		
a)	Below 3.75	Doubtful ¹⁾
b)	3.75 – 4.50	Good
c)	Above 4.50	Excellent

¹⁾ In case of ‘Doubtful quality’, it shall be necessary to carry out additional tests.