

AMENDMENT NO. 2 JULY 1991
TO
IS 516 : 1959 METHODS OF TESTS FOR
STRENGTH OF CONCRETE

(*Page 6, clause 2.9.1*) — Substitute the following for the existing clause:

'2.9.1 Cube Moulds — The mould shall be of 150 mm size conforming to IS 10086 : 1982*.'

(*Page 6*) — Insert the following foot-note at the bottom:

'*Specification for moulds for use in tests of cement and concrete.'

(*Page 7, clause 2.9.2*) — Except the last sentence, substitute the following for the existing matter:

'The cylindrical moulds shall be of 150 mm diameter and 300 mm height conforming to IS 10086 : 1982*.'

(*Page 7, clause 2.9.3*) — Substitute the following for the existing clause:

'2.9.3 Tamping Bar — The tamping bar shall conform to 6.1(a) of IS 10086 : 1982*.'

(*Page 7*) — Insert the following foot-note at the bottom:

'*Specification for moulds for use in tests of cement and concrete.'

(*Pages 15 and 16, clause 7.4.1*) — Substitute the following for the existing clause:

'7.4.1 Beam Moulds — The beam moulds shall conform to IS 10086 : 1982*.'

In assembling the mould for use, the joints between the sections of the mould shall be thinly coated with mould oil and a similar coating of mould oil shall be applied between the contact surfaces of the bottom of the mould and the base plate in order to ensure that no water escapes during the filling. The interior faces of the assembled mould shall be thinly coated with mould oil to prevent adhesion of the concrete.'

(*Page 15*) — Insert the following foot-note at the bottom:

'*Specification for moulds for use in tests of cement and concrete.'

(*Page 16, clause 7.4.2*) — Substitute the following for the existing clause:

'7.4.2 Tamping Bar — The tamping bar shall conform to 6.1(b) of IS 10086 : 1982*.'