

TECHNICAL DATA SHEET


2C plastic repair set REPLAST® ME 38 pieces

Art. no. 5964 089 301

P. Qty.: 1

For repairing plastic parts, including all required accessory products in a practical system case

Suitable for all plastics except PE (polyethylene), PP (polypropylene) and PTFE (polytetrafluoroethylene)



ORSY



Application area

For easy repair and connection of plastic parts such as spoilers, radiator grilles, trim clips, brackets on headlights, aprons, bumpers, wheel arches etc. Suitable for use in the food industry (NSF P1)

Processing information			
	Replast 25 sec.	Replast 90 sec.	Replast 210 sec.
Processing time	25 sec.*	90 sec.*	3.5 min.*
Can be sanded at 23 °C after	6 minutes	12 minutes	30 minutes
*at 23 °C/50 % RH			

Base material	Pre-treatment	Adhesion
SMC, BMC, RTM, wood, HPL, PUR-RIM	Sand	Excellent adhesion
CFRP (carbon fibre reinforced plastic)	Sand	Excellent adhesion
Coated, alloyed metal	In the case of bare metal, the metal should be protected against corrosion	Excellent adhesion
PP-EPDM/ABS	See separate instructions	Good (no structural bonding)

Application information

The substrate must be capable of bearing loads and must be clean, dry and free from grease and rust. Old adhesive residues must also be removed. To do so, clean the surface with the plastic cleaner and apply the primer. The flash-off time must be observed. Discard some adhesive before screwing on the mixer nozzle. The first 2 cm of adhesive from the mixer nozzle should also not be used. When applying the adhesive, the mixer should remain in the adhesive to prevent bubbles forming. Observe the processing instructions. The processing temperature must be between +15°C and +25°C.

Proof of performance

Certified in accordance with NSF P1 and EMICODE EC1+

TECHNICAL DATA SHEET



Notice

Not suitable for PE (polyethylene), PP (polypropylene) or PTFE (polytetrafluoroethylene). There may be adhesion problems in individual cases due to the coatings and release agents used in some cases in the plastic production process. Check material compatibility on a non-visible area if necessary. Please refer to the relevant product data sheets for information on properties and processing instructions for the individual products.

The usage instructions are recommendations based on the tests we have conducted and are based on our experience; carry out your own tests before each application. We do not assume any liability for a specific application result due to the large number of applications and storage and processing conditions. Insofar as our free customer service provides technical information or acts as an advisory service, no responsibility is assumed by this service except where the advice or information given falls within the scope of our specified, contractually agreed service or the advisor was acting deliberately. We guarantee consistent quality of our products. We reserve the right to make technical changes and further develop products.