

TECHNICAL DATA SHEET

Bond and Seal Power structural adhesive

Art. no. 0893 235 1

P. Qty.: 1 / 12

Heavy-duty, elasticated hybrid structural adhesive

Excellent adhesion to almost all surfaces such as aluminium (including anodised), steel, stainless steel, zinc-plated steel, sheet steel (including phosphated, chromated and zinc-plated), painted surfaces, copper, brass, zinc, ABS, GFRP, hard PVC, dense foams, PMMA, polyamide, polycarbonate, polystyrene (not foam), wood, HPL, cork, concrete, aerated concrete, gypsum, gypsum plasterboard, cement fibreboards, artificial stone, brick, enamel, glass, porcelain, ceramic, tiles.

Not suitable for PE, PP, PTFE, silicone, rubber, expandable polystyrene, mirrors, marble, bituminous substrates and softened plastics.





Contents	300 ml
Container	Cartridge
Chemical basis	Hybrid polymer
Colour	White
Max. skin-formation time	40 min
Min./max. skin-formation time	30-40 min
Smell/fragrance	Characteristic
Full curing speed/conditions	3 mm/d/23 °C and 50% relative humidity, moisture curing
Min./max. processing temperature	5 to 40 °C
Min./max. temperature resistance	-40 to +90 °C
Max. short-term temperature resistance	150 °C
Short term temperature resistance max./conditions	150 °C/after 16 hours
Min. tensile strength	3 N/mm ²
Min. combined tension and shear resistance	2 N/mm ²
Max. change in volume	2 %
Max. volume change/conditions	2 %/in accordance with DIN 52451
Short-term resistance against	Mineral oils, Fuels, Animal fat, Animal oils, Vegetable fat, Vegetable oils
Shelf life from production/conditions	12 Month/at max. 25 °C

TECHNICAL DATA SHEET

Silicone-free	Yes
Solvent-free	Yes
PVC-free	Yes
VOC-free	Yes
Isocyanate-free	Yes
Ultraviolet resistance	Yes
Sustainability	Pollutants/Emissions

**HYBRID
PU & SMP**



Application area

For dynamically loaded structural bonded connections and seam and joint sealing in bodywork, vehicle and caravan construction, railway carriage and container construction, metal and equipment construction, air-conditioning and ventilation duct construction, in the food industry, and much more.

TECHNICAL DATA SHEET

Bond + Seal products		B+S 0890 100 1 - 6 0890 100 111 - 3 0890 100 181 - 3 0890 100 11 + 13	B+S Power 0893 235 1 0893 235 2 0893 235 3	B+S Fast 0890 100 710 0890 100 720 0890 100 730	B+S Combi 0893 236 110 0893 236 120 0893 236 130
Metal	Aluminium	√ 1	√ 4	√ 1	√ 1
	Lead	x	x	x	x
	Stainless steel	√ 1	√ 4	√ 1	√ 1
	Copper	√ 1	√ 1	√ 1	√ 1
	Brass	√ 1	√ 1	√ 1	√ 1
	Steel/iron	√ 1	√ 4	√ 1	√ 1
	Zinc	√ 1	√ 4	√ 1	√ 1
Plastics	ABS	√ 2	√ 2	√ 2	x
	GFRP	√ 2	√ 2	√ 2	√
	Rubber/neoprene	x	x	x	√
	Dense foams	√ 2	√ 2	√ 2	√
	PE	x	x	x	x
	PMMA	√ 5	√ 5	√ 5	-
	Polyamide	√ 5	√ 5	√ 5	√
	Polycarbonate = PC	√ 5	√ 5	√ 5	-
	Polystyrene (not foam!)	√ 2	√ 2	√ 2	-
	PP	-	-	-	-
	PTFE	-	-	-	-
	Polyurethane = PU	√ 2	√ 2	√ 2	√
	Hard PVC	√ 2	√ 4	√ 2	√
	Silicone	-	-	-	-
	Expandable polystyrene	-	-	-	-

Surface must be pre-treated, please refer to the technical data sheets in accordance with the application.

1. Prime with primer for metal 0890 100 61
2. Prime with primer for p/w/s 0890 100 62
3. Pre-treat with deep-penetrating primer 0890 545 10
4. Pre-treat with activating cleaner 0890 100 60
5. Varioprimer safe + easy, 0890 024 021/0890 024 101

TECHNICAL DATA SHEET

Bond + Seal products		B+S 0890 100 1 - 6 0890 100 111 - 3 0890 100 181 - 3 0890 100 11 + 13	B+S Power 0893 235 1 0893 235 2 0893 235 3	B+S Fast 0890 100 710 0890 100 720 0890 100 730	B+S Combi 0893 236 110 0893 236 120 0893 236 130
Painted surfaces	2-component paints, stove enamels, cathodic dip coating, painted panels	√ 4	√ 4	√ 4	√ 4
Wood and engineered woods	Wood (including MDF, chipboard)	√ 2	√ 2	√ 2	√ 2
	Laminated panels (Resopal, Ultrapas)	√ 4	√ 4	√ 4	
	HPL	√ 4	√ 4	√ 4	√ 4
	Decorative panels	√	√	√	√
	Cork	√ 2	√ 2	√ 2	√
Stone and construction materials	Concrete	√ 2	√ 2	√ 2	√ 2
	Bituminous substrates	-	-	-	-
	Aerated concrete, gypsum, gypsum plasterboard	√ 3	√ 3	√ 3	√ 3
	Artificial stone (Corian, Varicor)	√ 2	√ 2	√ 2	√
	Delicate natural stone (e.g. marble)	-	-	-	-
	Natural stone, brick	√ 2	√ 2	√ 2	√ 2
	Cement fibreboards	√ 3	√ 3	√ 3	√
Others	Enamel	√ 5	√ 4	√ 5	√ 4
	Glass	√ 5	√ 4	√ 5	√ 4
	Fibreglass	-	-	-	-
	Mirrors	-	-	-	-
	Porcelain, ceramic, tiles	√ 5	√ 4	√ 5	√ 5
	Paper	√	√	√	√
	Cardboard	√	√	√	√
	Fabric	-	-	-	-
	Leather	-	-	-	-

Surface must be pre-treated, please refer to the technical data sheets in accordance with the application.

1. Prime with primer for metal 0890 100 61
2. Prime with primer for p/w/s 0890 100 62
3. Pre-treat with deep-penetrating primer 0890 545 10
4. Pre-treat with activating cleaner 0890 100 60
5. Varioprimer safe + easy, 0890 024 021/0890 024 101

TECHNICAL DATA SHEET

Optimierungstabelle		
Oberfläche/Material	Optimierungsschritte *	Hinweise
Aluminium eloxiert	1. HaftClean 2. HaftPlus Metall	-
Aluminium (AlMg3, AlMgSi1)		-
Buntmetalle (Messing, Kupfer, Bronze, etc.)	1. Grundreinigung mit IPA-Reiniger oder Klebstoffentferner	Die Verwendung von HaftPlus Metall ist zwingend erforderlich!
Edelstahl (rostfrei)	2. Mit Schleifvlies „very fine“ leicht anschleifen	-
Stahl (St 37, etc.)	3. Nachreinigung mit IPA-Reiniger	Bei korrosionsgefährdeten Bauteilen: 2K-PU- oder Epoxi-Korrosionsschutz erforderlich!
Stahl verzinkt (feuer- oder galvanisch verzinkt)	4. HaftClean	-
Zink	5. HaftPlus Metall oder Varioprimer safe + easy	-
Pulverbeschichtungen (PES, EP/PES)	HaftClean	Bei Anwendungen mit hohen Kräften oder feuchter Umgebung werden Vorversuche empfohlen.
2K-Decklacke, wasser- oder lösungsmittelbasierend (PUR, Acryl)	1. Grundreinigung mit IPA-Reiniger oder Klebstoffentferner 2. Varioprimer safe + easy	Aufgrund der Vielzahl an Lacken sind diese Angaben nur Anhaltspunkte, ggf. Vorversuche durchführen.
2K-Grundierungen, wasser- oder lösungsmittelbasierend (PUR, Acryl, Epoxidharz)	1. Grundreinigung mit IPA-Reiniger oder Klebstoffentferner 2. Varioprimer safe + easy	-
Kathodische Tauchlackierung (E-Coating)	HaftClean	-
Coil-Coat-Beschichtung	HaftClean	-
ABS	1. Grundreinigung mit IPA-Reiniger oder Klebstoffentferner 2. Mit Schleifvlies „very fine“ leicht anschleifen 3. Nachreinigung mit IPA-Reiniger 4. HaftPlus K/H/S	Bei gering belasteten Teilen kann das Anschleifen entfallen.
GFK (ungesättigte Polyester), Faserseite, Gelcoat-Seite oder SMC	1. Grundreinigung mit IPA-Reiniger oder Klebstoffentferner 2. Mit Schleifvlies „very fine“ oder Körnung 60-80 anschleifen und absaugen. 3. Nachreinigung mit IPA-Reiniger 4. HaftClean 5. HaftPlus K/H/S	Haftfläche muss vor UV-Strahlung geschützt sein (lichtundurchlässige Abdeckung).
Hart-PVC	1. HaftClean 2. HaftPlus K/H/S	-
PMMA/PC (ohne kratzfeste Beschichtung)	1. Grundreinigung mit IPA-Reiniger oder Klebstoffentferner	Haftfläche muss vor UV-Strahlung geschützt sein (lichtundurchlässige Abdeckung).
Polyamid	2. Varioprimer safe + easy	-
Holz, Sperrholz, MDF, Holzprodukte und Kork	1. Entstauben 2. HaftPlus K/H/S	-
HPL Schichtstoffplatten (Resopal, Ultrapas)	HaftClean	-
Glas	1. Grundreinigung mit IPA-Reiniger oder Klebstoffentferner 2. Varioprimer safe + easy	Haftfläche muss vor UV-Strahlung geschützt sein (lichtundurchlässige Abdeckung).
Emaile, Porzellan, Keramik, Fliesen	1. HaftClean oder IPA-Reiniger 2. Varioprimer safe + easy	-
Beton, mineralische Mörtel, Putze und Zementfaserplatten	1. Entstauben 2. Tiefgrund	-
* Entsprechende Reihenfolge der einzelnen Schritte einhalten		

TECHNICAL DATA SHEET

Kunststein (Corian, Varicor)	1. HaftClean 2. HaftPlus K/H/S	-
* Entsprechende Reihenfolge der einzelnen Schritte einhalten		

Application information

The substrates must be clean, dry and free from grease. The optimum temperature for the substance and material is between 15 °C and 25 °C.

Depending on the material and specification in the optimisation table, pre-treat with activating cleaner (art. no. 0890 100 60) or IPA cleaner (art. no. 0893 223 500, 0893 223 505), as well as primer for metal (art. no. 0890 100 61), primer for plastic/wood/stone (art. no. 0890 100 62), adhesive remover (art. no. 0890 100 63), deep-penetrating primer (art. no. 0890 545 10) or Varioprimer safe + easy (art. no. 0890 024 021/0890 024 101).

For more information on preparing material surfaces, refer to the optimisation table below. Carry out preliminary tests where necessary!

Cut the nozzle tip to create the required bead geometry. The adhesive must be applied using a manual, cordless or piston-rod-style compressed-air gun to ensure a reliable finish. We recommend a minimum adhesive layer thickness of 3 mm to harness the benefits of thick-coat bonding. Once opened, ensure that all containers are used up within a short period of time.

Non-cured material can be removed using adhesive remover (art. no. 0890 100 63).

Once cured, the material can be mechanically machined and painted over with activating cleaner after activation.

Proof of performance

NSF (P1) registered (no. 136996)

International approval for use in areas where food is processed or stored.



Notice

- In the case of B+S Power, an additional layer can be added within the skin formation time. Due to the multitude of different paints and coatings, preliminary tests must be performed to check compatibility. Two-component epoxy paints are compatible. Do not allow this product to come into contact with alkyd resin paint systems.
- Since the elasticity of the paint is lower than that of the adhesive/sealant, cracks may form in the paint around the joint.

The usage instructions are recommendations based on the tests we have conducted and on our experience; carry out your own tests before each application. Due to the large number of applications and storage and usage conditions, we do not assume any liability for a specific application result. Insofar as our free customer service provides technical information or acts as an advisory service, no responsibility is assumed by this service except where the advice or information given falls within the scope of our specified, contractually agreed service or the advisor was acting deliberately. We ensure the consistent quality of our products. We reserve the right to make technical changes and further develop products.