

# TECHNICAL DATA SHEET

## Hot melt adhesive 102

**Art. no. 0890 100 057**

P. Qty.: 1

**High-strength hot melt adhesive for effective dent removal on different materials and surfaces.**

|                                  |                                       |
|----------------------------------|---------------------------------------|
| Chemical basis                   | Compound of polymer and natural resin |
| Weight of content                | 500 g                                 |
| Colour                           | Yellow                                |
| Length                           | 200 mm                                |
| Diameter                         | 11.5 mm                               |
| Density/conditions               | 0.93 g/cm <sup>3</sup> /at 20 °C      |
| Viscosity                        | 3.24 Pas                              |
| Softening point                  | 91 °C                                 |
| Min./max. open time              | 15-40 s                               |
| Min./max. processing temperature | 180 to 220 °C                         |
| Shelf life from production       | 24 Month                              |
| Silicone-free                    | Yes                                   |
| Solvent-free                     | Yes                                   |
| Number of pieces                 | 25 PCS                                |



## Application area

High-strength hot melt adhesive that is ideal for the automotive industry for effective dent removal on different materials and surfaces by affixing pulling tabs.

## Proof of Performance



# TECHNICAL DATA SHEET

## Notice

Heat occurring during storage (e.g. due to solar radiation) must be avoided due to the changes to the outer shape of the hot melt adhesive this can cause.

The usage instructions are recommendations based on the tests we have conducted and on our experience; carry out your own tests before each application. Due to the large number of applications and storage and processing conditions, we do not assume any liability for a specific application result. Insofar as our free customer service provides technical information or acts as an advisory service, no responsibility is assumed by this service except where the advice or information given falls within the scope of our specified, contractually agreed service or the advisor was acting with deliberate intent. We guarantee the consistent quality of our products. We reserve the right to make technical changes and further develop products. Please observe the technical data sheet!