

TECHNICAL DATA SHEET

Superglue Klebfix

Art. no. 0893 090 0

P. Qty.: 1 / 25

For bonding metal, plastic and rubber parts with and to each other in a matter of seconds

Metal, plastic, rubber, all common types of elastomer (solid or foam rubber), in particular for SBR, EPDM, GFRP, EPDM, polycarbonate etc. as well as cork, artificial and natural stones, enamels, glass, mirror, porcelain and ceramic.



Chemical basis	Cyanoacrylate acidic ester
Colour	Transparent
Density	1.06 g/cm ³
Min./max. viscosity	70-120 mPas
Min. combined tension and shear resistance	15 N/mm ²
Stretch capacity	2 %
Max. gluing gap size	0.1 mm
Min./max. temperature resistance	-30 to +80 °C
Min./max. temperature conditions	-30 to 80 °C
Min./max. processing temperature	5 to 35 °C
Silicone-free	Yes
Solvent-free	Yes
Shelf life from production/conditions	15 Month/at room temperature
Contents	4.7 ml
Weight of content	5 g

Application area

Superglue for bonding metal, plastic and rubber parts with and to each other.

TECHNICAL DATA SHEET

		Klebfix	Klebfix Plasto	Klebfix Flex	Klebfix 4-in-1	Klebfix 4-in-1 Brush application	Klebfix GEL	Klebfix 2C
		089309 0893090 08930900 0893090030	0893091	0893092	0893423	0893094	0893403 08934031	0893093090
Metal	Aluminium	●2	-	●2	●2	●2	●2	●
	Lead	-	-	●	●	●	●	-
	Stainless steel	-	-	●	●	●	●	●
	Copper	●	-	●	●	-	-	●
	Brass	-	-	●	●	-	-	●
	Steel/iron	●	-	●	●	●	-	●
	Zinc	-	-	●	●	●	●	●
Plastics	ABS	-	●	-	●	●	●	●
	GRP	●	●1	-	-	●	●	●
	EPDM	●	-	●	-	-	●	-
	Rubber	●	-	●	●	●	●	●
	Dense foams	-	●1	●1	-	●1	●1	●
	Neoprene	-	-	●	-	-	-	●
	PE	-	●1	-	●1	●1	●1	●1
	PMMA	-	●	●	●	●	1	●
	Polyamide	-	-	-	-	-	-	●
	Polycarbonate = PC	●	-	●	●	●	●	●
	Expandable polystyrene	-	●1	●1	●	●	●	●
	PP	-	●1	-	-	-	●	●1
	PTFE	-	●1	-	-	-	-	-
	PU	-	●	-	-	-	-	●
	PVC	-	●	●	●	●	●	●
	Silicone	-	-	●1	-	-	-	-
	Polystyrene	-	●1	●1	-	-	-	●
Painted surfaces	Painted surfaces	-	-	-	-	●	●	●
Wood and engineered wood	Wood (MDF, chipboard)	-	-	-	●	●	-	●
	Laminated panels (Resopal, Ultrapas)	-	-	●	●	●	●	●
	Decorative panels	-	-	-	-	-	-	●
	Cork	●	●	●	●	●	●	-
1. With primer 0893 091 5 2. With activator 0893 301 20								

TECHNICAL DATA SHEET

		Klebfix	Klebfix Plasto	Klebfix Flex	Klebfix 4-in-1	Klebfix 4-in-1 Brush application	Klebfix GEL	Klebfix 2C
		089309 0893090 08930900 0893090030	0893091	0893092	0893423	0893094	0893403 08934031	0893093090
Stone and construction materials	Concrete	-	-	-	●	●	●	-
	Bituminous substrates	-	-	-	●	-	-	-
	Aerated concrete, gypsum, gypsum plaster-board	-	-	-	●	●	●	-
	Artificial stone (Corian, Varicor)	●	-	●	-	-	-	●
	HPL	-	-	●	●	●	●	-
	Natural stone (marble, granite)	● 1	-	●	-	-	●	●
	Stone	-	-	-	-	-	●	-
	Cement fibre-boards	-	-	-	●	●	●	-
Others	Enamel	● 1	-	●	-	-	-	-
	Glass	●	-	●	●	●	●	●
	Fibreglass	-	-	-	●	●	-	●
	Mirror	● 1	-	●	-	●	●	-
	Porcelain, ceramic, tiles	●	-	●	●	●	●	●
	Paper	-	-	●	●	●	●	●
	Cardboard	-	-	●	●	●	●	●
	Mesh	-	-	-	●	●	-	●
	Leather	-	-	-	●	●	-	-
1. With primer 0893 091 5 2. With activator 0893 301 20								

Tensile and lap-shear strength in accordance with DIN EN 1465		
Material		Typical tensile shear strength values (N/mm ²)
Steel	60-90 seconds	> 22
Aluminium	60-90 seconds	>
PA	20-30 seconds	8-12
PVC	20-30 seconds	10-20*
Polycarbonate	10-15 seconds	10-20*
POM	30-40 seconds	-
EPDM	5-9 seconds	> 10*
Neoprene	3-5 seconds	> 10*
* Material breakage		

TECHNICAL DATA SHEET

Handfestigkeit nach	089309 + 0893090	08930900
Aluminium/Aluminium	≥ 60 Sekunden	40 - 90 Sekunden
SBR/SBR	≥ 5 Sekunden	3 - 10 Sekunden
Polycarbonat/Polycarbonat	≥ 10 Sekunden	8 - 20 Sekunden
EPDM/EPDM	≥ 7 Sekunden	≤ 25 Sekunden
Aushärtegeschwindigkeit wird durch Verwendung des Aktivators beschleunigt		

Application information

The parts to be adhered must be clean, free from grease and dry.

Apply a thin, even layer of adhesive to just one of the surfaces to be adhered. Apply sufficient pressure to make the connection immediately, in order to ensure complete contact.

Use the activator (item no.: 0893 301 20) to speed up the reaction of Würth cyanoacrylate adhesives. This can usually be used on all kinds of substrates, but please test it beforehand on a concealed section for compatibility.

Proof of performance

NSF registered, class P1, reg. no. 151993

NSF-tested in accordance with NSF/ANSI 61 for use in service water and drinking water



Notice

- It is advisable to wear safety gloves and safety goggles.
- If surfaces are too dry or acidic, this will delay or prevent hardening, while higher levels of moisture and alkaline surfaces will have an accelerating effect.
- Due to the vapour pressure of the liquid adhesive, slow curing excess product around the adhesive area may result in a white deposit (blooming effect). These are adhesive vapours that are hardening. These can be removed with e.g. isopropanol or acetone. However, it is important to note that the surfaces of the parts to be cleaned are also resistant to these solvents. Blooming can be prevented/reduced by using the adhesive economically and ensuring sufficient air humidity and ventilation in the work area.

TECHNICAL DATA SHEET



Material breakage



Material breakage

The usage instructions are recommendations based on the tests we have conducted and on our experience; carry out your own tests before each application. Due to the large number of applications and storage and processing conditions, we do not assume any liability for a specific application result. Insofar as our free customer service provides technical information or acts as an advisory service, no responsibility is assumed by this service except where the advice or information given falls within the scope of our specified, contractually agreed service or the advisor was acting deliberately. We guarantee the consistent quality of our products. We reserve the right to make technical changes and further develop products. Please observe the technical data sheet!