

Machine learning based prediction of magnetic properties for half-Heusler compounds using atomic information

Pramosh Shrestha

September 7, 2021

Abstract

In this paper, we aim to demonstrate high reliability of machine learning model for the sought after parameters. By the end of this paper, we achieved our aim by deploying the atomic information of constituent elements like atomic radii and atomic mass to predict magnetic moment and elasticity. It is easily assumed the ML model trained on the half-Heusler compounds can easily incorporate the full-Heusler compounds. With that in mind the study is carried out on the half-Heusler compounds. Amongst the two employed ML model, the GBT reported co-efficient of determination to be as high as 0.97. The next model, artificial neural network, was close but stuck around 0.95. Our results may serve as a motivation to harness the robust ML models into calculation of desired parameters. Which may lead to a lowcost and short time development of new functional devices and materials.

1 Introduction

A general understanding of how microscopic structures and characteristics gives forth the material properties, which are necessary prerequisite for designing next iteration of desired materials. Due to the myriad of applicability the Heusler alloys receive tremendous experimental and theoretical interest. We are particularly interested in its use for spintronics and as a material. For the same, the calculation of total molecular magnetic moment and elasticity of the compound are the crucial physical parameters. By and large for this effort, the typical, computational simulations like DFT and molecular dynamics are vital tools. So far the Heusler compounds are treated in the equal footing [14,21]. However, in recent times the emerging Machine Learning techniques have grabbed the attention for such objectives. Sprung from the domain of statistics, the ML techniques have seeped into multiple disciplines including the material science. The cubic X_2YZ half-Heusler compounds are candidate for spintronics technology [5,6,8,15,26]. Interestingly, they possess high spin polarisation. The net electron spin magnetic moment in the molecule is an instrumental parameter for spintronics. We are inquisitive to see how well will a ML model closes down to the values calculated from DFT. Especially, after several reports of successful implementation of ML models to improve the thermal properties of materials [17,19,20,23,24].

The magnetism in a material originates from electron spin and the electron exchange interactions [4,7,22]. Indeed due to the double exchange, the compound Cu_2MnAl becomes ferromagnetic, although non of its constituent elements is ferromagnetic by itself [12]. The presence of two different magnetic sublattices in the crystal structure, the XYZ Heusler compounds displays multiple magnetic phenomena, and in fact, today ferromagnetism, ferrimagnetism, and half-metallic ferromagnetism are well studied. Similarly, the half-Heusler, materials exhibit one magnetic sublattice since only the atoms on the octahedral sites can carry a magnetic moment [11]. Understanding of these electronic properties have led to great breakthroughs.

Another important probe in new material designs and improvements is Elastic modulus. Several physical properties, such as hardness and melting point, are related to the elastic constants [9,10]. For the Heusler compounds, elasticity has been studied to determine its stability [25]. In this study, it will be the next parameter to predict via ML model.

As of today, Machine Learning algorithms like Decision trees and Deep neural networks has been applied to classify the Topological insulators [1,3] and topological phases [16]. Moreover, the high accuracy in lattice parameters prediction are demonstrated in multiple studies [2,13,27]. Machine learning techniques may soon be poised to compete, or at least corroborate, the results from traditional Computational frameworks. After all, it's robust and requires few and simple training features like atomic configurations and molecular parameters to churn out desired parameters. Incidentally, It's not the everyday choice. However, without any hassle the input features for any ML model can be easily be engineered for better output. In this paper, we tried to achieve similar feat on Machine learning based studies of materials. Traditionally, these calculations are performed via costly DFT. The necessary training data is obtained from the Python library Pymatgen [18].

References

- [1] N. Andrejevic, J. Andrejevic, C. H. Rycroft, and M. Li. Machine learning spectral indicators of topology. *arXiv preprint arXiv:2003.00994*, 2020.
- [2] L. Chonghe, T. Yihao, Z. Yingzhi, W. Chunmei, and W. Ping. Prediction of lattice constant in perovskites of gdfeo3 structure. *Journal of Physics and Chemistry of Solids*, 64(11):2147–2156, 2003.
- [3] N. Claussen, B. A. Bernevig, and N. Regnault. Detection of topological materials with machine learning. *Physical Review B*, 101(24):245117, 2020.
- [4] E. D. Commins. Electron spin and its history. *Annual Review of Nuclear and Particle Science*, 62:133–157, 2012.
- [5] R. De Groot, F. Mueller, P. Van Engen, and K. Buschow. New class of materials: half-metallic ferromagnets. *Physical Review Letters*, 50(25):2024, 1983.
- [6] A. Dehghan and S. Davatolhagh. d0-d half-heusler alloys: A potential class of advanced spintronic materials. *Journal of Alloys and Compounds*, 772:132–139, 2019.
- [7] T. Dietl. Exchange interactions: Super-exchange, double exchange, rkky; magnetic orders. *Annals of the West University of Timisoara. Physics Series*, 53:24, 2009.
- [8] L. Feng, E. Liu, W. Zhang, W. Wang, and G. Wu. First-principles investigation of half-metallic ferromagnetism of half-heusler compounds xyz. *Journal of magnetism and magnetic materials*, 351:92–97, 2014.
- [9] M. Fine, L. Brown, and H. Marcus. Elastic constants versus melting temperature in metals. *Scripta metallurgica*, 18(9):951–956, 1984.
- [10] J. J. Gilman. *Chemistry and physics of mechanical hardness*, volume 5. John Wiley & Sons, 2009.
- [11] T. Graf, J. Winterlik, L. MÜchler, G. H. Fecher, C. Felser, and S. S. Parkin. Magnetic heusler compounds. In *Handbook of magnetic materials*, volume 21, pages 1–75. Elsevier, 2013.
- [12] F. Heusler, W. Starck, and E. Haupt. Magnetisch-chemische studien. *Verh. Dtsch. Phys. Ges*, 5:219–232, 1903.
- [13] L. Jiang, J. Guo, H. Liu, M. Zhu, X. Zhou, P. Wu, and C. Li. Prediction of lattice constant in cubic perovskites. *Journal of Physics and Chemistry of Solids*, 67(7):1531–1536, 2006.
- [14] S. A. Khandy and D. C. Gupta. Dft investigations on mechanical stability, electronic structure and magnetism in co2taz (z= al, ga, in) heusler alloys. *Semiconductor Science and Technology*, 32(12):125019, 2017.
- [15] J. Ma, V. I. Hegde, K. Munira, Y. Xie, S. Keshavarz, D. T. Mildebrath, C. Wolverton, A. W. Ghosh, and W. Butler. Computational investigation of half-heusler compounds for spintronics applications. *Physical Review B*, 95(2):024411, 2017.
- [16] Y. Ming, C.-T. Lin, S. D. Bartlett, and W.-W. Zhang. Quantum topology identification with deep neural networks and quantum walks. *npj Computational Materials*, 5(1):1–7, 2019.
- [17] H. Miyazaki, T. Tamura, M. Mikami, K. Watanabe, N. Ide, O. M. Ozkendir, and Y. Nishino. Machine learning based prediction of lattice thermal conductivity for half-heusler compounds using atomic information. *Scientific reports*, 11(1):1–8, 2021.
- [18] S. P. Ong, W. D. Richards, A. Jain, G. Hautier, M. Kocher, S. Cholia, D. Gunter, V. L. Chevrier, K. A. Persson, and G. Ceder. Python materials genomics (pymatgen): A robust, open-source python library for materials analysis. *Computational Materials Science*, 68:314–319, 2013.
- [19] Y. Ouyang, C. Yu, G. Yan, and J. Chen. Machine learning approach for the prediction and optimization of thermal transport properties. *Frontiers of Physics*, 16(4):1–16, 2021.
- [20] Y. Ouyang, Z. Zhang, C. Yu, J. He, G. Yan, and J. Chen. Accuracy of machine learning potential for predictions of multiple-target physical properties. *Chinese Physics Letters*, 37(12):126301, 2020.
- [21] V. Srivastava, N. Kaur, R. Khenata, and S. A. Dar. Investigation of the electronic, magnetic, elastic, thermodynamic and thermoelectric properties of mn2cocr heusler compound: A dft-based simulation. *Journal of Magnetism and Magnetic Materials*, 513:167107, 2020.

- [22] G. E. Uhlenbeck and S. Goudsmit. Spinning electrons and the structure of spectra. *Nature*, 117(2938):264–265, 1926.
- [23] X. Wan, W. Feng, Y. Wang, H. Wang, X. Zhang, C. Deng, and N. Yang. Materials discovery and properties prediction in thermal transport via materials informatics: a mini review. *Nano letters*, 19(6):3387–3395, 2019.
- [24] Y. Wang, A. Kandeal, A. Swidan, S. W. Sharshir, G. B. Abdelaziz, M. Halim, A. Kabeel, and N. Yang. Prediction of tubular solar still performance by machine learning integrated with bayesian optimization algorithm. *Applied Thermal Engineering*, 184:116233, 2021.
- [25] S.-C. Wu, S. S. Naghavi, G. H. Fecher, and C. Felser. A critical study of the elastic properties and stability of heusler compounds: phase change and tetragonal $x_{-2}yz$ compounds. *arXiv preprint arXiv:1704.01741*, 2017.
- [26] R. Zhang, L. Damewood, Y. Zeng, H. Xing, C. Fong, L. Yang, R. Peng, and C. Felser. Two prospective li-based half-heusler alloys for spintronic applications based on structural stability and spin–orbit effect. *Journal of Applied Physics*, 122(1):013901, 2017.
- [27] Y. Zhang and X. Xu. Machine learning modeling of lattice constants for half-heusler alloys. *AIP Advances*, 10(4):045121, 2020.