

YOU WILL STICK NO BILLS
பெட்டியை அட்டிமாட்டீர்



கறையாக்க மனசுவராது





ABOUT US

We are a leading mining company in South India with over 50 years of dedicated experience in mining. Established in 1958, our company has been consistently ranked as one of the industry leaders. Our products are made from some of the richest limestone deposits in the country.



We manufacture a complete range of lime and limestone products to meet the needs of various industries across the sub-continent. Our products, which meet the highest standards of quality, have served some of the largest industries in the country. Our product portfolio includes high-quality minerals, slaked lime powder, wall putty and all-purpose fixer & sealer.

KRISHNA MINES SUPER WHITE SLAKED LIME POWDER

The outstanding quality of our products have turned Krishna Mines into a name that's synonymous with quality in the slaked lime powder industry.

With sophisticated manufacturing technologies, we have transformed naturally occurring deposits into supreme products. We maintain stringent quality parameters to guarantee that only the finest of raw materials are used in the making of our products. Our in-house labs conduct hourly quality tests on all batches to ensure highest quality standards in the industry.

Minimum whiteness & brightness: 80%

Minimum coverage factor: 100 - 120 Sq. Ft. per kilogram per coat



This product is from our "Super White" Range and is readily available all across Tamil Nadu. It can be used for both interiors and exteriors.

S.NO	TECHNICAL PARAMETERS	RESULTS
1	WHITENESS	Minimum 80%
2	BRIGHTNESS	Minimum 80%
3	BULK DENSITY (g/ml)	0.7 - 0.9
4	MIXING RATIO (Powder : Water)	1:1.5 By Weight
5	APPLICATION LIFE (At 30°C)	12 Hours
6	RECOAT TIME	Minimum 12 Hours
7	FULL CURE TIME	8 Hours
8	COVERAGE (Sq. Feet / Kg / Coat)	100-120 Sq.ft
9	SHELF LIFE (from the date of manufacturing)	6 Months

PREPARATION OF KRISHNA MINES SUPER WHITE SLAKED LIME POWDER

- Take required quantity of Krishna Mines Super White Slaked Lime powder in a pan. 150% water by volume is required to prepare lime milk of good consistency.
- For colour coating, add your favourite colour strainer in ratio of 5ml per 1Kg slaked lime powder.
- Add Fevicol (DDL) 25ml per 1Kg of slaked lime powder.
- Mix vigorously for 5-10 minutes to make a lump-free liquid.
- Ensure that the mixed quantity is used within 8 hours of preparation.
- Mixing can be done either manually or by using a suitable electric mixer.

APPLICATION OF KRISHNA MINES SUPER WHITE SLAKED LIME POWDER

- Ensure that the surface is totally clean.
- Ensure that the surface is made of cement material or is plastered.
- The surface should be moderately rough and in just-wet condition.
- First rub the wall and then cure with water. Apply 1st coat after 1 hour from mixing in 'bottom-to-top' movement.
- Apply 2nd coat after 12 hours from mixing in summers and after 24 hours in winters. Apply 2nd coat horizontally to even out application marks of the 1st coat, if any.