
Charpy Absorbed Energy vs. Temperature
Absorbed Energy (J)
100
75
50
25
0
approximate DBTT
(steel)
−50
0
50
100
Test Temperature (deg C)
AISI 1018 steel (BCC)
Aluminum alloy (FCC)