

Determination of the Molecular Weight of Conjugated Polymers with Diffusion-Ordered NMR Spectroscopy

Kaichen Gu, Jon Onorato, Steven Shuyong Xiao, Christine K. Luscombe, and Yueh-Lin Loo

[†]Department of Chemical and Biological Engineering, Princeton University, Princeton, New Jersey 08544, United States


[‡]Materials Science and Engineering Department, University of Washington, Seattle, Washington 98195-2120, United States

[§]1-Material Inc., 2290 Chemin St-François, Dorval, Quebec, H9P 1K2, Canada

^{||}Department of Chemistry, University of Washington, Seattle, Washington 98195-1700, United States

[⊥]Andlinger Center for Energy and the Environment, Princeton University, Princeton, New Jersey 08544, United States

ABSTRACT:



■ INTRODUCTION

The performance of electronic devices comprising conjugated polymers has improved steadily over the past two decades with polymer solar cells exhibiting record efficiencies over 10%, and polymer thin film transistors exhibiting mobilities well above $1 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$. Previous studies have demonstrated that the physical characteristics of conjugated polymers that serve as electrically active constituents, particularly their molecular weights (MWs) and molecular weight distributions (MWDs), play important roles in determining their optoelectronic properties.^{1–5} It is thus crucial to accurately and precisely determine the molecular weight and molecular weight distribution of conjugated polymers. Size exclusion chromatography (SEC) is commonly used to characterize polymer molecular weight and molecular weight distribution, yet it has many limitations. SEC is particularly ill-suited for characterizing conjugated polymers given their stiffer backbone and lower solubility because these polymers have a strong tendency to interact with and adsorb on the walls of SEC columns. These interactions alter the elution times of polymers in nontrivial ways, ultimately skewing the extracted molecular weight distribution. More problematically, conjugated polymers typically have optical band gaps in the range of 1.5–3 eV, so they tend to absorb light that is normally used for SEC detection.

Nuclear magnetic resonance (NMR) spectroscopy is a powerful tool for determining the structure, conformation, and dynamics of polymers. End-group analysis by NMR allows quantification of the number of repeating units, and can thus provide the absolute number-average MW (M_n) of low-MW polymers having chemical shifts that can be distinctly attributed to their backbone and end groups. Diffusion-ordered NMR spectroscopy (DOSY) can be used to characterize polymers whose MW falls between 10^2 and 10^6 g mol^{-1} . A 2D NMR technique, DOSY, introduces an additional frequency dimension that measures the translational diffusion coefficient (D) of polymers. The diffusion coefficient in turn provides a measure of the polymer hydrodynamic radius (R_H) through the Stokes–Einstein equation

$$D = \frac{kT}{6\pi\eta R_H} \quad (1)$$

where k is the Boltzmann constant, T is the absolute temperature, and η is the viscosity of the solvent. The diffusion coefficient can then be correlated with the molecular weight of the polymer (M) through

Received: December 5, 2017

Revised: January 11, 2018

Published: January 12, 2018

$$M = AD^{-\alpha} \quad (2)$$

where A and α are materials-relevant constants. For a polydisperse batch of polymer, the average diffusion coefficient is correlated with the weight-average molecular weight (M_w).

$$M_w = AD^{-d_f} \quad (3)$$

where d_f is the fractal dimension of the polymer chain in the solvent in which it is characterized.

DOSY has been employed to characterize the molecular weight for small molecules, polyoxometalates clusters, and commodity polymers and biopolymers. DOSY has also been used to study the formation of supramolecular graft copolymers containing conjugated poly(3-(2-ethylhexyl)-thiophene) blocks.

In this paper, we show that DOSY can be a viable and general method for characterizing the size and size distribution of conjugated polymers. DOSY is noninvasive and only requires minimal amounts of material (typically < 1 mg per sample). It correlates chemical identities with translational diffusion coefficients, making the technique well-suited for studying multicomponent systems or polymer samples having a distribution of molecular weights. Starting with four batches of tailor-made poly(3-hexylthiophene), or P3HT, whose MWD had previously been fully characterized by a combination of SEC and end-group analysis, we demonstrate DOSY as an approach to measure their diffusion coefficients in chloroform and extract their size distributions. Using the available SEC data, we further determined a correlation between the diffusion coefficients and the absolute molecular weights for several P3HT samples in chloroform. This correlation has allowed us to extend this approach for determining the P3HT-equivalent molecular weight of poly[4-(4,4-dihexadecyl-4H-cyclopenta[1,2-*b*:5,4-*b'*]dithiophen-2-yl)-*alt*-[1,2,5]thiadiazolo-[3,4-*c*]pyridine], or PCDTPT, a donor-acceptor polymer whose MW and MWD are otherwise challenging to determine given that its absorption coincides with the detection wavelengths normally used in SEC.

EXPERIMENTAL SECTION

Materials. PCDTPT was obtained from 1-Materials Inc. and fractionated into six batches as detailed in the Supporting Information. P3HT was synthesized per literature procedure, with minor modifications, as detailed in the Supporting Information. The four regioregular P3HT samples (P3HT_5, P3HT_10, P3HT_20, and P3HT_40) had been characterized by SEC and NMR end-group analysis separately, and their absolute molecular weights and dispersities are provided in the Supporting Information.

Optical Absorption Measurements. Absorption spectra were recorded using an Agilent Technologies Cary 5000 spectrophotometer. PCDTPT solutions in chloroform (ca. 0.01 mg mL⁻¹) were measured in quartz spectrophotometer cells having a 10 mm path length.

DOSY Experiments. Polymer samples were dissolved in CDCl₃ (ca. 0.5 mg mL⁻¹). DOSY experiments were performed at 25 °C on a Bruker AVANCE III with a probe of type PA BBO 500 S1 BBF-H-D-05. All experiments were run without spinning to minimize convection. The maximum gradient strength was 50 G cm⁻¹. The number of linear gradient steps was set to be 32. The standard Bruker pulse program, "ledbpgp2s", was used. The gradient recovery delay time was 0.5 ms and the eddy-current delay is 5 ms. For P3HT samples, diffusion times were between 50 and 70 ms and the gradient durations were between 2.0 and 2.6 ms. For PCDTPT samples, diffusion times were between 50 and 100 ms and the gradient durations were between 1.5 and 3.2 ms. The resulting NMR spectra

were processed by Mestrelab MNova, a DOSY maps were generated using MNova Bayesian transformation.

RESULTS AND DISCUSSION

To evaluate DOSY's capability for characterizing polymer size and size distribution, we started our experiments with polymer samples with well-defined MW and MWD. We used four batches of regioregular P3HT with distinct MWs (M_n of 5, 10, 20, and 40 kg mol⁻¹) and narrow MWD, hereafter referred to as P3HT_ X , where X represents the sample's M_n in kg mol⁻¹. In DOSY experiments, diffusion coefficients are measured through the attenuation of NMR signals under different pulsed field gradient strengths. Figure 1 shows an example of ¹H 1D




Figure 1. (a) Stacked 1D ¹H NMR spectra of P3HT_5 in CDCl₃ at concentrations ca. 0.5 mg mL⁻¹. The signal decays with increasing magnetic field gradient strength. (b) 2D DOSY map of the sample after Bayesian transformation. The map correlates the chemical identities of the different species with their translational diffusion coefficients.

NMR signal attenuation of P3HT_5 in CDCl₃ with increasing magnetic field gradient strength, g . We observe a chemical shift at 7.26 ppm, attributable to residual hydrogenated chloroform in the solution, and a shift at 1.56 ppm, attributable to traces of water. All other chemical shifts can be assigned to the protons of P3HT; a complete chemical shift assignment for P3HT is provided in the Supporting Information. As the gradient strength is increased from 1.0 to 47.5 G cm⁻¹ in 32 increments, the intensities associated with the chemical shifts of P3HT_5, chloroform, and water exponentially decay. This decay is related to the diffusion coefficient of the species and is described by:

$$I = I_0 \exp(-DZ) \quad (4)$$

Here, Z is a parameter that encodes the magnetic field gradient amplitude, g , the gyromagnetic ratio, γ , the duration of each pulse, δ , and the interval between pulses, Δ . We used the "ledbpgp2s" pulse sequence (longitudinal eddy-current delay sequence with bipolar gradient pulse pair with 2 oil gradients) in these experiments, in which Z is defined as

$$Z = \gamma^2 g^2 \delta^2 \left(\Delta - \frac{\delta}{3} - \frac{\tau}{2} \right) \quad (5)$$

This pulse sequence minimizes the effect of eddy current and doubles the effective gradient. We observed that the signal




Figure 2. (a) Stejskal–Tanner plot of intensity signal attenuation at $\delta = 0.91$ ppm of the four batches of P3HT in CDCl_3 . (b) Absolute weight-average molecular weight of P3HT as a function of diffusion coefficient. (c) Diffusion coefficient distributions obtained from DOSY analysis. (d) Absolute molecular weight distributions (solid lines) and calculated distributions from DOSY analysis (dotted lines) for the four batches of P3HT.

associated with chloroform protons decays faster than that associated with P3HT protons, consistent with the fact that chloroform is much smaller and thus has a larger diffusion coefficient compared to its polymer solute.

The stacked spectra were processed via Bayesian transformation to yield the 2D DOSY map that is shown in

b. The DOSY map shows three well-separated peaks along the diffusion dimension, corresponding to the presence of trace amounts of water, hydrogenated chloroform, and P3HT_5. In view of its ability to spectroscopically isolate distinct chemical species, DOSY is also referred to as “NMR chromatography”.

a shows the Stejskal–Tanner plot tracking the attenuation of intensity of the chemical shift at 0.91 ppm, attributable to the methylene protons at the end of the hexyl side chains of P3HT, for the four batches of P3HT in CDCl_3 . In all cases, the intensity decays exponentially with Z . Per the absolute value of the slope of each fit corresponds to the diffusion coefficient of the respective batch of P3HT. Increasing the polymer molecular weight from P3HT_5 to P3HT_40 leads to larger hydrodynamic radii; we should thus expect to measure progressively smaller diffusion coefficients per the Stokes–Einstein Equation. The extracted diffusion coefficients of the different batches of P3HT are tabulated in the Supporting Information.

The power-law relationship in correlates the weight-average molecular weight that is separately obtained through a combination of SEC and end-group analysis, with the diffusion coefficient that is obtained by DOSY. This equation can be linearized by taking the logarithms on both sides, yielding

$$\log(M_w) = -d_f \log(D) + \log(A) \quad (6)$$

The observation that $\log(M_w)$ varies linearly with $\log(D)$ for P3HT in chloroform, per , indicates that P3HT exhibits comparable hydrodynamic behavior over the experimentally accessed MW range. From the fit in b, we obtained a quantitative relationship of $\log(M_w) = -1.78 \log(D) - 6.29$, in which M_w and D adopt units of g mol^{-1} and $\text{cm}^2 \text{s}^{-1}$,

respectively. By assessing the maximum and minimum slopes to the fits of the data set, we obtain $d_f = 1.78 \pm 0.04$ and $\log(A) = -6.29 \pm 0.25$. This power-law relationship provides a calibration for future P3HT samples. Given samples with known D , we can predict their M_w , and vice versa. Importantly, this relationship also lends insight into the interactions between P3HT and chloroform. The prefactor indicates a fractal dimension of 1.78 for P3HT in chloroform. This observation suggests that chloroform is a moderately good solvent for P3HT. Were chloroform a theta-solvent in which P3HT adopts Gaussian-like conformation because polymer–polymer and polymer–solvent interactions are comparable, the fractal dimension would have been 2. Were chloroform a good solvent in which P3HT chains are fully solvated because polymer–solvent interactions are more favorable, the fractal dimension would have been 1.70.

We also investigated the diffusion coefficient distributions (DCDs) obtained from DOSY analysis, shown in c. The DCDs of P3HT_5, P3HT_10, P3HT_20, and P3HT_40 progressively shift toward smaller values. Using the M_w – D relationship above, we converted the DCDs to MWDs and compared these with the experimentally obtained absolute molecular weight distributions, shown in d. Here, the absolute MWDs were extracted from SEC measurements, with an overall M_n determined by NMR end-group analysis. Generally, we observe qualitative agreement between the MWDs extracted from DCDs and the experimentally obtained MWDs. Increasing the molecular weight of P3HT increases the hydrodynamic radius of P3HT, resulting in a decrease in the diffusion coefficient per the Stokes–Einstein Equation. We observe that the DCD-derived MWDs are generally narrower than those experimentally determined by SEC and NMR end-group analysis. This discrepancy likely results from the need to inverse Laplace transform frequency-domain data, a process that is mathematically ill-posed. Further exacerbating this discrepancy is the fact that we only have a limited number of data points for this DOSY transformation. Though microscopic

averaging effects in which solute molecules tend to diffuse at the same rate as its neighboring molecules due to intermolecular interactions could also play a role in peak narrowing, this effect is not significant at the low polymer concentrations used in our study.

The DCD of P3HT_20 shown in **c** has a shoulder to the left of the main peak. This shoulder is reminiscent of the bimodal feature in the MWD of P3HT_20 that is captured by SEC analysis, as shown in **d**. The DCD indicates the shoulder portion of P3HT has a larger diffusion coefficient compared to the minority population in P3HT_20. This observation correlates well with the SEC-obtained MWD that reveals the majority population of P3HT_20 to be higher in molecular weight. The main peak and shoulder, however, are closer to each other in the DCD-derived MWD compared to the experimentally obtained MWD. This observation is consistent with those made on polypropylene with bimodal MWDs. We attribute this difference to issues associated with inverse Laplace transformation, not different from the peak narrowing issues highlighted above.

π -Conjugation along the polymer backbone tends to promote chain rigidity. The DOSY-derived diffusion measurements allow us to quantify the extent of chain rigidity because R_H , related to the diffusion coefficient by the Stokes–Einstein equation, is a function of chain conformation as well as molecular weight. Assuming the wormlike chain (WLC) model, we estimated the persistence length (L_p) of P3HT from the dependence of its radius of gyration (R_g) on molecular weight per

$$\frac{R_g^2}{M} = \frac{L_p}{3m_L} - \frac{L_p^2}{M} + \frac{2L_p^3 m_L}{M^2} \left(1 - \frac{L_p m_L}{M} \left[1 - \exp\left(-\frac{M}{L_p m_L}\right) \right] \right) \quad (7)$$

where M is the molecular weight and m_L is the molecular weight per unit contour length of 0.39 nm. We first estimate the value of R_g from R_H by the Kirkwood–Riseman theory:

$$R_g = \frac{3}{2} R_H \quad (8)$$

This theoretical framework for calculating persistence length was originally developed for monodisperse systems. To account for the polydispersity in these P3HT samples, we used ensemble-average values to approximate the MWs in the model. We estimated the persistence length of P3HT to be 2.32 nm using M_w and 3.15 nm using M_n , in good agreement with experimental values obtained by light scattering (2.4 ± 0 nm) and neutron scattering (3.0 ± 0.1 nm), respectively. Regioregularity will necessarily affect chain conformation. In fact, the persistence length of regiorandom P3HT is estimated to only be approximately one-third that of its regioregular counterpart. Given its sensitivity to chain conformation, DOSY should be able to shed light on the impact regioregularity has on the hydrodynamic behavior of P3HT; this study is the subject of a future publication.

To assess the general applicability of DOSY for quantifying size and size distribution of conjugated polymers, we applied this analysis to PCDTPT, a low-band-gap donor–acceptor semiconducting polymer, whose chemical structure is shown in **a**. PCDTPT is a copolymer comprising cyclopenta[2,1-




Figure 3. (a) Chemical structure of PCDTPT used in this study. (b) Absorption spectra of the six batches of PCDTPT solutions (ca. 0.01 mg mL^{−1} in chloroform) at room temperature. (c) Maximum absorbance wavelength of the original sample (empty square) and the fractionated aliquots (solid circles) as a function of PCDTPT hydrodynamic radius.

b:3,4-*b'*)dithiophene (CDT) as its donor moiety and pyridal-[2,1,3]-thiadiazole (PT) as its acceptor moiety. Characterization of PCDTPT with SEC is challenging because PCDTPT strongly absorbs light at the incident wavelength of the laser used for detection.

We fractionated as-received PCDTPT based on solubility differences imparted by MW differences via Soxhlet extraction. To induce selective fractionation, we varied the solvent quality using binary solvent mixtures of chloroform and methanol. Chloroform is a good solvent, whereas methanol is an antisolvent for PCDTPT. Increasing chloroform content in these mixtures thus increases the solvent quality for PCDTPT and induces selective extraction of less soluble portions, i.e., the higher-MW component. Because methanol–chloroform mixtures form a positive azeotrope, the starting composition is not representative of the composition in the extracting reservoir. To quantify the composition in the extracting reservoir, we calculated the instantaneous vapor composition, or the instantaneous condensate composition, from methanol–chloroform vapor–liquid equilibrium. Then we performed numerical integrations based on the Rayleigh equation for single-stage batch distillation to estimate the average effective composition for each solvent mixture used in this study. The solvent mixtures used and estimation of the reservoir compositions are detailed in **Table S1** in the Supporting Information. We started with a solvent mixture with 80 vol % methanol and extracted the most soluble portions of PCDTPT, which presumably has the lowest MW in the batch. Using solvent mixtures with increasing chloroform content, we yielded six distinct batches of PCDTPT, which we refer to as PCDTPT_1 through PCDTPT_6 in the order of decreasing solubility, and presumably increasing molecular weight.

b shows the optical absorption spectra of all six batches of PCDTPT in chloroform at ca. 0.01 mg mL^{−1}. The absorption spectra of PCDTPT_1 through PCDTPT_6 show a progressive red shift; the wavelengths at maximum absorbance are quantified in **c** as a function of the hydrodynamic radius of the samples in chloroform, as quantified from the diffusion coefficients obtained from DOSY experiments. Plotting the absorbance wavelength as a function of the hydrodynamic radius reveals a monotonic relationship; this observation is expected since increasing the

polymer size increases its conjugation length, which in turn decreases its optical gap, resulting in a red shift in its absorption spectrum.

a shows the Stejskal–Tanner plot displaying the attenuation of the integrated intensity of the chemical shifts




Figure 4. (a) Stejskal–Tanner plot of intensity signal attenuation integrated over $\delta = 0.5$ – 1 ppm and (b) diffusion coefficient distributions obtained from DOSY analysis for the six batches of PCDTPT, PCDTPT_1 through PCDTPT_6. (c) P3HT-equivalent molecular weight distributions of the six batches of PCDTPT, calculated from the respective diffusion coefficient distributions with the power-law relationship in

between 0.4 and 0.9 ppm for the six batches of PCDTPT in CDCl_3 . Due to its more complicated chemical structure and overlapping chemical shifts, we chose to quantify the integrated intensity of chemical shifts over the finite range of 0.4–0.9 ppm for PCDTPT. Because is only valid for the quantification of intensity attenuation of chemical shifts belonging to a single species, we verified that the chemical shifts in this range are all attributable to PCDTPT, and not to the solvent or any impurities in solution. This chemical shift range does not overlap with the chemical shift of water at 1.56 ppm or that of chloroform at 7.26 ppm. The rate at which the signal decays

decreases progressively in the Stejskal–Tanner plot of PCDTPT_1 to PCDTPT_6. The extracted diffusion coefficients of the different batches of PCDTPT are tabulated in the Supporting Information.

b shows the diffusion trace for each batch of PCDTPT obtained from DOSY analysis. Consistent with an increase in conjugation length that we expected given the progressive red shift in the optical absorbance, we observe a decrease in diffusion coefficients from sample PCDTPT_1 to PCDTPT_6.

We were not able to determine the absolute molecular weight of PCDTPT by end-group analysis because the intensities of the chemical shifts associated with the end groups of PCDTPT are negligible and the chemical shifts associated with the bulky alkyl side chains on the donor–acceptor repeating units convolute chemical shifts from other portions of the polymer. This transformation would have allowed us to quantify the absolute number-average molecular weight of PCDTPT. To determine the relative molecular weights of PCDTPT samples, we borrowed a framework commonly used in SEC analysis. We converted the DCD of the six batches of PCDTPT to MWDs, based on the M_w – D correlation we determined for P3HT. The P3HT-equivalent MWDs for PCDTPT are shown in c. To first order, this method of assessing P3HT-equivalent MW gives us a relative estimate of the size of the polymer. From the estimated MWs, we believe the first three batches of PCDTPT (PCDTPT_1, PCDTPT_2, and PCDTPT_3) to be oligomeric in nature, with P3HT-equivalent M_w of 1340, 2270, and 5840 g mol^{-1} , respectively. The P3HT-equivalent M_w for PCDTPT_4, PCDTPT_5, and PCDTPT_6 are 27 200, 29 700, and 73 500 g mol^{-1} . The same analysis carried out on the as-received, unfractionated PCDTPT, in comparison, reveals a P3HT-equivalent M_w of 32 500 g mol^{-1} . The molecular weight increase across the series of PCDTPT samples is consistent with the progressive red shift in their optical spectra. That the M_w of unfractionated PCDTPT falls between those of PCDTPT_5 and PCDTPT_6 is further consistent with its optical spectra, with its maximum absorbance located at a wavelength between those of PCDTPT_5 and PCDTPT_6. A critical assumption we have made with this framework is that P3HT and PCDTPT exhibit the same hydrodynamic characteristics in chloroform. Given that PCDTPT has a larger M_w unit contour length (approximately 600 $\text{g mol}^{-1} \text{nm}^{-1}$ compared to P3HT (approximately 400 $\text{g mol}^{-1} \text{nm}^{-1}$), the P3HT-equivalent M_w 's we extracted for the PCDTPT samples are likely to underestimate their actual molecular weights. Nonetheless, this approach has provided important relative size information about these samples that would otherwise be challenging to obtain.

CONCLUSIONS

We demonstrate DOSY as a complement to SEC for characterizing the size of conjugated polymers. DOSY analysis is particularly useful and relevant to conjugated polymers whose molecular weight characterization by SEC is limited by their absorption characteristics.

We determined a power-law relationship between M_w and D for regioregular P3HT dissolved in chloroform, from which we extracted the fractal dimension of P3HT to be 1.78. The fractal-dimension analysis provides a viable platform to probe the interactions of different pairs of solvent and conjugated polymers. Further, the M_w – D calibration curve can be used

to interconvert M_w and D of future P3HT samples on an absolute basis, or other polymers on a relative basis. Unlike the molecular weight, the diffusion coefficient is dependent on temperature and the solvent used. To ensure accuracy for M_w – D conversion, experiments should be carried out under the same conditions. We also demonstrated that diffusion coefficient distributions obtained by DOSY qualitatively agree with the molecular weight distributions yielded by a combination of SEC and end-group analysis. Quantitative agreement between them is difficult given that the data inversion process can inherently result in artifacts, such as peak-narrowing.

Complementary to conventional SEC, DOSY, a 2D NMR technique, offers a facile way for determining polymer size. It uniquely addresses molecular weight determination for polymers, particularly conjugated polymers, that absorb at SEC detection wavelengths and those that interact with SEC columns. Owing to its ability to measure a wide range of molecular weights and separate chemically distinct species, DOSY shows promise toward becoming a standard method for determining polymer size.

■ ASSOCIATED CONTENT

Supporting Information

The Supporting Information is available free of charge on the at DOI:

P3HT synthesis and characterizations, DOSY operating procedures, PCDTPT solvent-antisolvent Soxhlet extraction, and summary of diffusion coefficients ()

■ AUTHOR INFORMATION

Corresponding Author

*E-mail:

ORCID

Christine K. Luscombe:

Yueh-Lin Loo:

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript.

Notes

The authors declare no competing financial interest.

■ ACKNOWLEDGMENTS

This work was supported by ExxonMobil through its membership in the Princeton E-filiates Partnership of the Andlinger Center for Energy and the Environment. C.K.L. acknowledges NSF DMR 1708317. The P3HT samples were synthesized in part upon work supported by the State of Washington through the University of Washington Clean Energy Institute and via funding from the Washington Research Foundation.

■ REFERENCES

- (1) Zhao, J.; Li, Y.; Yang, G.; Jiang, K.; Lin, H.; Ade, H.; Ma, W.; Yan, H. Efficient Organic Solar Cells Processed from Hydrocarbon Solvents. *Nat. Energy* **2016**, *1*, 15027.
- (2) Sirringhaus, H. 25th Anniversary Article: Organic Field-Effect Transistors: The Path beyond Amorphous Silicon. *Adv. Mater.* **2014**, *26*, 1319–1335.
- (3) Koch, F. P. V.; Rivnay, J.; Foster, S.; Müller, C.; Downing, J. M.; Buchaca-Domingo, E.; Westacott, P.; Yu, L.; Yuan, M.; Baklar, M.; Fei, Z.; Luscombe, C.; McLachlan, M. A.; Heeney, M.; Rumbles, G.; Silva, C.; Salleo, A.; Nelson, J.; Smith, P.; Stingelin, N. The Impact of Molecular Weight on Microstructure and Charge Transport in Semicrystalline Polymer Semiconductors-poly(3-Hexylthiophene), a Model Study. *Prog. Polym. Sci.* **2013**, *38*, 1978–1989.
- (4) Gasperini, A.; Sivula, K. Effects of Molecular Weight on Microstructure and Carrier Transport in a Semicrystalline Poly-(thieno)thiophene. *Macromolecules* **2013**, *46*, 9349–9358.
- (5) Himmelberger, S.; Vandewal, K.; Fei, Z.; Heeney, M.; Salleo, A. Role of Molecular Weight Distribution on Charge Transport in Semiconducting Polymers. *Macromolecules* **2014**, *47*, 7151–7157.
- (6) Strobl, G. *The Physics of Polymers*, 3rd ed.; Springer-Verlag: Berlin, 2007.
- (7) Spiess, H. W. 50th Anniversary Perspective: The Importance of NMR Spectroscopy to Macromolecular Science. *Macromolecules* **2017**, *50*, 1761–1777.
- (8) Augé, S.; Schmit, P.-O.; Crutchfield, C. A.; Islam, M. T.; Harris, D. J.; Durand, E.; Clemancey, M.; Quoineaud, A.-A.; Lancelin, J.-M.; Prigent, Y.; Taulelle, F.; Delsuc, M.-A. NMR Measure of Translational Diffusion and Fractal Dimension. Application to Molecular Mass Measurement. *J. Phys. Chem. B* **2009**, *113*, 1914–1918.
- (9) Einstein, A.; Furth, R.; Cowper, A. D. *Investigations on the Theory of the Brownian Movement*; Courier Dover Publications: Mineola, NY, 1956.
- (10) Chen, A.; Wu, D.; Johnson, C. S. Determination of Molecular Weight Distributions for Polymers by Diffusion-Ordered NMR. *J. Am. Chem. Soc.* **1995**, *117*, 7965–7970.
- (11) Li, W.; Chung, H.; Daeffler, C.; Johnson, J. A.; Grubbs, R. H. Application of ^1H DOSY for Facile Measurement of Polymer Molecular Weights. *Macromolecules* **2012**, *45*, 9595–9603.
- (12) Crutchfield, C. A.; Harris, D. J. Molecular Mass Estimation by PFG NMR Spectroscopy. *J. Magn. Reson.* **2007**, *185*, 179–182.
- (13) Floquet, S.; Brun, S.; Lemonnier, J. F.; Henry, M.; Delsuc, M. A.; Prigent, Y.; Cadot, E.; Taulelle, F. Molecular Weights of Cyclic and Hollow Clusters Measured by DOSY NMR Spectroscopy. *J. Am. Chem. Soc.* **2009**, *131*, 17254–17259.
- (14) Viel, S.; Capitani, D.; Mannina, L.; Segre, A. Diffusion-Ordered NMR Spectroscopy: A Versatile Tool for the Molecular Weight Determination of Uncharged Polysaccharides. *Biomacromolecules* **2003**, *4*, 1843–1847.
- (15) Hardeman, T.; Willot, P.; De Winter, J.; Josse, T.; Gerbaux, P.; Shestakova, P.; Nies, E.; Koeckelberghs, G. Study on the Formation of a Supramolecular Conjugated Graft Copolymer in Solution. *J. Polym. Sci., Part A: Polym. Chem.* **2014**, *52*, 804–809.
- (16) Bronstein, H. A.; Luscombe, C. K. Externally Initiated Regioregular P3HT with Controlled Molecular Weight and Narrow Polydispersity. *J. Am. Chem. Soc.* **2009**, *131*, 12894–12895.
- (17) Cobas, C.; Sýkora, S. Poster Presentation. Bayesian Dosy: A New Approach To Diffusion Data Processing. In *SMASH Small Molecule NMR 2008 Conference 2008*, Santa Fe, NM, Sept 7–10, 2018; SMASH NMR Conference, 2018.
- (18) Stejskal, E. O.; Tanner, J. E. Spin Diffusion Measurements: Spin Echoes in the Presence of a Time-Dependent Field Gradient. *J. Chem. Phys.* **1965**, *42*, 288–292.
- (19) Johnson, C. S., Jr. Diffusion Ordered Nuclear Magnetic Resonance Spectroscopy: Principles and Applications. *Prog. Nucl. Magn. Reson. Spectrosc.* **1999**, *34*, 203–256.
- (20) Cohen, Y.; Avram, L.; Frish, L. Diffusion NMR Spectroscopy in Supramolecular and Combinatorial Chemistry: An Old Parameter - New Insights. *Angew. Chem., Int. Ed.* **2005**, *44*, 520–554.
- (21) Gounarides, J. S.; Chen, A.; Shapiro, M. J. Nuclear Magnetic Resonance Chromatography: Applications of Pulse Field Gradient Diffusion NMR to Mixture Analysis and Ligand-Receptor Interactions. *J. Chromatogr., Biomed. Appl.* **1999**, *725*, 79–90.
- (22) Jerschow, A.; Müller, N. Diffusion-Separated Nuclear Magnetic Resonance Spectroscopy of Polymer Mixtures. *Macromolecules* **1998**, *31*, 6573–6578.

- (23) Teraoka, I. *Polymer Solutions: An Introduction to Physical Properties*, 1st ed.; John Wiley & Sons: New York, 2002; Vol. 3.
- (24) Brinkmann, M.; Wittmann, J.-C. Orientation of Regioregular Poly(3-Hexylthiophene) by Directional Solidification: A Simple Method to Reveal the Semicrystalline Structure of a Conjugated Polymer. *Adv. Mater.* **2006**, *18*, 860–863.
- (25) Kirkwood, J. G.; Riseman, J. The Intrinsic Viscosities and Diffusion Constants of Flexible Macromolecules in Solution. *J. Chem. Phys.* **1948**, *16*, 565–573.
- (26) Heffner, G. W.; Pearson, D. S. Molecular Characterization of Poly(3-Hexylthiophene). *Macromolecules* **1991**, *24*, 6295–6299.
- (27) McCulloch, B.; Ho, V.; Hoarfrost, M.; Stanley, C.; Do, C.; Heller, W. T.; Segalman, R. A. Polymer Chain Shape of Poly(3-Alkylthiophenes) in Solution Using Small-Angle Neutron Scattering. *Macromolecules* **2013**, *46*, 1899–1907.
- (28) Ying, L.; Hsu, B. B. Y.; Zhan, H.; Welch, G. C.; Zalar, P.; Perez, L. A.; Kramer, E. J.; Nguyen, T.; Heeger, A. J.; Wong, W.; Bazan, G. C. Regioregular Pyridal[2,1,3]thiadiazole π -Conjugated Copolymers. *J. Am. Chem. Soc.* **2011**, *133*, 18538–18541.
- (29) Nagata, I. Isobaric Vapor-Liquid Equilibria for the Ternary System Chloroform-Methanol-Ethyl Acetate. *J. Chem. Eng. Data* **1962**, *7*, 367–373.
- (30) Meier, H.; Stalmach, U.; Kolshorn, H. Effective Conjugation Length and UV/vis Spectra of Oligomers. *Acta Polym.* **1997**, *48*, 379–384.
- (31) Klaerner, G.; Miller, R. D. Polyfluorene Derivatives: Effective Conjugation Lengths from Well-Defined Oligomers. *Macromolecules* **1998**, *31*, 2007–2009.
- (32) Izumi, T.; Kobashi, S.; Takimiya, K.; Aso, Y.; Otsubo, T. Synthesis and Spectroscopic Properties of a Series of B-Blocked Long Oligothiophenes up to the 96-Mer: Re-Evaluation of Effective Conjugation Length. *J. Am. Chem. Soc.* **2003**, *125*, 5286–5287.
- (33) Wohlgenannt, M.; Jiang, X. M.; Vardeny, Z. V. Confined and Delocalized Polarons in π -Conjugated Oligomers and Polymers: A Study of the Effective Conjugation Length. *Phys. Rev. B: Condens. Matter Mater. Phys.* **2004**, *69*, 241204.
- (34) Tseng, H. R.; Phan, H.; Luo, C.; Wang, M.; Perez, L. A.; Patel, S. N.; Ying, L.; Kramer, E. J.; Nguyen, T. Q.; Bazan, G. C.; Heeger, A. J. High-Mobility Field-Effect Transistors Fabricated with Macroscopic Aligned Semiconducting Polymers. *Adv. Mater.* **2014**, *26*, 2993–2998.