



Deconstructing Oligomer Distributions: Discrete Species and Artificial Distributions

Abstract: The separation of an oligo(methyl acrylate) distribution, obtained from reversible addition–fragmentation chain transfer (RAFT) polymerization, in a discrete (dispersity = 1) oligomeric library (degree of polymerization between 1 and 22) is presented. The properties of this library in terms of diffusivity, glass transition temperature, and viscosity are determined, filling a significant knowledge gap associated with these materials. The obtained oligomer library is used to construct artificial oligomer distributions on demand. These artificial oligomer distributions are used to highlight the potential to tailor physical properties of a material, while concomitantly demonstrating the limitations associated with size-exclusion chromatography analysis of molecular weight and dispersity in particular.

The last decade has been marked by the rapid development of precision polymer synthesis. Discrete oligomers are regarded as the “Holy Grail” in polymer science, owing to their enormous potential as catalysts (artificial enzymes), as molecular recognition agents (artificial lectins), and as molecular stores of information (artificial DNA).^{1–11} As a consequence, various synthesis strategies that rely on iterative and orthogonal growth, step-growth, or reversible deactivation radical polymerization (RDRP) have been developed to date, and applications in drug delivery and catalysis are currently being explored.^{1–11} Nevertheless, no systematic data is available yet on the properties of discrete synthetic oligomers to allow for a better fundamental understanding of their physical and thermal characteristics, such as diffusivity, glass transition temperature, viscosity, crystallinity, and rheological behavior. Herein, a number of these properties are studied.

Furthermore, mixing discrete oligomers results in artificial distributions, which can be used to tune material properties in a non-chemical pathway. The oligomers are obtained via the deconstruction of a conventional polymer distribution. These

components can then be recombined into any desired distribution.

RDRP is typically fast and does not require protection/deprotection chemistry. The disperse mixtures obtained are separated into discrete oligomers via flash column chromatography, a strategy introduced by Hawker and co-workers.^{1–11} This allows the study of thermal and physical characteristics of oligomers with a stable hydrocarbon backbone that are chemically identical to well-known disperse synthetic polymers.^{1–11}

The properties of disperse acrylic polymers have been widely investigated.^{1–11} For high-performance applications in fields such as data storage,^{1–11} catalysis,^{1–11} or pharmacology,^{1–11} stringent prerequisites necessitate absolute control over material characteristics together with the capability to tune material properties.^{1–11} Parameters such as diffusion coefficients, intrinsic viscosities, and glass transition temperatures are of high interest for discrete species, since to date only average values are known, hampering the theoretical understanding of chain-length dependencies. Being able to provide a full set of physical data for a series of oligomers will enable a better understanding of scaling laws and fundamentals of polymer physics.

RAFT was used to prepare a discrete oligo(methyl acrylate) library ranging from 1 to 22 methyl acrylate monomer insertions (degree of polymerization DP = 1–22). These unimers (1-mers) to docosamers (22-mers) are from here on referred to as DP 1 to 22. The discrete oligo(methyl acrylate)s are expected to behave substantially differently from their disperse high-molecular-weight polymeric counterparts, owing to being monodisperse, but mostly also to not having reached the length yet that is required to form ideal polymer coils. The transition between oligomers and polymers is not precisely defined, but the general consensus is that this point is located around 50 to 100 monomer units when chains switch from a pure Rouse motion towards more reptation-like behavior according to the Edwards tube model in polymer melts.^{1–11} This transition toward oligomers coincides with a much stronger dependency of physical properties on molecular weight.^{1–11}

With discrete oligomers at hand it is also possible to create precisely defined artificial oligomer distributions. The design of tailored molecular weight distributions (MWD) has found substantial interest over the years as the MWD governs the resulting thermal and mechanical properties.^{1–11} Furthermore, artificial distributions can potentially be used to encode information in a simple fashion in a barcode-like manner. Various reported examples exist to tailor unusual MWDs, yet they all start from an inherently disperse polymer mixture.^{1–11}

[*] J. De Neve, Dr. J. J. Haven, Prof. T. Junkers
Polymer Reaction Design Group, School of Chemistry
Monash University
19 Rainforest Walk, Building 23, Clayton, VIC 3800 (Australia)
E-mail: tanja.junkers@monash.edu

J. De Neve, Prof. T. Junkers
Institute for Materials Research, Hasselt University
Martelarenlaan 42, 3500 Hasselt (Belgium)

Dr. S. Harissou
Laboratoire des IMRCP, CNRS UMR 5623, University of Toulouse
118 Route de Narbonne, 31062 Toulouse Cedex 9 (France)

Supporting information and the ORCID identification number(s) for the author(s) of this article can be found under:

The use of discrete oligomers also provides insight into MWD analysis via size-exclusion chromatography (SEC). Polymer distributions are typically characterized by their number-average molecular weight (M_n) and dispersity ($\bar{D}$). However, for narrow distributions ($\bar{D} < 1.5$) the standard deviation (σ) provides a more intuitive measure of dispersion than $\bar{D}$.^[1]

To generate the oligomer library, a crude oligomer mixture obtained from RAFT polymerization of methyl acrylate (MA; see the Supporting Information for experimental details) was used as starting point. Subsequently, flash column chromatography, as first introduced by Hawker as an oligomer separation method,^[1] was employed to isolate discrete oligomers in the molecular-weight range of 432 (DP = 1) to 2261 g mol⁻¹ (DP = 22) (Figure 1). With increasing DP, the relative difference in polarity progressively diminishes, which limits the maximum length of oligomers that can be purified. The library prepared here includes an oligomer of DP 22 (docosamer) which is (to the best of our knowledge) by far the longest reported isolated oligomer via RDRP. DP 22 corresponds to a length often used in block copolymers.^[1]

The influence of oligomer chain length on thermal properties was studied via differential scanning calorimetry (DSC) as shown in Figure 1 (see the Supporting Information for experimental details). A glass transition (T_g) was apparent from DP 3 (−47.5 °C) to 22 (−8.4 °C) as can be expected for non-crystalline oligo(methyl acrylate) (PMA).^[1] While literature values for the T_g of PMA (with M_n of 76 500 g mol⁻¹ and $\bar{D}$ of 1.26) are situated around 10 °C,^[1] much lower T_g values were measured for the small DP oligomers.^[1] This trend is in good agreement with the Flory–Fox equation that is applicable to higher-molecular-weight polymers [Eq. (1)]:^[1]

$$T_g = T_{g,\infty} - \frac{K}{M_n} \quad (1)$$

with $T_{g,\infty}$ the limiting T_g at infinite molar mass and K the Flory–Fox constant (related to the free volume of the polymer matrix^[1]), which are 5.6 ± 0.5 °C and $(3.39 \pm 0.07) \times 10^4$ °C g mol⁻¹, respectively, for the discrete oligomers. The Flory–Fox constant is consistent with literature values.^[1] Thus, shorter oligomer chains with a relative higher abundance of chain end units contribute to an increased free volume and consequently lower T_g . The T_g for the crude oligomer mixture before fractionation was −14.2 °C.

Knowledge on intrinsic viscosities is of high importance for the molecular-weight analysis of polymers. For high-molecular-weight polymers (> 10 000 g mol⁻¹), molecular weight and intrinsic viscosity are related by the Mark–Houwink–Kuhn–Sakurada (MHKS) equation [Eq. (2)]:

$$[\eta] = K \times M^\alpha \quad (2)$$

with $[\eta]$ the intrinsic viscosity, M the molecular weight, and the Mark–Houwink parameters K and α . While the MHKS equation is generally only valid for polymers of substantial length, an increase in intrinsic viscosity was still observed for our longer oligomers (see the Supporting Information). The resulting data obtained in THF at 40 °C fitted the MHKS equation with α of 0.30 ± 0.02 and K of 0.37 ± 0.04 mL g⁻¹. This is a considerable deviation from literature values for α of PMA under otherwise identical conditions.^[1] The lower value of α indicates that oligomers adopt a more compact conformation than their polymeric counterparts in THF solution. Owing to their insufficient length, the oligomers adopt worm-like configurations rather than forming statistical polymer coils. Interestingly, for the intercept of the MHKS fit with reported values for higher MW polymers, the cross-over chain length can be calculated (Supporting Information, Figure S28), from where on oligomers become polymers in the sense of forming random coils. This length is determined to be around 37 chain units. While speculations had been made that




Figure 1. Development of a discrete methyl acrylate oligomer library with a total of 22 entries via reversible addition–fragmentation chain-transfer (RAFT) polymerization followed by flash column chromatography purification. All oligomers were characterized by NMR spectroscopy, size-exclusion chromatography, differential scanning calorimetry, and mass spectrometry to report on physical parameters such as intrinsic viscosity, diffusion coefficient, and glass transition temperature as a function of chain length. MW_{exp} = experimentally determined molecular weight via mass spectrometry, $[\eta]$ = intrinsic viscosity, D = diffusion coefficient, T_g = glass transition temperature.

the transition should occur in this range,¹¹ no reliable method of determination had been found so far.

Figure 2 shows diffusion coefficients obtained through diffusion-ordered NMR spectroscopy (DOSY) measurements in deuterated chloroform. Diffusion coefficients provide a measure of the mobility of the oligomer chains.




Figure 2. Diffusion coefficients as obtained for every individual oligomer chain length through diffusion-ordered spectroscopy.

Knowledge of diffusivity for oligomeric species would remove the need for several assumptions that are typically made in, for example, the theory of bimolecular termination rate coefficients in radical polymerizations. The highest self-diffusion of $11.1 \times 10^{-10} \text{ m}^2 \text{ s}^{-1}$ is measured for DP 1 after which a logarithmic decrease is observed with a final value of $4.3 \times 10^{-10} \text{ m}^2 \text{ s}^{-1}$ for DP 22 (Figure 2). The diffusion coefficient of the starting oligomer mixture before fractionation was measured to be $4.8 \times 10^{-10} \text{ m}^2 \text{ s}^{-1}$. These diffusion coefficients are substantially higher than those of high-molecular-weight polydisperse samples, demonstrating the expected increased mobility of oligomeric chains.¹¹ The best fit of the data to $D = k \times \text{CL}^{-a}$ yields an exponent of -0.306 ± 0.01 (Supporting Information, Figure S30), which is in remarkably good agreement with reported data on the termination rate coefficient in methyl acrylate polymerizations in this chain length regime (note that the chain length dependency of termination and diffusion is directly correlated).¹¹ Again, this provides for the first time a direct and unambiguous determination of data that had to date only been derived in very indirect manner and that had remained subject to speculation. It should be noted that all DOSY experiments were performed in deuterated chloroform while SEC experiments were conducted in THF owing to practical considerations.

Mechanical properties such as plasticity and elasticity are directly dependent on the MWD. Over the past couple of years, the topic of systematically varying dispersity and (to a lesser extent) purposefully manipulating MWDs obtained via RDRP has caught the attention of the scientific community.¹¹ However, explicit knowledge of the relative contribution of each chain length to the overall distribution could not be obtained owing to constraints in the availability of proper starting materials and adequateness of synthetic methods

applied. Studying artificial polymer distributions arising from a deconstructed oligomer library not only allows a deeper understanding of molecular-weight analysis performed via SEC, it also acts as an example of how material properties could be tuned to achieve desired characteristics at will.

With this method, experimentally obtained molecular-weight distributions can be deconstructed and subsequently reconstructed in any shape. To showcase the versatility of this strategy unusual distributions were produced that would normally be inaccessible by any controlled polymerization technique. As a first example we mixed $0.25 \mu\text{mol mL}^{-1}$ of each oligomer with DP 1 to 5 and 18 to 22 together with $0.10 \mu\text{mol mL}^{-1}$ of oligomers with DP 6 to 17 as shown in Figure 3 (see the Supporting Information for more examples). This gives a theoretical number distribution containing 2 peaks at either end of the molecular weight range connected by a lower bridge formed by chains of average length (Figure 3A). In the resulting number distribution after SEC analysis (Figure 3B), M_n calculated from the moments of the SEC distribution displayed very good agreement with the theoretically expected value. However, the overall shape of the MWD is quite different from what some might expect on first glance. The reason for the discrepancy between experimental number distributions and the envisioned distribution is rooted in a band broadening effect that mainly stems from the purely physical effect of axial dispersion. Furthermore, a difference in elution for diastereoisomers could have a minor influence which is currently being studied in our research labs. This leads to the result that even discrete oligomers appear as distributions in SEC (with $\bar{D}$ around 1.02) and hence single oligomer profiles overlap. Owing to the logarithmic nature of SEC separation, overlaps elevate higher MW areas more than lower MW areas. With the input of all individual oligomer profiles obtained from the MHKS plot measurements, an improved simulation of full MWDs is obtained which is nearly identical to the experimental observations (Figure 3B,E). This highlights that even if the components are low in apparent dispersity, band broadening and peak overlaps need to be accounted for to accurately predict overall MWDs. As can be seen in Figure 3D,E, a significantly different theoretical number distribution is required to reach the desired SEC-measured number distribution. For this specific oligomer mixture a T_g of -43.6°C was determined, which is significantly lower than the expected T_g of -21.3°C calculated from the M_n and the Flory–Fox equation. This further demonstrates that not only the average molecular weight must be taken into account, but also the shape and breadth of the MWD. This is in good agreement with a previous study where we had shown that T_g is dependent on dispersity.¹¹

It is remarkable that even though exotic distributions with very substantial multimodality are created (see Supporting Information for further examples), in most cases the overall dispersities remain in the expected range for a well-controlled polymerization (that is, <1.3), and all are <1.5 . This is in agreement with previous reports that dispersity is a misleading measure of the homogeneity of polymer samples, especially in the short chain-length regime. Standard deviation has been proposed as a more intuitive indicator.¹¹ For the example




Figure 3. Representation of the recombination of different chain lengths. A), D) Specific ratios of each discrete oligomer were mixed to create designer distributions. B), E) The resulting number distributions are displayed with a comparison between the simulated result and the experimentally obtained data. C), F) The resulting double weighted SEC distributions. C_i = concentration, d_n = number distribution, d_w = double weighted SEC distribution, $\bar{D}$ = dispersity, M_n = number average molecular weight, σ = standard deviation.

given in Figure 3 B, the standard deviation of the distribution is 671 g mol^{-1} for an M_n of 1336 g mol^{-1} ($\bar{D} = 1.25$). From σ , it is immediately evident that a highly non-uniform mixture has been obtained, while the dispersity alone gives a counter-intuitive impression. In fact, we were unable to create unacceptably high dispersities (defined as $\bar{D} > 1.5$) using our library. Understanding this deceptive feature of MWD dispersity is highly important as more and more research is dedicated to the creation of precision polymers carrying specific compositions and defined spatial arrangements of functionalities.

Acknowledgements

The authors are grateful for helpful discussions with Peter Nichols regarding DOSY NMR and with Maarten Rubens for the simulation of SEC number distributions. They would also like to kindly acknowledge Kei Saito for granting access to their DSC instrument. The authors thank Andres Castro Villavicencio for his help with preliminary experiments. J.D.N. is grateful to the Bijzonder Onderzoeks Fonds (BOF) of Hasselt University for providing a scholarship. Funding from Monash University is also kindly acknowledged.

Conflict of interest

The authors declare no conflict of interest.

Keywords: diffusion · discrete polymers · dispersity · glass transition · RAFT polymerization

- [1] J.-F. Lutz, M. Ouchi, D. R. Liu, M. Sawamoto,
- [2] J.-F. Lutz, J.-M. Lehn, E. W. Meijer, K. Matyjaszewski, *Nat. Rev. Mater.* **2016**, *1*, 16024.
- [3] J. De Neve, J. J. Haven, L. Maes, T. Junkers,
- [4] S. C. Solleder, R. V. Schneider, K. S. Wetzel, A. C. Boukis, M. A. R. Meier,
- [5] E. Maron, J. H. Swisher, J. Haven, T. Y. Meyer, T. Junkers, H. G. Börner, *Angew. Chem. Int. Ed.* **2019**, ; *Angew. Chem.* **2019**,
- [6] J. J. Haven, J. A. De Neve, T. Junkers,
- [7] J. J. Haven, T. Junkers,
- [8] J. Lawrence, S.-H. Lee, A. Abdilla, M. D. Nothling, J. M. Ren, A. S. Knight, C. Fleischmann, Y. Li, A. S. Abrams, B. V. K. J. Schmidt, M. C. Hawker, L. A. Connal, A. J. McGrath, P. G. Clark, W. R. Gutekunst, C. J. Hawker,
- [9] J. M. Ren, J. Lawrence, A. S. Knight, A. Abdilla, R. B. Zerdan, A. E. Levi, B. Oschmann, W. R. Gutekunst, S.-H. Lee, Y. Li, A. J. McGrath, C. M. Bates, G. G. Qiao, C. J. Hawker,
- [10] E. A. Campo, in *Selection of Polymeric Materials* (Ed.: E. A. Campo), William Andrew Publishing, Norwich, NY, **2008**, pp. 1–39.
- [11] J. Lawrence, E. Goto, J. M. Ren, B. McDearmon, D. S. Kim, Y. Ochiai, P. G. Clark, D. Laitar, T. Higashihara, C. J. Hawker,
- [12] S. Martens, A. Landuyt, P. Espeel, B. Devreese, P. Dawyndt, F. Du Prez, *Nat. Commun.* **2018**, *9*, 4451.
- [13] J. W. Kramer, D. S. Treitler, E. W. Dunn, P. M. Castro, T. Roisnel, C. M. Thomas, G. W. Coates,

- [14] P. R. Judzewitsch, T.-K. Nguyen, S. Shanmugam, E. H. H. Wong, C. Boyer, ;
- [15] G. Moriceau, J. Tanaka, D. Lester, G. S. Pappas, A. B. Cook, P. O'Hora, J. Winn, T. Smith, S. Perrier,
- [16] M. E. Cates,
- [17] G. S. Grest,
- [18] N. Corrigan, A. Almasri, W. Taillades, J. Xu, C. Boyer,
- [19] D. T. Gentekos, J. Jia, E. S. Tirado, K. P. Barteau, D.-M. Smilgies, R. A. DiStasio, B. P. Fors,
- [20] N. Corrigan, R. Manahan, Z. T. Lew, J. Yeow, J. Xu, C. Boyer,
- [21] D. T. Gentekos, L. N. Dupuis, B. P. Fors,
- [22] S. Harrison,
- [23] T. Chang, M. S. Lord, B. Bergmann, A. Macmillan, M. H. Stenzel,
- [24] C. Zhang, Y. Zhu, C. Zhou, W. Yuan, J. Du,
- [25] J. Hintermeyer, A. Herrmann, R. Kahlau, C. Goiceanu, E. A. Rössler,
- [26] K. B. Guice, Y.-L. Loo,
- [27] T. G. Fox, Jr., P. J. Flory,
- [28] V. N. Novikov, E. A. Rössler,
- [29] R. F. Boyer,
- [30] B. Metin, F. D. Blum,
- [31] T. Gruendling, T. Junkers, M. Guilhaus, C. Barner-Kowollik,
- [32] N. Cherifi, A. Khoukh, A. Benaboura, L. Billon,
- [33] A. Theis, A. Feldermann, N. Charton, M. H. Stenzel, T. P. Davis, C. Barner-Kowollik,
- [34] V. Yadav, N. Hashmi, W. Ding, T.-H. Li, M. K. Mahanthappa, J. C. Conrad, M. L. Robertson,

Manuscript received: June 2, 2019

Accepted manuscript online: July 9, 2019

Version of record online: ■■ ■■, ■■■■


Zuschriften



Polymerisation

J. De Neve, J. J. Haven, S. Harrisson,
T. Junkers* ————— ■■■■-■■■■

Deconstructing Oligomer Distributions:
Discrete Species and Artificial
Distributions



Eine diskrete RAFT-Bibliothek: Durch die Auftrennung einer Oligo-Methylacrylatverteilung, erhalten durch RAFT-Polymerisation, wird eine diskrete Oligomerenbibliothek aufgebaut. Die Eigenschaften dieser Bibliothek (Diffusionsvermögen, Glasübergangstemperatur und Viskosität) werden bestimmt. Die erhaltene Oligomerenbibliothek wird verwendet, um eine künstliche Oligomerenverteilung nach Bedarf zu erzeugen.