

Appendix I

Mark-Houwink Parameters for Homopolymers

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
Polystyrene	THF	20	1.55	0.692			1
		23	0.682	0.766	50–1000	A	2
		25	1.11	0.725		B	3
			1.60	0.706	> 3		4
			1.17	0.725		B	5
			1.17	0.717		B	6
			1.25	0.707			7
			1.68	0.69			8
			1.41	0.70			9
			1.25	0.717			10
			1.42	0.70			11
			1.16	0.724			12
			1.28	0.70			13
			0.609	0.768			14
		30	1.76	0.679			15
			0.86	0.74		B	16
			1.05	0.731	36–10 ⁴		17
			1.57	0.698			18
			1.05	0.731		B	19
			1.62	0.701		B	20
			1.112	0.723			21
			1.28	0.712	> 10 ⁴	C	22
			17.1	0.428	< 10 ⁴		
		31.15	1.25	0.717	4–1800		23
		35	1.258	0.715			24
			1.580	0.704			25
			1.60	0.703			26
		38	1.247	0.720			27
		40	1.90	0.68			28
			1.31	0.719	19.1–1110	B	29
			1.51	0.706	5.11–1030	A	
	benzene	25	1.13	0.73			30
		30	1.623	0.695	5–400		31
	toluene	25	1.05	0.73			32
			0.662	0.76			33
			11.4	0.470	< 9000		34
			1.06	0.728	> 9000		

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
PMS	chloroform	30	1.786	0.680	5–2000		31
			1.20	0.714	17–10 ⁴		17
			9.86	0.499	0.56–17		
			1.57	0.695		B	35
		60	0.797	0.75			36
		68	1.528	0.691			15
		25	0.716	0.76	100–2800		37
		30	1.36	0.708	24–10 ⁴		17
			11.1	0.502	0.16–24		
			0.49	0.796			38
	<i>p</i> -dioxane	30	2.241	0.655	5–100		31
	MC	25	1.533	0.695			39
		30	1.157	0.718			40
	MC/DCA	30	1.4	0.70		D	41
	cyclohexane	34.5	8.3	0.50		B	35
		44.5	2.30	0.608		B	
	cyclohexanone	40	3.02	0.643		E	42
	MEK	30	1.79	0.642		B	35
	DMF	20	2.40	0.63			43
		30	2.606	0.612	5–400		31
	DMF + 0.01 M LiBr	60	1.30	0.662			44
	DMF	135	2.80	0.606			45
	OCP	25	14.3	0.488			46
		90	1.2	0.70			28
	TCB	127	1.21	0.71			47
		130	0.895	0.727		A	2
		135	1.21	0.707			48
			1.72	0.67			49
		140	1.90	0.655			50
			1.34	0.70			51
		145	4.14	0.610			52
			3.53	0.617			
			1.75	0.67			53
	ODCB	87	1.0	0.73		B	54
		135	1.156	0.715			22
			1.38	0.70	2–900		55
			4.87	0.606			56
			1.51	0.693			57
		138	1.38	0.7		F	58
	<i>m</i> -cresol	130	0.846	0.715		B	59
		135	2.02	0.65	4–200		28
	<i>cis</i> -decalin	25	4.0	0.574	20–24000	B	60
	HFIP/ toluene (2:8)	50	1.795	0.657			61
	Phenol/TCB (1:1)	135	1.303	0.69			62
	CNP	208	1.86	0.657			63
	THF	25	4.2	0.608			11
	TCB	135	1.61	0.672			48

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
PVC	THF	25	1.63	0.766	20-170		4
			1.50	0.77	20-100	B	6
			7.2	0.61	27-100		8
			4.48	0.70			14
			1.6	0.77		G	64
			4.76	0.673			65
		30	1.60	0.77	100-1000	B	5
		35	1.556	0.690			24
			1.8	0.76		B	66
		110	1.61	0.762			67
PVAc	TCB						
	THF	25	3.50	0.63	10-1000	B	5
			0.942	0.737			12
			0.51	0.791			68
			1.6	0.70			69
		30	1.49	0.698			70
PMMA		35	1.56	0.708			71
	TCB	135	1.37	0.687			70
	THF	23	0.93	0.69			8
		25	1.28	0.69	150-1200		9
			0.958	0.695			13
			0.787	0.75			65
			1.48	0.677			72
			1.99	0.660			73
		35	1.22	0.69			26
	chloroform	25	1.47	0.714			73
		30	0.43	0.80			38
		25	3.66	0.578			73
	acetone	25	3.66	0.578			73
	MEK	25	0.71	0.72			38
	benzene	25	0.55	0.76			30
			4.38	0.597			73
		30	0.52	0.76			74
		25	1.91	0.68			33
	toluene		2.08	0.64	> 7800		34
		40	3.66	0.603		E	42
		25	0.404	0.787		A	75
	DMF		2.5	0.625		B	
	TFE	30	0.281	0.88			76
	(100% isotactic) (92% iso) (83% iso) (35% iso) (23% iso) (15% iso)	25	1.665	0.660			77
			1.690	0.659			
			1.719	0.658			
			0.984	0.692			
			0.9577	0.695			
PEMA	THF	25	0.8892	0.694			
							14
PBMA	THF	25	1.549	0.679			78
			2.25	0.66			
	MEK	25	0.503	0.758			14
			0.613	0.7258	$10^4-2 \times 10^4$		79
			0.970	0.68	$10^5-7 \times 10^5$		80

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
POMA	THF	25	5.556	0.560			14
PLMA	THF	25	0.73	0.69			81
PSMA	THF	30	0.90	0.67		B	82
PMA	THF	25	0.388	0.82			83
	toluene	35	2.1	0.60			84
PtBA	THF	25	0.33	0.80		H	85
Polyethylene	ODCB	135	4.77	0.70	6–700		56
			4.90	0.74			86
		138	5.06	0.7		F	58
	TCB	135	5.50	0.704			87
			4.34	0.724			48
			9.54	0.64			49
			5.3	0.7		F	88
HDPE	ODCB	135	5.05	0.693	10–1000		57
	TCB	127	3.58	0.74			47
		130	3.92	0.725			89
		135	9.54	0.64			90
			5.26	0.70			88
			5.23	0.70			91
			7.1	0.67			92
			5.63	0.70			93
		140	3.95	0.726			50
			3.23	0.735			94
		145	1.73	0.784			52
	decalin	135	4.17	0.71			95
			3.9	0.74			96
			4.6	0.73			91
		138	6.2	0.7		F	97
	decane	120	6.98	0.65			95
LDPE	ODCB	135	5.06	0.70	0.2–200		99
LLDPE	TCB	145	5.91	0.69			53
Hydrogenated PB	TCB	135	2.7	0.746	2.4–40		58
PP	TCB	135	1.37	0.75			48
			1.76	0.73			91
		145	1.56	0.76			53
	ODCB	135	1.0	0.78			86
			2.42	0.707		B	98
			1.10	0.80			99
	decalin	135	1.10	0.80			86, 91
Polyisobutylene	THF	25	5	0.60		H	100
		40	6.47	0.593	0.73–67.6	A	29
			5.79	0.593	0.82–80.4	B	
Polycarbonate	THF	25	3.99	0.77		I	28
			4.9	0.67	7–270		101
			4.12	0.69	10–300	J	102
		35	3.18	0.680		K	25
PB	toluene	30	5.19	0.679	0.5–10 ⁴		17
			2.888	0.734			21
		68	2.103	0.753			15

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
	THF	25	1.012	0.621			27
			18.4	0.58			65
			1.6	0.776			67
		30	4.57	0.693	0.5–10 ⁴		17
			2.56	0.74		B	82
		40	3.96	0.697		L	103
	chloroform	30	4.51	0.704	0.19–10 ⁴		17
		40	5.78	0.67	10–100		28
		30	76.0	0.44			
(<i>cis/trans</i> = 0.8)			25	2.36	0.75	3–6	
(20% <i>cis</i> -20% vinyl)			4.57	0.693	80–1100		10
(8% vinyl)			4.51	0.693	20–300		
(28% vinyl)			4.28	0.693	20–200		
(52% vinyl)			4.03	0.693	20–200		
(73% vinyl)			4.10	0.693	2.4–40		
SBR(25% styrene)	THF	25	4.10	0.693	70–1000		28
		40	3.18	0.70			
Natural rubber							
(poly- <i>cis</i> -isoprene)	THF	25	1.09	0.79	10–1000	G	
Polyisoprene	THF	25	1.77	0.753	40–500		10
Butyl rubber	THF	25	0.85	0.75	4–4000		28
PDSX	toluene	25	0.828	0.72			38
		60	0.977	0.725			36
	chloroform	30	0.54	0.77			38
	cyclohexane	35	0.63	0.77			104
	ODCB	87	8.19	0.50	20–800		54
		138	3.83	0.57	25–300		55
	DMAC	25	1.3	0.69		M	105
Nylon 6	<i>m</i> -cresol	25	32	0.62	0.5–5		28
	OCP	90	6.2	0.64			
	HFB	25	4.2	0.76			106
	TFE	25	4.58	0.742	20–100		107
			5.36	0.75	13–100		108
Nylon 66	<i>m</i> -cresol	25	3.53	0.79	0.15–50		28
		130	4.01	1.00	8–24	B	59
	HFIP		19.8	0.63			109
Nylon 610	<i>m</i> -cresol	25	1.35	0.96	8–24		28
Nylon 11	<i>m</i> -cresol	30	9.1	0.69			110
Nylon 12	<i>m</i> -cresol	25	4.6	0.75	10–125		28
	HFIP/ toluene (2:8)	50	6.163	0.6585			61
Trogamid T	DMF	22	2.737	0.706			111
TFA-nylon 6	MC	25	3.355	0.64		N	112
	THF		1.66	0.70		O	113
TFA-nylon 12	MC	30	0.738	0.81		P	114
TFA-Trogamid	THF	25	0.87	0.73		O	113
PET	<i>m</i> -cresol	25	0.077	0.95			28
		135	1.75	0.81	27–32		
			2.0	0.90	0.45–0.8		
	OCP	23	6.31	0.658			115
	PTCE	23	7.44	0.648			

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
	HFIP	23	5.20	0.695			
	PFP	23	3.85	0.723			
	HFIP/PFP (1:1)	23	4.50	0.705			
		25	6.31	0.658			46
	MC/DCAA	30	4.5	0.68		Q	41
	MC/HFIP (7:3)	25	4.034	0.691		R	116
LCA polyester	PFP	50	0.9205	1.05			117
PTHF	cyclohexanone	40	4.16	0.676		E	42
Polyoxymethylene	DMF	135	0.932	0.79			45
PVDBC	THF	25	9.1	0.827			118
PVB	THF	25	1.4	0.80		H	119
POA	THF	25	0.842	0.202	> 12.5	G	120
			0.961	0.674	< 12.5	G	
PDEPP	THF	25	2.5	0.65		S	121
PDPPP, PAPP	THF	30	1.19	0.649		B, T	20
PVK	THF	25	0.127	0.80		U	122
PPS	CNP	210	0.891	0.747			63
PEEK	sulfuric acid	25	0.3849	0.94		B	62
	phenol/TCB (1:1)	115	7.588	0.67		B	62

Abbreviations. THF – tetrahydrofuran; MC – methylene chloride; MEK – methyl ethyl ketone; DMF – *N,N*-dimethylformamide; OCP – *o*-chlorophenol; TCB – 1, 2,4-trichlorobenzene; ODCB – *o*-dichlorobenzene; HFIP – hexafluoroisopropanol; CNP – 1-chloronaphthalene; TFE – trifluoroethanol; DMAC – *N,N*-dimethylacetamide; HFB – hexafluorobutanol; PTCE – phenol/tetrachloroethane (6:4); PFP – pentafluorophenol; PMS – poly(methyl styrene); PVC – poly(vinyl chloride); PVAc – poly(vinyl acetate); PMMA – poly(methyl methacrylate); PEMA – poly(ethyl methacrylate); PBMA – poly(butyl methacrylate); POMA – poly(octyl methacrylate); PLMA – poly(*n*-lauryl methacrylate); PSMA poly(stearyl methacrylate); PMA – poly(methyl acrylate); PtBA – poly(*tert*-butyl acrylate); HDPE – high density polyethylene (PE); LDPE – low density PE; LLDPE – linear LDPE; PP – polypropylene; PB – polybutadiene; SBR – styrene-butadiene rubber; PDSX – polydimethylsiloxane; Trogamid T – poly(trimethylhexamethylene terephthalamide); PET – poly(ethylene terephthalate); LCA polyester-liquid crystalline aromatic polyester; PTHF – poly(tetrahydrofuran); PVDBC – poly(*N*-vinyl-3,6-dibromocarbazole); PVB – poly(vinyl butyral); POA – poly[*N*-(*n*-octadecyl) maleimide]; PDEPP – poly(diethoxyphosphazene); PDPPP – poly(diphenyl phosphazene); PAPP – poly(aryloxy phosphazene); PVK – poly(*N*-vinyl-3,6-dibromocarbazole); PPS – poly(phenylene sulfide); PEEK – poly(arylether ether ketone).

Remarks. A – $[\eta] = KM_n^a$; B – $[\eta] = KM_w^a$; C – narrow MW distribution; D – MC/dichloroacetic acid (8:2) + 0.01 M tetrabutylammonium acetate; E – 0.01 M tetrabutylammonium nitrate included; F – $[\eta] = KM_n^a$; G – use K and a from [4] for PS; H – use K and a from [6] for PS; I – 4,4'-dihydroxy-2,2-propane carbonate; J – use K and a from [9] for PS; K – bisphenol A/diethylene glycol (50:50); L – 35% cis, 55% trans, 10% 1,2; M – poly(methyl) (pyridine-3-yl) siloxane; N – use K and a from [37] for PS; O – use $K = 1.31 \times 10^{-2}$ and $a = 0.714$ for PS; P – use K and a from [38] for PS; Q – MC/dichloroacetic acid + 0.01 M tetrabutylammonium acetate; R – use $K = 7.998 \times 10^{-2}$ and $a = 0.54$ for PS; S – 0.1% tetra(*n*-butylammonium) bromide included; T – 0.1 M LiBr included; U – use K and a from [3] for PS.

References

1. ECHARRI J, IRUIN JJ, GUZMAN GM, AMSORENA J (1979) *Makromol Chem* 180:2749
2. BONI KA, SLIEMERS FA, STICKNEY PB (1968) *J Polym Sci Part A* 26:1579
3. SPATORICO AL, COULTER B (1973) *J Polym Sci Polym Phys Ed* 11:1139
4. PROVDER T, ROSEN EM (1970) *Sep Sci* 5:437
5. GOEDHAR D, OPSHOOR A (1970) *J Polym Sci Part A-2*, 8:1227
6. KOLÍNSKY M, JANČA J (1974) *J Polym Sci Polym Chem Ed* 12:1181
7. MORRIS MC (1971) *J Chromatogr* 55:203
8. GRUBISIC Z, REMPP P, BENOIT H (1967) *J Polym Sci Part B* 5:753
9. RUDIN A, HOEGY HW (1972) *J Polym Sci Part A-1*, 10:217
10. KRAUS C, STACY CJ (1972) *J Polym Sci Part A-2*, 10:657
11. SCHRODER UKO, EBERT KH (1987) *Makromol Chem* 188:1415
12. COLEMAN TA, DAWKINS JV (1986) *J Liq Chromatogr* 9:1191
13. JENKINS R, PORTER RS (1980) *J Polym Sci Polym Lett Ed* 18:743
14. SAMAY G, KUBÍN M, PODEŠVA J (1978) *Angew Makromol Chem* 72:185
15. AMBLER MR (1973) *J Polym Sci Polym Chem Ed* 11:191
16. WILLIAMS RC, SCHMIT JA (1971) *J Polym Sci Part B* 9:413
17. AMBLER MR (1980) *J Appl Polym Sci* 25:901
18. SUDDABY KG, SANAYEI RA, O'DRISCOLL KF, RUDIN A (1993) *Makromol Chem* 194:1965
19. AMBLER MR, MCINTYRE D (1977) *J Appl Polym Sci* 21:2269
20. DEJAEGER R, LECACHEUX D, POTIN PH (1990) *J Appl Polym Sci* 39:1793
21. SMITH WV (1974) *J Appl Polym Sci* 18:3685
22. HANEY MA, ARMONAS JE, ROSEN L (1987) In: PROVDER T (ed) *ACS Symposium Series No. 352*, ACS, Washington, p 119
23. VAN DIJK JAPP, SMIT JAM, KOHN FE, FEIJEN J (1983) *J Polym Sci Polym Chem Ed* 21:197
24. PERKINS G, HAEHN (1990) *J Vinyl Technol* 12:2
25. MAHABADI HKH (1989) *International GPC Symposium*, Newton, Mass, 434
26. MAHABADI HKH (1985) *J Appl Polym Sci* 30:1535
27. ITO K, SAITO T, AOYAMA T (1987) *Polymer* 28:1589
28. EVANS JM (1973) *Polym Eng Sci* 13:401
29. XIE J (1994) *Polymer* 35:2385
30. TSITSILIANIS C, MITSIANI G, DONDOS A (1989) *J Polym Sci Part B Polym Phys* 27:763
31. ZINBO M, PARSONO JL (1971) *J Chromatogr* 55:55
32. WINTERMANTEL M, ANTONIETTI M, SCHMIDT M (1993) *J Appl Polym Sci, Appl Polym Symp* 52:91
33. PRICE GJ, MOORE JW, GUILLET JE (1989) *J Polym Sci Part A Polym Chem* 27:2925
34. SANAYEI RA, O'DRISCOLL KF (1991) *J Macromol Sci Chem A* 28:987
35. VARMA BK, FUJITA Y, TAKAHASHI M, NOSE T (1984) *J Polym Sci Polym Phys Ed* 22:1781
36. MANDIK L, FOKSOVÁ A, FOLTYN J (1979) *J Appl Polym Sci* 24:395
37. OTH J, DESREUX V (1954) *Bull Soc Chim Belges* 63:285
38. DAWKINS JV (1968) *J Macromol Sci Phys B* 2:623
39. BIAGINI E, COSTA G, GATTIGLIA E, IMPERATO A, RUSSO S (1987) *Polymer* 28:114
40. OGAWA T, SAKAI M (1988) *J Polym Sci Part A Polym Chem* 26:3141
41. MOUREY TH, BRYAN TG, GREENER J (1993) *J Chromatogr A* 657:377
42. MOUREY TH, MAILLER SM, FERRAR WT, MOLAIRE TR (1989) *Macromolecules* 22:4286
43. KRANZ D, POHL HU, BAUMANN H (1972) *Angew Makromol Chem* 26:67
44. AZUMA C, DIAS ML, MANO EB (1986) *Macromol Chem Macromol Symp* 2:169
45. OGAWA T (1990) *J Liq Chromatogr* 13:51
46. MARTIN L, LAVINE M, BALKE ST (1992) *J Liq Chromatogr* 15:1817
47. SCHEINERT W (1977) *Angew Makromol Chem* 63:117
48. COLL H, GILDING DK (1970) *J Polym Sci Part A-2* 6:1579
49. WILLIAMSON GR, CERVENKA A (1972) *Eur Poly J* 8:1009
50. BARLOW A, WILD L, RANGANATH R (1977) *J Appl Polym Sci* 21:3319

51. KAŠPARKOVA V, OMMUNDSEN E (1993) *Polymer* 34:1765
52. LEW R, CHEUNG P, BALKE ST, MOUREY TH (1993) *J Appl Polym Sci* 47:1685
53. GRINSHUPUN V, RUDIN A (1985) *Makromol Chem Rapid Commun* 6:219
54. DAWKINS JV, HEMMING M (1972) *Makromol Chem* 155:75
55. DAWKINS JV, MADDOCK JW, COUPE DJ (1970) *J Polym Sci Part A-2* 8:1803
56. TROTH HG (1968) 5th International Seminar for GPC
57. POLLOCK DJ, KRATZ RF (1968) 6th International Seminar for GPC
58. DAWKINS JV, MADDOCK JW (1971) *Eur Polym J* 7:1537
59. DUDLEY MA (1972) *J Appl Polym Sci* 16:493
60. KULICKE WM, PRESCHER M (1984) *Makromol Chem* 185:2619
61. OGAWA T, SAKAI M, ISHITOBI W (1985) *J Polym Sci Polym Chem Ed* 24:109
62. DEVAUX J, DELIMOY D, DAOUST D, LEGRAS R, MERCIER JP (1985) *Polymer* 26:1994
63. STACY CJ (1986) *J Appl Polym Sci* 34:3959
64. LEDERER K, AMTMANN I, VIJAYAKUMAR S, BILLIANI J (1990) *J Liq Chromatogr* 13:1849
65. CHAPLIN RP, HAKEN JK, PADDON JJ (1979) *J Chromatogr* 171:55
66. HATTORI S, ENDOH H, NAKAHARA H, KAMATA T, HAMASHIMA M (1978) *Polym J* 10:173
67. PANG S, RUDIN A (1993) *J Appl Polym Sci* 49:1189
68. PARK WS, GRAESSLEY WW (1977) *J Polym Sci Polym Phys Ed* 15:71
69. CANE F, CAPACCIOLI T (1978) *Eur Polym J* 14:185
70. LECACHEUX D, LESEC J, QUIVORON C, PRECHNER R, PANARAS R, BENOIT H (1984) *J Appl Polym Sci* 29:1569
71. ATKINSON CML, DIETR R (1979) *Eur Polym J* 15:21
72. CHEE KK (1985) *J Appl Polym Sci* 30:1323
73. DOBBIN CJB, RUDIN A, TCHIR MF (1982) *J Appl Polym Sci* 27:1081
74. COHN-GINSBERG E, FOX TG, MASON HF (1962) *Polymer* 3:97
75. KOSSLER I, NETOPILIK M, SCHULZ G, GNAUCK R (1982) *Polym Bull* 7:597 (1982)
76. VEITH CA, COHEN RE (1989) *Polymer* 30:942
77. JENKINS R, PORTER RS (1982) *Polymer* 23:105
78. GRUBISIC-GALLOT Z, LINGELSER JP, GALLOT Y (1990) *Polym Bull* 23:389
79. SIMIONESCU CI, SIMIONESCU BC, NEAMTU I, IOAN S (1987) *Polymer* 28:165
80. FEDORS RF (1979) *Polymer* 20:226
81. MAHABADI HKH, O'DRISCOLL KH (1977) *J Appl Polym Sci* 21:1283
82. ZHONGDE X, MINGSHI S, HADJICHRISTIDIS N, FETTERS LJ (1981) *Macromolecules* 14:1591
83. SZESZTAY M, TUEDOES F (1981) *Poly Bull* 5:429
84. KRAUNAKARAN K, SANTAPPA M (1968) *J Polym Sci Part A-2*, 6:713
85. MRKVIČKOVA L, DANHELKA J (1990) *J Appl Polym Sci* 41:1929
86. OGAWA T, INABA T (1977) *J Appl Polym Sci* 21:2979
87. LEHTINEN A, VAINIKKA R (1989) International GPC Symposium, Newton, MA, 612
88. PEYROUSET A, PRECHNER R, PANARIS R, BENOIT H (1975) *J Appl Polym Sci* 19:1363
89. WAGNER HL, HOEVE CAJ (1973) *J Polym Sci Polym Phys Ed* 11:1189
90. WILLIAMSON GR, CERVENKA A (1972) *Eur Polym J* 8:1009
91. CROUZET P, MARTENS A, MANGIN P (1971) *J Chromatogr Sci* 9:525
92. COTE JA, SHIDA M (1971) *J Polym Sci Part A-2*, 9:421
93. HERT M, STRAZIELLE C (1983) *Makromol Chem* 184:135
94. WILD L, RANGANATH R, RYLE T (1971) *J Polym Sci Part A-2*, 9:2137
95. BOHM LL, LANVER U, LECHNER MD (1983) *Makromol Chem* 184:585
96. DE LA CUESTA MO, BILLMEYER FW Jr (1963) *J Polym Sci A-1*, 1:1721
97. CHIANG R (1965) *J Phys Chem* 69:1645
98. ATKINSON CML, DIETZ R (1976) *Makromol Chem* 177:213
99. OGAWA T, SUZUKI Y, INABA T (1972) *J Polym Sci Part A-1*, 10:737
100. MRKVIČKOVA L, LOPOUR P, POKORNY S, JANČA J (1980) *Angew Makromol Chem* 90:217
101. MOORE WR, UDDIN M (1969) *Eur Polym J* 5:185
102. BAILLY C, DAOUST D, LEGRAS R, MERCIER JP, STRAZIELLE C, LAPP A (1986) *Polymer* 27:1410

103. BARLOW A, WILD L, ROBERTS T (1971) *J Chromatogr* 55:155
104. DAWKINS JV, HEMMING M (1975) *Makromol Chem* 176:1777
105. VILENCHIK LZ, RUBINSTAJN S, ZELDIN M, FIRE WK (1991) *J Polym Sci Part B Polym Phys* 29:1137
106. COSTA G, RUSSIO S (1982) *J Macromol Sci Chem Ed* A18:299
107. AHARONI SM, CILURSO FG, HANRAHALN JM (1985) *J Appl Polym Sci* 30:2505
108. MATTIUSSI A, GECELE GB, FRANCESCONI R (1969) *J Polym Sci A-2*, 7:411
109. SAMANTA SR (1992) *J Appl Polym Sci* 45:1635
110. TERAN CC, MACCHI EM, FIGINI RV (1987) *J Appl Polym Sci* 34:2433
111. HEROLD J, MEYERHOFF G (1980) *Makromol Chem* 181:2625
112. BIAGINI E, COSTA G, GATTIGLIA E, IMPERAT A, RUSSO S (1987) *Polymer* 28:114
113. WEISSKOPF K (1985) *Polymer* 26:1187
114. OGAWA T, SAKAI M (1988) *J Polym Sci Part A Polym Chem* 26:3141
115. BERKOWITZ S (1984) *J Appl Polym Sci* 29:4353
116. OVERTON JR, BROWING HL Jr (1984) In: PROVDER T (ed) *ACS Symposium Series No. 245*, ACS, Washington, p 219
117. KINUGAWA A (1991) *J Liq Chromatogr* 14:1315
118. HORTA A, Saíz E, BARRALES-RIENDA JM, GÓMEZ PAG (1986) *Polymer* 27:139
119. MRKVIČKOVA L, DANHELKA J, POKORY S (1984) *J Appl Polym Sci* 29:803
120. BARRALES-RIENDA JM, GALIECA CR, HORTA A (1983) *Macromolecules* 16:932
121. TARAZONA MP, BRAVO J, RODRIGO MM, SAIZ E (1991) *Polym Bull* 26:465
122. BARRALES-RIENDA JM, GOMEZ PAG, HORTA A, SAIZ E (1985) *Macromolecules* 18:2572

Appendix II

Mark-Houwink Parameters for Polar Polymers

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
PAN	DMF	20	3.25	0.725			1
		25	2.43	0.75			2
		60	0.146	0.897		A	3
PVP	DMF		2.12	0.75		A	4
		60	1.85	0.646		A	3
		MeOH/H ₂ O (1:1)	25	0.851		B	5
P2VP	THF	25	2.23	0.66			6
		35	3.02	0.61			7
		TFA + NaNO ₃	35	0.575	0.922	C	
Polyacrylamide	water		1.62	0.745		D	
			2.57	0.651		E	
		pyridine	25	0.445	0.78	F	8
		NMP	80	0.88	0.73	G	
		DMF	50	1.23	0.69	H	
		sodium formate	25	0.25	0.93	I	9
				0.50	0.83	J	
				0.17	0.95	K	
		see Remark	25	2.5	0.68	L	10
			25	6.80	0.66		11
				1.0	0.755	M	12
			30	0.631	0.80		13
		0.1 M Na ₂ SO ₄	25	1.94	0.70		14
		0.5 M NaCl	25	1.21	0.746	pH 9, M	15
		1 M NaCl		1.84	0.72	pH 9, M	
NaPA	0.3 N NaCl	25	1.69	0.75			16
Phenol (RN)	acetone	25	4.7	1.90	1–8, M_n		17
		30	63.1	0.28	0.37–28, M_n		18
	THF	30	73	0.28	0.54–4.7, M_n		
	DMF	25	18.0	0.51	1–8, M_n		17
	1N NaOH		16.6	0.48			
	(HO) acetone	30	8.13	0.5	0.69–2.6, M_n		18
	PVPDMAEMA LiNO ₃	25	1.42	0.67		N	19
PTAC 50	1 M NaCl	25	5.64	0.90		O	20
PTAC 100	1 M NaCl	25	1.55	0.97		O	20
PTMAC 50	1 M NaCl	25	185	0.66		O	20
PTMAC 100	1 M NaCl	25	59.8	0.72		O	20
PMVEMA	tris-buffer	35	3.17	0.70		P	21
PDMDAAC	0.1 M NaCl	30	3.5	0.62		O	22

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
Poly(<i>N</i> -vinylacetamide)							
	H ₂ O	30	16	0.52		Q	22
Polyamic acid	DMAc	30	2.01	0.79		R	23
PEG, PEO	H ₂ O	25	1.25	0.78			24
		30	1.25	0.78			13
	LiNO ₃	25	2.8	0.72		N	19
		35	3.48	0.70		P	21
PEG	0.1 N NaNO ₃	35	10.1	0.58			25
PEO			3.47	0.70			
	0.42 N NaOH	25	2.5	0.66			26
	<i>p</i> -dioxane	25	3.50	0.71	0.06–19		27
	DMF	25	2.40	0.73	1–30		
		60	5.0	0.653		A	3
			5.50	0.643		A	4
	MeOH/H ₂ O (1:1)	25	2.21	0.75		B	5
PEG	MeCN/H ₂ O (2:8)	35	87.3	0.60			25
PEO			2.45	0.73			
	MeOH/H ₂ O (2:8)	25	3.4	0.75			28
PPG	benzene	30	3.241	0.686	1–4		27
	toluene	30	0.447	0.920	0.8–4		
	<i>p</i> -dioxane	30	2.247	0.715	1–4		
	DMF	30	5.284	0.598	0.8–4		
PVA	H ₂ O	25	14.0	0.60	10–70		29
	0.1 N NaNO ₃	35	13.3	0.56	13–250		30
Cellulose nitrate	THF	25	25.0	1.00	95–2300		31
			82	1.0	DP < 1	S	32, 33
			446	0.76	DP > 1	S	
			6.44	0.73		T	34
Nitrocellulose	THF	25	3.21	0.83			35
Methyl cellulose	H ₂ O	25	10.7	0.61		O	36
Dextran	H ₂ O	25	9.78	0.5			24
	0.1 M NaCl	23	15.7	0.451		U	37
		25	13.6	0.47			38
	0.1 M NaNO ₃	25	37	0.40		V	39
	0.2 M NaNO ₃		48.5	0.39			40
	0.2 M NaNO ₃ + 0.025 M KH ₂ PO ₄	30	47.6	0.34			41
	0.42 N NaOH	25	12.0	0.48			26
	NaOH (0.005 N)	25	18.0	0.438			42
	(0.0185 N)		18.5	0.431			
	(0.097 N)		15.8	0.451			
	(0.287 N)		12.4	0.474			
	(0.501 N)		13.2	0.478			
	(0.671 N)		14.7	0.465			
	(0.877 N)		15.1	0.464			
Branched dextran	MeOH/H ₂ O		103	0.25			43
Pullulan	0.1 M NaCl	25	1.79	0.67			38
	0.2 M NaNO ₃		4.22	0.64			40
	0.1 M NaNO ₃ + 0.025 M KH ₂ PO ₄	30	1.70	0.72			41

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	MW range ($M \times 10^{-3}$)	Re- mark	Ref
Polysaccharide	NaAc buffer	25	1.79	0.67			44
	H ₂ O	25	2.23	0.67		Q	45
			2.36	0.66			46
	0.1N NaNO ₃	35	2.14	0.66			25
	MeCN/H ₂ O (2:8)	35	3.72	0.59			
	MeOH/H ₂ O (2:8)	25	4.4	0.6			28
	H ₂ O	25	6.9	0.6			
Xanthan	0.1M NaNO ₃	25	0.024	1.10		V	39
Xylan	0.5M NaOH	25	2.67	0.73			47
NaPSS	phosphate	25	0.60	0.74		Q, W	45
		25	0.50	0.80		Q, X	45
	NaCl (0.005 N)	25	0.057	1.061			42
	(0.05 N)		0.106	0.935			
	(0.20 N)		0.209	0.845			
	(0.50 N)		0.285	0.794			
	(1.0 N)		0.416	0.741			
	0.1 M NaCl	60	0.24	0.80			48
	NaOH (0.005 N)	25	0.038	1.079			42
	(0.0185 N)		0.146	0.935			
	(0.097 N)		0.458	0.805			
	(0.287 N)		0.281	0.815			
	(0.501 N)		0.198	0.828			
	(0.671 N)		0.174	0.830			
	(0.877 N)		0.110	0.851			
	0.42N NaOH	25	0.2	0.82			26
	see Remark		1.09	0.74		Y	10
Chitosan	see Remark	25	19.9	0.59		O, Z	49
HA	0.15M NaCl	25	6.54	1.16			50
	see Remark		3.6	0.78		Z2	51
Ch4-S	0.2M NaCl	25	17	1.01			50
	0.02M NaCl		3.1	0.74			52
P(DL)LA	THF	31.15	5.49	0.639			53
Proteins	guanidine		3.16	0.66		Z3	54
	see Remark	25	0.0174	1.09		Z4	55

Abbreviations. DMF – *N,N*-dimethylformamide; THF – tetrahydrofuran; TFA – trifluoroacetic acid; NaAc – sodium acetate; phosphate – phosphate buffer; NMP – *N*-methylpyrrolidone; PAN – poly(acrylonitrile); PVP – poly(vinyl pyrrolidone); P2VP – poly(2-vinyl pyridine); NaPA – sodium polyacrylate; phenol (RN) – phenol-formaldehyde resin (random novolak resin); Phenol(HO) – phenol-formaldehyde resin (high-ortho resin); PEG – poly(ethylene glycol); PEO – poly(ethylene oxide); PPG – poly(propylene glycol); PVA – poly(vinyl alcohol); NaPSS – sodium poly(styrene sulfonate); PVPDMAEMA – poly(vinylpyrrolidone-co-dimethylaminoethyl methacrylate); PTAC50 – poly(acrylamide-co-*N,N,N*-trimethylammonium ethyl acrylate chloride); PTAC100 – poly(*N,N,N*-trimethylammonium ethyl acrylate chloride); PTMAC50 – poly(acrylamide-co-*N,N,N*-trimethylammonium ethyl methacrylate chloride); PTMAC100 – poly(*N,N,N*-trimethylammonium ethyl methacrylate chloride); PMVEMA – poly(methyl vinyl ether-co-maleic anhydride); PDMDAAC – poly(dimethyldiallylammonium chloride); HA – hyaluronic acid; Ch4-S – chondroitin 4-sulfate; P(DL)LA – poly(DL-lactic acid).

Remarks. A – 0.01 M LiBr included; B – 0.01 M LiNO₃ included; C – 0.1 % TFA + 0.01 N NaNO₃; D – 0.1 % TFA + 0.20 N NaNO₃; E – 9.1 % TFA + 0.50 N NaNO₃; F – use $K = 0.379 \times 10^{-2}$ and $a = 0.81$ for PS; G – use $K = 1.8 \times 10^{-2}$ and $a = 0.68$ for PS; H – use $K = 2.88 \times 10^{-2}$ and $a = 0.60$ for PS; I – 0.1 M sodium formate at pH 3.50; J – 0.5 M sodium formate at pH 3.50; K – 0.1 M sodium formate + 20 % methanol at pH 3.55; L – 80 % (0.5 M Na₂SO₄ + 0.5 M MeCOOH) + 20 % MeCN; M – $[\eta] = KM_w^a$; N – 0.5 M LiNO₃ (pH 7.0); O – $[\eta] = KM_w^a$; P – 0.1 M tris (hydroxymethyl amino methane) with 0.2 M LiNO₃ adjusted to pH 9.0 with HNO₃; Q – $[\eta] = KM_w^a$; R – 0.03 M LiBr + 0.03 M H₃PO₄ + 1 vol % THF in dimethyl acetamide, use $K = 1.21 \times 10^{-2}$ and $a = 0.69$ for PS; S – $[\eta] = K(DP)^a$, DP – degree of polymerization; T – 0.01 M acetic acid included; U – 0.02 M disodium hydrogen phosphate at pH 7 included; V – 0.2 g/l NaN₃ + 0.1 % ethylene glycol included; W – 0.51 M phosphate buffer (pH 8.0); X – 0.05 M phosphate buffer (pH 8.0); Y – 80 % of 0.03 M Na₂SO₄ + 20 % MeCN; Z – 0.5 M acetic acid + 0.5 M sodium acetate; Z2 – 0.1 M phosphate + 0.1 M NaCl; Z3 – 6 M guanidinium hydrochloride; Z4 – 0.1 M sodium phosphate + 2 % sodium dodecyl sulfate + 0.02 M dithiothreitol (pH 7.0), proteins (bovine serum albumin, chymotrypsinogen, lysozyme chloride, and cytochrome C).

References

1. KRANZ D, POHL HU, BAUMANN H (1972) *Angew Makromol Chem* 26:67
2. KENYON AS, MOTTUS EH (1974) *Appl Polym Symp* 25:57
3. MORI S (1983) *Anal Chem* 55:2414
4. AZUMA C, DIAS ML, MANO EB (1986) *Macromol Chem Macromol Symp* 2:169
5. SENAK L, WU CS, MALAWER EG (1987) *J Liq Chromatogr* 10:1127
6. HUGELIN C, DONDOS A (1969) *Macromol Chem* 126:207
7. NAGY DJ, TERWILLIGER DA, LAWREY BD, TIEDGE WF (1989) *International GPC Symposium*, Newton, MA, 637
8. RAND WG, MUKHERJI AK (1982) *J Chromatogr Sci* 20:182
9. PATTON EV, WONNACOTT DM (1987) *J Chromatogr* 389:115
10. KÜHN A, FORSTER S, LÖSCH R, ROMMELFANGER M, ROSENAUER C, SCHMIDT M (1993) *Makromol Chem Rapid Commun* 14:433
11. ISHIGE T, HAMIELEC AE (1973) *J Appl Polym Sci* 17:1479
12. KULICKE WM, KNIEWSKE R, KLEIN J (1982) *Prog Polym Sci* 8:373
13. SAFIEDDINE AM, HESTER RD (1991) *J Appl Polym Sci* 43:1987
14. KULICKE WM, BÖSE N (1982) *Polym Bull* 7:205
15. MCCARTHY KJ, BURKHARDT CW, PARAZAK DP (1987) *J Appl Polym Sci* 33:1699
16. ROCHAS C, DOMARD A, RINAUDO M (1980) *Eur Polym J* 16:135
17. TOBIASON FL, CHANDLER C, SCHWARZ FE (1972) *Makromolecules* 5:321
18. KAMIDE K, MIYAKAWA Y (1978) *Makromol Chem* 179:359
19. WU CS, SENAK L (1990) *J Liq Chromatogr* 13:851
20. KULICKE WM, JACOBS A (1992) *Makromol Chem Macromol Symp* 61:59
21. WU CS, SENAK L, MALAWER EG (1989) *J Liq Chromatogr* 12:2919
22. DUBIN PL, LEVY IJ (1982) *J Chromatogr* 235:377
23. WALKER CC (1988) *J Polym Sci Part A Polym Chem* 26:1649
24. BAILEY FE, KUCERA JL, IMHOF LG (1958) *J Polym Sci* 32:517
25. NAGY DJ (1990) *J Liq Chromatogr* 13:677
26. CALLEC G, ANDERSON AW, TSAO GT (1984) *J Polym Sci Polym Chem Ed* 22:287
27. ZINBO M, PARSONO JL (1971) *J Chromatogr* 55:55
28. DAWKINS JV, GABBOTT NP, MONTENEGRO AMC (1990) *J Appl Polym Sci Appl Polym Symp* 45:103
29. DIEU HA (1954) *J Polym Sci* 12:417
30. NAGY DJ (1993) *J Liq Chromatogr* 16:3041
31. RUDIN A, HOEGY HW (1972) *J Polym Sci Part A-1*, 10:217
32. MARX-FIGINI M, SOUBELET O (1984) *Polym Bull* 11:281
33. SOUBELET O, PRESTA MA, MARX-FIGINI M (1990) *Angew Makromol Chem* 175:17

34. EREMEEVA TE, BYKOVA TO, GROMOV VS (1990) *J Chromatogr* 522:67
35. BROWN W, WILKSTROM R (1965) *Eur Polym J* 1:1
36. SAKAMOTO N (1987) *Polymer* 28:288
37. MAZSAROFF I, REGNIER FE (1988) *J Chromatogr* 442:15
38. KATO T, TOKUYAMA T, TAKAHASHI A (1983) *J Chromatogr* 256:61
39. TINLAND B, MAZET J, RINAUDO M (1988) *Makromol Chem Rapid Commun* 9:69
40. BAHARY WS, HOGAN MP, JILANI M, ARONSON MP (1995) In: PROVIDER T, BARTH HG, URBAN MW (eds) *Adv Chem Ser* 247, ACS, Washington, p 151
41. BAHARY WS, HOGAN MP (1996) *Int J Polym Anal Charact* 2:121
42. BOSE A, ROLLINGS JE, CARUTHERS JM, OKOS MR, TSAO GT (1982) *J Appl Polym Sci* 27:795
43. CERNY L, McTIERVAN J, STASIW D (1973) *J Polym Sci Symp* 42:1455
44. SOMMERMEYER K, CECHE F, PFITZER E (1988) *Chromatographia* 25:167
45. DUBIN PL, TECKLENBURG MM (1985) *Anal Chem* 57:275
46. KAWAHARA K, OHTA K, MIYAMOTO H, NAKAMURA S (1984) *Carbohydr Polym* 4:335
47. EREMEEVA TE, BYKOVA TO (1993) *J Chromatogr* 639:159
48. MALFAIT T, SLOOTMAEKERS D, CAUWELAERT FV (1990) *J Appl Polym Sci* 39:571
49. YOMOTO C, MIYAZAKI T, OKADA S (1993) *Colloid Polym Sci* 271:76
50. HITTNER DM, COWNAN MK (1987) *J Chromatogr* 402:149
51. LAURENT TC, RYAN M, PIETRUSZKIEWICZ A (1960) *Biochim Biophys Acta* 42:476
52. MATHEWS MB, DORFMAN A (1953) *Arch Biochem Biophys* 42:41
53. VAN DIJK JAPP, SMIT JAM, KOHN FE, FEIJEN J (1983) *J Polym Sci Polym Chem Ed* 21:197
54. NAVE R, WEBER K, POTSCHEKA M (1993) *J Chromatogr A* 654:229
55. CHIKAZUMI N, OHTA T (1991) *J Liq Chromatogr* 14:403

Appendix III

Mark-Houwink Parameters for Copolymers

Polymer	Solvent	Temp (°C)	$K \times 10^2$ (ml/g)	a	Remark	Ref
PVC-PVAc	THF	25	6.72	0.611	10–13% VAc	1
EPM	toluene	30	3.051	0.76	50% PP, A	2
EPDM	THF	35	27.4	0.54		3
EPR	ODCB	135	4.43	0.725		4
			2.42	0.707		5
	toluene	30	3.1	0.72	62% PE, B	6
E-NORB	xylene	90	10.0	0.535	50%	7
	DEB	120	4.93	0.589		
EVA	THF	20	9.7	0.62	27–29% EVA, C	8
P (S-MMA)	THF	ns	0.775	0.76	alternating	9
	MEK		1.15	0.69		
	toluene		1.09	0.73		
	<i>n</i> -chlorobutane		1.08	0.70		
	THF		0.641	0.76	1:1 block	
	MEK		1.466	0.67		
	toluene		1.318	0.69		
	<i>n</i> -chlorobutane		4.446	0.55		
	toluene	ns	1.14	0.70	statistical, 30% S	10
	<i>n</i> -chlorobutane		2.65	0.60		
	toluene		1.32	0.71	57% S	
	<i>n</i> -chlorobutane		2.49	0.63		
	toluene		0.832	0.75	71% S	
	<i>n</i> -chlorobutane		1.76	0.67		
P (S-MAH)	THF	25	3.98	0.595	MAH 5– 50mol%, B	11
P (S-AN)	DMF	20	1.45	0.71	12% S, D	12
			1.80	0.71	25% S	
			2.65	0.72	52% S	
		25	1.86	0.690	15–82% AN, E	13
	THF		1.98	0.681	0–35% AN, E	
	MEK		3.30	0.619	10–48% AN, E	
P (AN-EVE)	DMF	55	0.142	0.9636	18% EVE, F	14
P (SA-AA)	0.5M NaCl	25	0.81	0.789	10% SA, G, pH 9	15
	1M NaCl		0.307	0.860		
	0.5M NaCl		1.09	0.775	20% SA	
	1M NaCl		1.307	0.759		
	0.5M NaCl		5.78	0.655	50% SA	
	1M NaCl		2.98	0.695		
	0.5M NaCl		0.638	0.844	70% SA	
	1M NaCl		0.026	1.072		

Abbreviations. THF – tetrahydrofuran; ODCB – *o*-dichlorobenzene; DEB – diethylbenzene; MEK – methyl ethyl ketone; ns – not specified; PVC – polyvinyl chloride; PVAc – polyvinyl acetate; EPM – ethylene-propylene copolymer; EPDM – terpolymer of ethylene, propylene, diene monomers; EPR – ethylene-propylene rubber; E-NORB – ethylene-norbornene (50%); EVA – ethylene-vinyl acetate copolymer; S – polystyrene (PS); MMA – polymethyl methacrylate (PMMA); MAH – maleic anhydride; AN – polyacrylonitrile (PAN); EVE – ethyl vinyl ether; SA – sodium acrylate; AA – acrylamide.

Remarks. A – use $K = 1.112 \times 10^{-2}$ and $a = 0.723$ for PS; B – $[\eta] = KM_w^a$; C – use $K = 1.55 \times 10^{-2}$ and $a = 0.692$ for PS; D – use $K = 2.40 \times 10^{-2}$ and $a = 0.63$ for PS and $K = 3.25 \times 10^{-2}$ and $a = 0.725$ for PAN; E – $[\eta] = K(W_{AN} + 1.041)^a M_w^a$, W_{AN} : weight fraction of AN unit; F – 0.05 M LiBr included, use $K = 2.2 \times 10^{-2}$ and $a = 0.615$ for PS; G – $[\eta] = KM_w^a$; H – use $K = 1.17 \times 10^{-2}$ and $a = 0.717$ for PS.

References

1. JANČA J, MRKVIČKOVÁ L, KOLÍNSKY M (1978) J Appl Polym Sci 22:2661
2. SMITH WV (1974) J Appl Polym Sci 18:3685
3. CHIANTORE O, CINQUINA P, GUAITA M (1994) Eur Polym J 30:1043
4. GIANOTTI G, CICUTA A, ROMANINI D (1980) Polymer 21:1087
5. ATKINSON CML, DIETZ R (1976) Makromol Chem 177:213
6. DE CHIRICO A, ARRIGHETTI S, BRUZZONE M (1981) Polymer 22:529
7. BRAUER E, WIEGLEB H, HELMSTEDT M (1986) Polym Bull 15:551
8. ECHARRI J, IRUIN JJ, GUZMAN GM, AMSORENA J (1979) Makromol Chem 180:2749
9. KOTAKA T, TANAKA T, ONHUMI H, MURAKAMI Y, INAGAKI H (1970) Polym J 1:245
10. GOLDWASSER JM, RUDIN A (1983) J Liq Chromatogr 6:2433
11. CHOW CD (1976) J Appl Polym Sci 20:1619
12. KRANZ D, POHL HU, BAUMANN H (1972) Angew Makromol Chem 26:67
13. MENDELSON RA (1987) In: PROVIDER T (ed) ACS Symposium Series No 352, ACS, Washington, p 263
14. KENYON AS, MOTTUS EH (1974) Appl Polym Symp 25:57
15. MCCARTHY KJ, BURKHARDT CW, PARAZAK DP (1987) J Appl Polym Sci 33:1699

Appendix IV

Specific Refractive Index Increments

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	$A_2 (\times 10^3)$	Ref, Remark
Polystyrene	toluene	632.8	0.110	23		1
		632.8	0.108	25		2, A
		632.8	0.108			3
		632.8	0.107			4
		632.8	0.109	22	0.5–0.3	5
		632.8	0.111	20		6
		670	0.108			7
		589.3	0.107			8, C
	benzene	546.0	0.104			9
		546.0	0.1064			9
		546.0	0.109	25		10
		436	0.112	25		10
	CCl ₄	546.0	0.146			9
		488	0.199			10
	tetrahydrofuran (THF)	632.8	0.190			3
		632.8	0.193	20		6
		632.8	0.1845	25		11
		632.8	0.184	30		12
		632.8	0.186			4
		632.8	0.184			13
		632.8	0.188	22	0.47–0.3	5
		632.8	0.192	25		14
		632.8	0.184	40		15
		670	0.180	25		11
		670	0.1805	30		16, D
	chloroform	632.8	0.155			3
		632.8	0.1608			17
		546.0	0.169	25		10
		436	0.161	25		10
	acetone	670	0.224			7
	methyl ethyl ketone (MEK)	632.8	0.212	22	0.125–0.06	5
		632.8	0.214			7
		670	0.213			7
		589.3	0.212			8, C
		546.0	0.220			9
	tetrahydronaphthalene	670	0.0615			7

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Polystyrene	MC/DCAA (8:2)	632.8	0.156			18, E
	ethyl benzoate	632.8	0.103	15		19
	dimethyl-	632.8	0.165	20		7
	formamide (DMF)	632.8	0.159			20, F
	tetrachloroethylene (TCE)	632.8	0.0934	25		21
	<i>p</i> -dioxane	546.0	0.152	35		22
	(star)	546.0	0.168	35		22
	cyclohexane	546.0	0.170	35		22
	(star)	546.0	0.168	35		22
Poly(dimethylsiloxane)	TCE	632.8	-0.0932	25		21
	toluene	632.8	-0.0913	26		20
		632.8	-0.0648	26		20
Poly(styrene-divinylbenzene)	DMF/LiBr	546	0.170	30		23
	THF	546.1	0.1963	30		24
Poly(styrene-methyl methacrylate)	ethyl benzoate	632.8	0.0398	15		19, G
Poly(methyl methacrylate)	THF	632.8	0.083	25	0.2	25
		632.8	0.084			26, H
		632.8	0.084			13
		632.8	0.084			14
		632.8	0.084			27
		632.8	0.09			28
		589	0.0865	23		29
		546	0.0871	25		10
	HFIP	436	0.0887	25		10
		632.8	0.190	25		30, J
		632.8	0.190			27
		546	0.0157	25		10
	toluene	488	0.010	18		19
		439	0.0094	25		10
		632.8	0.053	25		31
		MEK	546	0.1140		9
		546	0.1173	25		10
		436	0.100	25		10
		546.0	-0.010			9
		546.0	-0.011	25		10
	benzene	436	-0.0039	25		10
		CCl ₄	546.0	0.023		9
		acetone	546.0	0.1340		9
Poly(ethyl methacrylate)	MEK	546.0	0.104	23		10
	ethyl acetate	436	0.109	25		10
Poly(<i>n</i> -butyl methacrylate)	MEK	546.0	0.102	25		10
		436	0.103	25		10
	benzene	546.0	-0.014	25		10
		436	-0.023	25		10

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Poly(methacrylic acid)	ethanol	436	0.154	25		10
	methanol	546	0.134	25		10
Poly(methyl acrylate)	benzene	436	-0.019	30		10
	acetonitrile	546.0	0.118	25		10
		436	0.120	25		10
Poly(ethyl acrylate)	acetone	546.0	0.107	23		10
		436	0.109	23		10
	chloroform	546.0	0.0363	25		10
	MEK	546.0	0.0856	20		10
		436	0.0870	20		10
Poly(<i>n</i> -butyl acrylate)	acetone	436	0.0870	20		10
	benzene	546	-0.0292	30		10
	THF	546	0.0651	30		10
		632.8	0.067			6
	toluene	546	-0.0239	30		10
		632.8	-0.024	20		6
	MEK	632.8	0.097	20		6
	DMF	632.8	0.016	20		6
Poly(<i>tert</i> -butyl acrylate)	MEK	546	0.0818	25		10
	propyl alcohol	546	0.074			32
Poly(vinyl chloride)	THF	632.8	0.101			20
		589.0	0.106	23		29
		589.0	0.115			29
		589.0	0.115	25		10
		578	0.1010	16.5		10
		546.0	0.1017	16.5		10
		546.0	0.116	25		10
		435.8	0.115	20		33
		435.8	0.1124	20		34
		435.8	0.1074	25		35
		435.8	0.104	16.5		10
		435.8	0.119	25		10
	cyclohexanone	632.8	0.0650			20
		589.0	0.076	25		10
		546.0	0.077	25		10
		435.8	0.079	25		10
Polyisoprene	toluene	632.8	0.031			3
	THF	632.8	0.127			3
		589.0	0.156			29
	chloroform	632.8	0.093			3
(<i>cis</i> -1,4)	benzene	546.0	0.0194	20		10
		436	0.0143	20		10
(<i>trans</i> -1,4)	cyclohexane	436	0.117			10
Polybutadiene	toluene	632.8	0.032			3
	THF	632.8	0.132			3
		632.8	0.1295	26		20, K
		589.0	0.132	40		29
	chloroform	632.8	0.094			3
		546.0	0.083			10

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Polybutadiene (<i>cis</i> -1,4) (<i>trans</i> -1,4) (1,2-)	cyclohexane	632.8	0.1151	30		36
		632.8	0.1084	30		36
		632.8	0.0873	30		36
		632.8	0.111	30		36, L
		546	0.118			10
		546	0.1174	25		9
		436	0.126			10
	benzene	436	0.1345	25		9
		546	0.0086	20		10
		546	0.0099	25		9
		436	0.0117	20		10
	hexane	436	0.0160	25		9
		546	0.1523	25		9
		436	0.2181	25		9
Polychloroprene	THF	632.8	0.1274	25		11
	MEK	546	0.156	25		10
		436	0.162	25		10
Polyisobutylene	1-chloronaphthalene	632.8	-0.122	135		37
		578	-0.128	135		37
		546	-0.131	135		37
		436	-0.146	135		37
	trichlorobenzene (TCB)	632.8	-0.051	135		37
		578	-0.053	135		37
		546	-0.054	135		37
		436	-0.066	135		37
	THF	632.8	0.1026	23		20, M
		632.8	0.125	25	0.35	38
		546.1	0.114	25		39
	toluene	632.8	0.106	25		2, B
Poly(1-butene)	1-chloronaphthalene	632.8	-0.177	135		37
		578	-0.183	135		37
		546	-0.187	135		37
		436	-0.206	135		37
	TCB	632.8	-0.103	135		37
		578	-0.105	135		37
		546	-0.108	135		37
		436	-0.120	135		37
	<i>n</i> -nonane	436	-0.108	35		10
Polyethylene	TCB	632.8	-0.097	135		20
		632.8	-0.104	135		12
		632.8	-0.098	145		12
		632.8	-0.098	145		40
		632.8	-0.091	145		41
		546	-0.106	135		10
	1-chloronaphthalene	589.3	-0.1063	135		8, C
		589.3	-0.1085			8, C
		632.8	-0.177	145		20

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Polyethylene	decane	589.3	-0.1883			8
		546.0	-0.191	135		42
		577	0.1200	125		43
		546	0.1213	125		43
		436	0.1263	125		43
	<i>o</i> -dichlorobenzene (ODCB)	404	0.1233	125		43
		632.8	-0.056	135		20
		589	-0.090	135		29
	1-cyclonaphthalene	546	-0.078	120		10
		546	-0.214	125		10
		436	-0.245	125		10
HDPE	TCB	632.8	-0.112	145	2.00	44
		632.8	-0.107	135		37
		578	-0.108	135		37
		546	-0.110	135		37
		436	-0.125	135		37
	(SRM 1475) ODCB	632.8	-0.104	135	1.90	45
		632.8	-0.056	145	1.41	44
		589	-0.069	135		29
	(SRM 1475) 1-chloronaphthalene	632.8	-0.056	135		45
		632.8	-0.189	145	0.68	44
		632.8	-0.183	135		37
		578	-0.188	135		37
		546	-0.192	135		37
	(SRM 1475) diphenylmethane	436	-0.215	135		37
		632.8	-0.177	145		45
		(SRM 1475) 589.3	-0.1932	135		8
		546	-0.125	142		46
	LDPE TCB	632.8	-0.108	145	3.05	44
		632.8	-0.102	135		37
		578	-0.103	135		37
		546	-0.105	135		37
		436	-0.117	135		37
(SRM 1476) LDPE	TCB	632.8	-0.091	135	4.3	45
		632.8	-0.091	140	0.42	47
		632.8	-0.051	145	1.71	44
		589.0	-0.104	138		29
		632.8	-0.185	145	0.87	44
	ODCB	632.8	-0.178	135		37
		578	-0.184	135		37
		546	-0.189	135		37
		546	-0.195	125		48
		436	-0.212	135		37
	1-chloronaphthalene	(SRM 1476) 589.3	-0.1916	135		8
		632.8	-0.106	145	1.50	44
		632.8	-0.106	145		49, N
		632.8	-0.103	145		49, O
		632.8	-0.048	145	1.05	44
Linear-LDPE	TCB	632.8	-0.180	145	0.79	44
		632.8	-0.180	145		44

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Polypropylene	1-chloronaphthalene	546	-0.227	125		10
		546	-0.191	125		27
		436	-0.228	125		10
		632.8	-0.173	135		37
		578	-0.180	135		37
		546	-0.184	135		37
		436	-0.205	135		37
		632.8	-0.177	135		37
		578	-0.183	135		37
		546	-0.188	135		37
		436	-0.211	135		37
	TCB	632.8	-0.095	135		50
		632.8	-0.093	145		49
		632.8	-0.091	145		20
		632.8	-0.092	145		51
		632.8	-0.094	145		51
		632.8	-0.102	135		37
		578	-0.105	135		37
		546	-0.107	135		37
		436	-0.121	135		37
		632.8	-0.105	135		37
		578	-0.109	135		37
		546	-0.111	135		37
		436	-0.123	135		37
Polyoxymethylene	DMF	632.8	-0.0505	135		52
Polyethylene terephthalate	HFIP	632.8	0.257		2.9	53
	HFIP/PFP (5:5)	632.8	0.242			53, P
	MC/DCAA (8:2)	632.8	0.148	RT		18, E
	DCAA	589	0.106			54, Q
	<i>m</i> -cresol	589.0	-0.073	25		29
	<i>o</i> -chlorophenol	589.0	-0.070	25		29
Polyamide 6	HFIP	632.8	0.2375	25		55
	MC/DCAA (8:2)	632.8	0.180	RT		56
	<i>o</i> -chlorophenol	589.0	-0.012	90		29
Polyamide 11	MC/DCAA (8:2)	632.8	0.133	RT		56
	HFIP	546	0.25	30	7.8-5.6	57
Polyamide 12	MC/DCAA (8:2)	632.8	0.133	RT		56
	HFIP	632.8	0.2212			58
		546	0.25	30		59
Polyamide 6, 6 (46 K) (32 K)	MC/DCAA (8:2)	632.8	0.182	RT		56
			0.188	RT		56
			0.194	RT		56
	HFIP	632.8	0.241	25	4.8	60
	formic acid	632.8	0.136	25		60
	<i>m</i> -cresol	589.0	-0.016	130		29
Polyamide 6, 9	MC/DCAA (8:2)	632.8	0.163	RT		56

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Polyamide 6, 10	MC/DCAA (8:2)	632.8	0.163	RT		56
Polyamide 6, 12	MC/DCAA (8:2)	632.8	0.149	RT		56
Polyamide 6T	MC/DCAA (8:2)	632.8	0.201	RT		56
Silk (Silkworm)	HFIP	632.8	0.236			61
(Spider)	HFIP	632.8	0.235			61
Polyacrylonitrile	DMF	632.8	0.092	25		31
		546	0.082	20		10
		436	0.087	20		10
	dimethylsulfoxide	546	0.031	25		10
		436	0.029	25		10
	dimethylacetamide	546	0.0769	25		10
		436	0.0767	25		10
	THF	632.8	0.1546	23		20
Poly(acrylonitrile-styrene) (28.5/71.5)						
Polyurethane	THF	632.8	0.0863	25		62
		632.8	0.1469	23		20, R
Poly(methyl vinyl ether)	cyclohexane	632.8	0.050	50		63
PMVEMA	0.1 M tris	632.8	0.227			64, S
Poly(phenyl acetylene)	THF	632.8	0.2864	25		65
Epoxy resin	THF	632.8	0.187	23		20
Phenoxy resin	THF	632.8	0.1773			26
Polycarbonate	THF	632.8	0.177			20
		632.8	0.1855			20
Polyphosphazene I	THF	632.8	0.160	30		66, T
		632.8	0.145	30		66, T
		632.8	-0.029	30		66, T
		632.8	-0.023	25	1.0	67, T
	acetone	632.8	0.019	25	5.1	67, T
		632.8	-0.053	40	6.7	67, T
	cyclohexanone	632.8	-0.053	40	6.7	67, T
		632.8	-0.053	40	6.7	67, T
Poly(ether sulfone)	DMF	632.8	0.188	25		4
Polyimide	DMF	632.8	0.208	25		4
	N-methylpyrrolidone	632.8	0.132			68, U
PEEK (MW 14300-22600)	conc. H ₂ SO ₄	632.8	0.376		4.3-2.0	69, V
		632.8	0.419		1.8-2.7	69, V
		632.8	0.419		1.8-2.7	69, V
Poly(phenylene sulfide)	1-chloronaphthalene	632.8	0.167	220		70
		632.8	0.167	220		70
Poly(vinyl butyral)	HFIP	632.8	0.189	25		30, J
	THF	632.8	0.089			30, J

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark		
Poly(2-vinylpyridine)	benzene	546	0.075	25		71		
Poly(4-vinylpyridine)	DMF	436	0.160	25		10		
	chloroform	436	0.150	25		10		
Poly(vinylpyrrolidone)	DMF	632.8	0.095	23		20		
	chloroform	546	0.108			10		
			436	0.108			10	
			546	0.185			10	
	water	546	0.185			10		
			436	0.185			10	
6 FDA/p-PDA	N-methylpyrrolidone	632.8	0.107			72, W		
6 FDA/MDA		632.8	0.132			72, W		
BTDA/DDS		632.8	0.145			72, W		
Methylated humic acid	THF	632.8	0.22	−0.042		73		
Benzylated humic acid	THF	632.8	0.19	−0.041		73		
Hydroxyethyl cellulose acetate	THF	488	0.0734	25		74		
Poly(vinyl acetate)	THF	632.8	0.0517	25		11		
			632.8	0.0471	26		20, X	
			632.8	0.0402	26		20, Y	
			632.8	0.077	23		20	
			546	0.104	25		10	
	ethyl acetate acetone	436	0.104	25		10		
		MEK	546	0.080	25		10	
				436	0.083	25		10
			Poly(vinyl alcohol)	0.05 M NaNO ₃	632.8	0.1501	27	
		0.05 M NaNO ₃		632.8	0.1429	27		75, Z
	632.8			0.1501	25		76, a	
	632.8			0.1429	25		76, b	
	632.8			0.1534	23		20	
0.1 M KH ₂ PO ₄	546	0.164		30		10		
		436		0.168	30		10	
Polyacrylamide	water	632.8		0.1735			77	
				632.8	0.142	23		20, C
				632.8	0.1829	25		20, d
			546	0.163			10	
			632.8	0.1587	25		20, e	
	1 M NaCl	632.8	0.1556	25		20, f		
	0.1 M Na ₂ HPO ₄	632.8	0.163			78		
	0.02 M Na ₂ SO ₄	632.8	0.176	23		79, g		
				0.174	23		79, h	
			632.8	0.165			80	
Poly(acrylamide-co-sodium acrylate)	1 M NaCl	632.8	0.165			81		
	0.1 M NaH ₂ PO ₄ + 0.3 M Na ₂ SO ₄ , pH 2.2	632.8	0.16			20		
(70/30)	0.1 M NaNO ₃	632.8	0.165			20		
Sodium polyacrylate	0.3 M NaCl	488	0.159	25		82		
	0.1 M NaCl	632.8	0.175	23		20		
	water	632.8	0.1463	23		20, i		

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Poly(acrylic acid)	aqueous NaCl	436	0.158	30		10
		632.8	0.0738	23		20
		632.8	0.0994	23		20
	0.2N HCl	632.8	0.133			83
Poly(allyl amine)	0.1% TFA/	632.8	0.2034	35		84, j
	0.20M NaNO ₃	632.8	0.1950	35		84, k
Poly(vinyl amine)	0.1% TFA/0.20M NaNO ₃	632.8	0.1751	35		84, m
Branched polyethyleneimine						
	water	632.8	0.210	35		85
	1 M NaCl	632.8	0.195	35		85
	methanol	632.8	0.225	35		85
Poly(ethylene oxide)	methanol	632.8	0.145	25		86
Dextran	water	632.8	0.147			87, n
	water	632.8	0.150	25		88
	0.1 M KNO ₃	632.8	0.150	25		88
	0.05 M KH ₂ PO ₄ (pH 7)	632.8	0.137			87, n
	0.15 M NaCl	632.8	0.145			89
	0.05 M K ₂ HPO ₄ (pH 7)	632.8	0.1378		0.41	90
	water	546	0.148			91
	0.5 M NaCl	546	0.145			91
	water	436	0.150			91
	0.5 M NaCl	436	0.148			91
	0.2 M NaNO ₃	514.5	0.147	RT		92
DEAE-dextran	0.8 M NaNO ₃	632.8	0.150	20		93, o
Pullulan	0.2 M NaNO ₃	514.5	0.147	RT		92
	0.15 M NaCl	632.8	0.145			89
	water	488	0.148	25		94
Polysaccharide	water	632.8	0.146			95
	0.1 M NaCl	632.8	0.143			96, p
(anionic)	0.1 M NaCl	632.8	0.143			96, q
Sodium hyaluronate	0.1 M NH ₄ NO ₃	632.8	0.155		3	97
Sodium heparin	0.1 M NaCl	632.8	0.163	23		98, r
Sodium poly(styrene sulfonate)						
	water	632.8	0.17			99
(0.9 meq/g)	0.05 M NaCl	546	0.212	25		10
(1.8 meq/g)		546	0.207	25		10
(2.0 meq/g)	0.10 M NaCl	546	0.195	25		10
(2.7 meq/g)		546	0.205	25		10
	0.1 M NaNO	632.8	0.195			100
Poly(sulfoalkyl methacrylate)						
(ethyl)	0.1 M NaCl	532	0.135	25		101
(hexyl)		532	0.140	25		101
(decyl)		532	0.170	25		101
(octyl)		532	0.149	25		101
Hydroxyethyl-cellulose	0.1 M NaCl	632.8	0.159			102

Sample	Solvent	Wave-length (nm)	dn/dc (ml/g)	Temp (°C)	A ₂ (× 10 ³)	Ref, Remark
Carboxymethyl-cellulose	0.1 M NaCl	632.8	0.147			102
PNaAMPS	water	632.8	0.20			99, s
BSA	water	632.8	0.187	25		103, t
BSA-SDS	water	632.8	0.376	25		103, u
Ovalbumin-SDS	water	632.8	0.374	25		103
Ribonuclease-SDS	water	632.8	0.398	25		103
Ribonuclease A	75 % A – 25% B	632.8	0.172	7.5 × 10 ⁻²		104, v
Lysozyme	65 % A – 35% B	632.8	0.182	-5.39 × 10 ⁻²		104, v
BSA	58 % A – 42 % B	632.8	0.172	7.49 × 10 ⁻²		104, v
Bovin alkaline phosphatase	50 % A – 50% B	632.8	0.142	0.854		105, w
	60 % A – 40 % B	632.8	0.1188	-9.81		105, w
	70 % A – 30%B		0.0956	-163		106, w
	70 % A – 30 % B	632.8	0.0956	-163		105, w
Bovin thyroglobulin (MW 669000)	0.10 M Na ₂ SO ₄	632.8	0.165	20		106, x
Serum albumin (MW 68000)	0.10 M Na ₂ SO ₄	632.8	0.165	20		106, x
Chymotrypsinogen A (MW 25900)	0.10 Na ₂ SO ₄	632.8	0.170	20		106, x
DNA	water	632.8	0.166			99
DNA fragment	0.1 M NaCl	632.8	0.168	25	0.6	107

Remarks. A: $dn/dc = 0.108 - 21.0/M_n$; B: $dn/dc = 0.106 - 12.4/M_n$; C: polystyrene MW- $(dn/dc)_{\text{toluene}} - (dn/dc)_{\text{MEK}}$, $1.8 \times 10^6 - 0.109 - 0.216$, $97200 - 0.107 - 0.214$, $51000 - 0.106 - 0.212$, $19800 - 0.103 - 0.213$, $10300 - 0.102 - 0.209$, $4800 - 0.101 - 0.210$, $2030 - 0.0985 - 0.208$, polyethylene/trichlorobenzene $dn/dc = -(0.1023 + (20.4/M))$; D: $(dn/dc)_{670} = 0.9783 (dn/dc)_{632.8}$, $(dn/dc)_{670} = 0.1804 - 9.149/M$; E: methylene chloride; F: DMF – *N,N*-dimethylformamide; G: 60% MMA diblock; H: PS/THF, $A_2 = 0.01 M_w^{-0.25}$, PMMA/THF, $A_2 = 0.012 M_w^{-0.29}$; J: vinyl alcohol content ranging from 11 to 23%, hexafluoroisopropanol; K: $M_w = 6160$; L: $dn/dc = 0.111 - 15.3/M_n$ (36% *cis*-1,4, 57% *trans*-1,4, 7% 1,2-); M: $M_w = 6100$ (0.0974 for $M_w = 3300$); N: ethylene-co-octene-1; O: ethylene-co-butene-1; P: pentafluorophenol; Q: dichloroacetic acid; R: $M_w - dn/dc$, 35500 – 0.1417, 46200 – 0.1523, 63100 – 0.1477, 72400 – 0.1469; S: poly(methyl vinyl ether-co-maleic anhydride), hydroxymethyl aminomethane, pH 9; T: I – poly(diphenoxy)phosphazene, II – poly(aryloxy)phosphazene, III – poly(fluoroalkoxy)phosphazene, IV – poly[bis(trifluoroethoxy) phosphazene]; U: 6F-dianhydride-1,4-phenylenediamine $dn/dc = 0.107$, 6F-dianhydride-4,4-methylenediamine $dn/dc = 0.132$, benzophenone-3,3',4,4'-diaminodiphenylsulfone $dn/dc = 0.145$; V: poly(arylether ether ketone); W: 6FDA – 6F-dianhydride, MDA – 4,4'-methylenediamine, DDS – 4,4'-diamine diphenyl sulfone, BTDA – benzophenone-3,3',4,4'-tetracarboxylic dianhydride, PDA – 1,4-phenylenediamine; X: $M_w = 4.66 \times 10^6$; Y: $M_w = 1.07 \times 10^5$; Z: 88% degree of hydrolysis; a: 98% hydrolysis; b: 88% hydrolysis; c: $M_w = 5.5 \times 10^6$; d: $M_w = 3.69 \times 10^6$; e: $M_w = 7.72 \times 10^5$; f: $M_w = 8 \times 10^6$; g: $5.32 \times 10^5 M_w$; h: $2.18 \times 10^6 M_w$; i: $M_w = 28000$; j: TFA – trifluoroacetic acid, $M_w = 3.61 \times 10^4$; k: $M_w = 1.06 \times 10^5$; m: $M_w = 2.50 \times 10^5$; n: $M_w = 6.82 \times 10^4$; o: DEAE – 2-diethylaminoethyl; p: Schizophyllan

(neutral polysaccharide); q: xanthan (anionic heteropolysaccharide); r: 0.01 M NaCl – 0.142 – $A_2 = 16$, 0.1 M NaCl – 0.137 – 5.8, 0.5 M NaCl – 0.126 – 2.52; 1 M NaCl – 0.121 – 1.52; s: poly(sodium-2-(acrylamide)-2-methyl propanesulfonate); t: bovine serum albumin; u: sodium dodecyl sulfonate; v: A – 0.15% TFA in water, B – 0.15% TFA in 95% acetonitrile; w: A – 2.5 M ammonium sulfate in 0.5 M ammonium acetate (pH 6.0), B – 0.5 M ammonium acetate (pH 6.0); x: in 0.02 M $\text{Na}_2\text{HPO}_4 - \text{NaH}_2\text{PO}_4$ at pH 6.9.

References

1. ANDERSON RI (1976) *Am Lab* 8(5):95
2. HADJICHRISTIDIS N, FETTERS LJ (1982) *J Polym Sci Polym Phys Ed* 20:2163
3. JORDAN RC, SILVER SF, SEHON RD, RIVARD RJ (1984) In: PROVIDER T (ed) *Size Exclusion Chromatography*, ACS Symposium Series 245, American Chemical Society, Washington, DC, p 295
4. SEGUDOVIC N, KARASZ FE, MACKNIGHT WJ (1990) *J Liq Chromatogr* 13:2581
5. YUNAN W, ZHONGDE X, LI J, ROSENBLUM WM, MAYS JW (1993) *J Appl Polym Sci* 49:967
6. MALIHI FB, KUO CY, PROVIDER T (1984) *J Appl Polym Sci* 29:925
7. FRANK R, FRANK L, FORD NC (1995) In: PROVIDER T, BARTH HG, URBAN MW (eds) *Chromatographic Characterization of Polymers*, *Adv Chem Ser* 247, American Chemical Society, Washington, DC, p 110
8. WAGNER HL, HOEVE CAJ (1971) *J Polym Sci A-2*, 9:1763
9. KHAN HU, GUPTA VK, YAMIN M (1983) *J Macromol Sci – Chem* A20:503
10. BRANDRUP J, IMMERGUT EH (1972) *Polymer Handbook*, Wiley, New York
11. JORDAN RC, MCCONNELL ML (1980) In: PROVIDER T (ed) *Size Exclusion Chromatography*, ACS Symposium Series 138, American Chemical Society, Washington, DC, p 107
12. JENG L, BALKE ST, MOUREY TH, WHEELER L, ROMEO P (1993) *J Appl Polym Sci* 49:1359
13. MOUREY TH, MILLER SM, BALKE ST (1990) *J Liq Chromatogr* 13:435
14. LEE HC, REE M, CHANG T (1995) *Polymer* 36:2215
15. JENG L, BALKE ST (1993) *J Appl Polym Sci* 49:1375
16. MOUREY TH, COLL H (1995) In: PROVIDER T, BARTH HG, URBAN MW (eds) *Chromatographic Characterization of Polymers*, *Adv Chem Ser* 247, American Chemical Society, Washington, DC, p 123
17. OUANO AC, KAYE W (1974) *J Polym Sci Polym Chem Ed* 12:1151
18. MOUREY TH, BRYAN TG, GREENER J (1993) *J Chromatogr A* 657:377
19. KENT MS, TIRRELL M, LODGE TP (1994) *J Polym Sci Part B Polym Phys Ed* 32:1927 (1994)
20. Wyatt Technology, Data Sheet, Santa Barbara, CA
21. DUMELOW T (1989) *J Macromol Sci-Chem* A26:125
22. SUN SF, CHAO D, LIN S (1989) *Polym Commun* 24:84
23. FORGET JL, BOOTH C, CANHAM PH, DUGGLEBY H, KING TA, PRICE C (1979) *J Polym Sci Polym Phys Ed* 17:1403
24. AMBLER MR, MCINTYRE D (1977) *J Appl Polym Sci* 21:3237
25. LEE S, KWON O-S (1995) In: PROVIDER T, BARTH HG, URBAN MW (eds) *Chromatographic Characterization of Polymers*, *Adv Chem Ser* 247, American Chemical Society, Washington, DC, p 93
26. PODZIMEK S (1994) *J Appl Polym Sci* 54:91
27. BERKOWITZ SA (1983) *J Liq Chromatogr* 6:1359 (1983)
28. DEGOULET C, NICOLAI T, DURAND D, BUSNEL JP (1995) *Macromolecules* 28:6819
29. EVANS JM (1973) *Polym Eng Sci* 13:401
30. REMSEN EE (1991) *J Appl Polym Sci* 42:503
31. ASADUZZAMAN AKM, RAKSHIT AK, DEVI S (1993) *J Appl Polym Sci* 47:1813
32. MRKVICKOVA J, DANHELKA J (1990) *J Appl Polym Sci* 41:1929
33. HATTORI S, ENDOH H, NAKAHARA H, KAMATA T, HAMASHIMA M (1978) *Polym J* 10:173
34. RUDIN A, BENSCHOP-HENDRYCHOVA I (1974) *J Appl Polym Sci* 15:2881 (1971)

35. GEERISSEN H, ROOS J, WOLF BA (1985) *Makromol Chem* 186:735
36. CHEN X, XU Z, HADJICHRISTIDIS N, FETTERS LJ, CARELLA J, GRAESSLEY WW (1984) *J Polym Sci Polym Phys Ed* 22:777
37. HORSKA J, STEJSKAL J, KRATOCHVIL P (1983) *J Appl Polym Sci* 28:3873
38. HUBER CH, LEDERER K (1980) *J Polym Sci Polym Let Ed* 18:535
39. MRKVICKOVA L, LOPOUR P, POKORNY S, JANCA J (1980) *Angew Makromol Chem* 90:217
40. GRINSHPUN V, O'DRISCOLL KF, RUDIN A (1984) *J Appl Polym Sci* 29:1071
41. PANG S, RUDIN A (1993) In: PROVDER T (ed) *Chromatography of Polymers*, ACS Symposium Series 521, American Chemical Society, Washington, DC, p 254
42. WILD L, RANGANATH R, RYLE T (1971) *J Polym Sci A-2* 9:2137
43. BOEHN LL, LANVER U, LECHNER MD (1983) *Makromol Chem* 184:585
44. GRINSHPUN V, O'DRISCOLL KF, RUDIN A (1984) In: PROVDER T (ed) *Size Exclusion Chromatography*, ACS Symposium Series 245, American Chemical Society, Washington, DC, p 273
45. MACRURY TB, MCCONNELL ML (1979) *J Appl Polym Sci* 24:651
46. HORSKA J, STEJSKA J, KRATOCHVIL P (1979) *J Appl Polym Sci* 24:1845
47. RAM A, MILTZ J (1971) *J Appl Polym Sci* 35:2639
48. DROTT EE, MENDELSON RA (1970) *J Polym Sci Part A-2*, 8:1373
49. GRINSHPUN V, RUDIN A (1985) *Makromol Chem Rapid Commun* 6:219
50. BILLIANI J, LEDERER K (1990) *J Liq Chromatogr* 13:3013
51. GRINSHPUN, RUDIN A (1985) *J Appl Polym Sci* 30:2413
52. OGAWA T (1990) *J Liq Chromatogr* 13:51
53. BERKOWITZ S (1984) *J Appl Polym Sci* 29:4353
54. OHYOYA S, MATSUO T (1989) *Chem Expr (JPN)* 4:761
55. SCHORN H, KOSFELD R, HESS M (1983) *J Chromatogr* 282:579
56. MOUREY TH, BRYAN TG (1994) *J Chromatogr A* 679:201
57. TERAN CC, MACCHI EM, FIGINI RV (1987) *J Appl Polym Sci* 34:2433
58. OGAWA T, SAKAI M (1985) *J Polym Sci Polym Chem Ed* 23:1109
59. HAMMEL R, GERTH CH (1977) *Makromol Chem* 178:2697
60. SAMANTA SR (1992) *J Appl Polym Sci* 45:1635
61. JACKSON C, O'BRIEN JP (1995) *Macromolecules* 28:5975
62. PETROVIC ZS, MACKNIGHT WJ (1991) *Polym Bull* 27:281
63. PETRI HM, STAMMER A, WOLF BA (1995) *Makromol Chem Phys* 196:1453
64. WU CS, SENKA L, MALAWER EG (1989) *J Liq Chromatogr* 12:2919
65. SEDLACK J, VOHLIDE J (1993) *Makromol Chem Rapid Commun* 14:51
66. DE JAEGER R, LECACHEUX D, POTIN PH (1990) *J Appl Polym Sci* 39:1793
67. MOUREY TH, MILLER SM, FERRAR WT, MOLLAIRE TR (1989) *Macromolecules* 22:4286
68. KONAS M, MOY TM, ROGERS ME, SCHULTZ AR, WARD TC, McGRATH JE (1995) *J Polym Sci Part B Polym Phys* 33:1441
69. DEVAUX J, DELIMOY D, DAOUST D, LEGRAS R, MERCIER JP, NIELD E (1985) *Polymer* 26:1994
70. STACY CJ (1986) *J Appl Polym Sci* 32:3959
71. TALLEY CP, BOWMAN LM (1979) *Anal Chem* 51:2239
72. KONAS M, MOY TM, ROGERS ME, SHULTZ AR, WARD TC, McGRATH JE (1995) *J Polym Sci Part B Polym Phys* 33:1441
73. OLSON ES, DIEHL JW (1985) *J Chromatogr* 349:337
74. WU C, SIDDIG M, JIANG S, HUANG Y (1995) *J Appl Polym Sci* 58:1779
75. NAGY DJ (1995) In: WU C-S (ed) *Handbook of Size Exclusion Chromatography*, Dekker, New York, p 279
76. NAGY DJ (1986) *J Polym Sci Part C Polym Let Ed* 24:87
77. LESEC J, VOLET G (1989) *International GPC Symposium*, Massachusetts, p 386
78. LANGHORST MA, STANLEY FW Jr, CUTIE SS, SUGARMAN JH, WILSON LR, HOAGLAND DA, PRUD'HOMME RK (1986) *Anal Chem* 58:2242
79. KIM CJ, HAMIELEC AE, BENEDEK A (1982) *J Liq Chromatogr* 5:1277
80. MULLER G, YONNET C (1984) *Makromol Chem Rapid Commun* 5:197

81. PAPAZIAN LA (1990) *J Liq Chromatogr* 13:3389
82. KATO T, TOKUYA T, NOZAKI T, TAKAHASHI A (1984) *Polymer* 25:218
83. LACIK I, SELB J, CANDAN F (1995) *Polymer* 36:3197
84. NAGY DJ, TERWILLIGER DA, LAWREY BD, TIEDGE WF (1989) *International GPC Symposium, Massachusetts*, p 637
85. PARK IH, CHOI EJ (1996) *Polymer* 37:313
86. KINUGASA S, NAKAHARA H, KAWAHARA J, KOGA Y, TAKAYA H (1996) *J Polym Sci Part B Polym Phys* 34:583
87. LDC/Milton Roy/Chromatix Technical Note LS 7 (1979)
88. VAN DIJK JAPP, VARKEVISSER FA, SMIT JAM (1987) *J Polym Sci Part B Polym Phys* 25:149
89. JACKSON C, NILSSON L, WYATT PJ (1989) *J Appl Polym Sci Appl Polym Symp* 43:99
90. KIM CJ, HAMIELEC AE, BENEDEK A (1982) *J Liq Chromatogr* 5:425
91. VINK H, DAHLSTROM G (1967) *Makromol Chem* 109:249
92. BAHARY WS, HOGAN MP, JILANI M, ARONSON MP (1995) In: PROVIDER T, BARTH HG, URBAN MW (eds) *Chromatographic Characterization of Polymers*, *Adv Chem Ser* 247, American Chemical Society, Washington, DC, p 151
93. HANSELMANN R, BURCHARD W (1995) *Makromol Chem Phys* 196:2259
94. KATO T, OKAMOTO T, TOKUYA T, TAKAHASHI A (1982) *Biopolymers* 29:1623
95. YU LP, ROLLINGS JE (1988) *J Appl Polym Sci* 35:1085
96. CAPRON I, GRISEL M, MULLER G (1995) *Int J Polym Anal & Charact* 2:9
97. REED WF (1995) *Makromol Chem Phys* 196:1539
98. MIKLAUTS H, RIEMANN J, VIDIC HJ (1986) *J Liq Chromatogr* 9:2073
99. HOLZWARTH G, SONI L, SCHULZ DN (1986) *Macromolecules* 19:422
100. TIELKING H, KULICKE WM (1996) *Anal Chem* 68:1169
101. PEIGIANG W, SIDDIG M, HUIYING C, DI Q, WU C (1996) *Macromolecules* 29:277
102. PICTON L, MERLE L, MULLER G (1996) *Int J Polym Anal & Character* 2:103 (1996)
103. KONISHI K (1988) In: DUBIN P (ed) *Aqueous Size Exclusion Chromatography*, Elsevier, Amsterdam, p 327
104. MHATRE R, KRULL IS, STUTING HH (1990) *J Chromatogr* 502:21
105. KRULL IR, STUTING HH, KRZYSKO SC (1988) *J Chromatogr* 442:29
106. BINDELS JG, DE MAN BM, HOENDERS HJ (1982) *J Chromatogr* 252:255
107. NICOLAI T, VAN DIJK L, VAN DIJK JAPP, SMIT JAM (1987) *J Chromatogr* 389:286

Subject Index

A

absorbance 43
additives 196
adsorption 169
–, coefficient 14
–, effect 67
agarose gel 47
aggregate 160
anionic polymers 170
antioxidant 68
aqueous SEC column 50–52, 65

B

band broadening 90
–, equation 90
baseline
–, selection 79
–, fluctuation 69
branched points 158
– polyethylene 158
branching factor 128
– index 158
– parameter 157
Butylated hydroxytoluene (BHT) 155

C

calculation of MW average 77
calibration curve 62, 63, 95
– standard 62
capacity factor 25
capillary viscometers 124
cellulose nitrate 144
chemical composition distribution 185
– heterogeneity 187
colligative properties 3
columns 47
– efficiency 24
– selection 64, 65
– selectivity 22, 25
– temperature 73
concentration dependence 58, 60
– effect 58
– -based detector 38
conical model 14, 15
copolymers 185

correction factor, MW 27
– of peak broadening 90
cumulative MWD 85, 86
cylindrical pore model 15

D

DALLS 118
data handling system 89
Debye plot 119
deconvolution approaches 91
deflection type/refractometer 39
density detector 42
dependence of retention volume on column
temperature 73
dextrans 46
2,6-di-*tert*-butyl-4-methylphenol 155
2,6-di-*tert*-butyl-*p*-cresol (BHT) 53
differential MWD 85, 88
– pressure 124
–, transducer 124
– refractometer 38
distribution coefficient 16
–, for size exclusion 14
–, for solute-packing interaction effects 14
Dondos–Benoit equation 137
dual-angle laser LS 118

E

effect of injection volume on retention
69–71
effective radius 103
Einstein's viscosity equation 102
end-group analysis 3
end-to-end-distance 103
–, of the chain 19
enthalpic interactions 13
epoxy resins 137–140
equivalent hydrodynamic sphere 103
error, MW 27
ethylene–propylene copolymers 161, 186
– -diene terpolymers 161
ethylene-vinyl acetate copolymer 162
evaporative light scattering detector 41
exclusion limit 12, 64
experimental conditions 69

- extended chain length 105–106
 extra-column band broadening 32
- F**
- flame ionization detector 42
 Flory constant 20
 – most probable distribution function 99
 – temperature 55
 – universal constant 20, 104
 Flory-Fox equation 20
 flow meters 83
 – rate dependence of retention volume 71
 flow-rate fluctuation 83
 Fourier-transform infrared (FTIR) spectro-
 photometer 44
 Fresnel's law 40
- G**
- Gaussian distribution 24
 –, function 85
 gel filtration chromatography (GFC) 4
 – permeation chromatography (GPC) 4
 geometric models 14
 Gladstone–Dale rule 121
 good solvent 55, 101
- H**
- height equivalent to a theoretical plate*
 (HETP) 24
 hemicelluloses 181
 heparin 182
 high-temperature SEC 155
 –, (HTSEC) systems 33
 HPLC setup 32
 Huggins equation 108
 Huggins' constant 108
 hyaluronic acid 182
 hydrodynamic radius 103
 – volume 20, 61, 103, 126
 –, concept 17
 hydrogen bonding 169
 hydrophobic interaction 169
- I**
- infrared (IR) detector 44
 inherent viscosity 107
 injection volume 69–71
 injector 34
 instrumental spreading function 90
 integral MWD 85, 86–88
 – operator 91
 interferometer 40
 internal marker 83
 interstitial volume 11
 intramolecular electrostatic interaction 169
- intrinsic viscosity 20, 76, 108, 23
 ion exchange 168
 – exclusion 168
 –, effect 71
 – inclusion 168
 ionic strength 68
 Ionol 155
 Irganox 1010 156
 isoelectric point 172
 iterative methods 92
- K**
- Kraemer constant 108
 – equation 108
- L**
- lag time, detector 149
 LALLS 118
 light scattering 4
 linear calibration curve 97
 logarithmic-normal distribution 85
 long-chain branching 157–160
 low-angle laser LS 118
- M**
- MALLS 118
 Mark–Houwink constants 108, 148–149
 – equation 21, 108
 –, for copolymers 215
 –, for homopolymers 199
 –, for polar polymers 209
 measurement of flow rate 83
 melamine-formaldehyde resin 141
 membrane osmometry 3
 molar absorption coefficient 43
 molecular hydrodynamic volume 11
 – size 11, 101–105
 – weight distribution 85–88
 monomer unit 106
 multi-angle laser LS 118
 MW-sensitive detector 38
- N**
- narrow-molecular weight distribution
 standards 95
 non-aqueous SEC column 47–50
 – SEC columns 64–65
 nonionic polymers 169
 nonlinear calibration curve 98
 non-size exclusion effects 168
 non-solvent 55
 nucleic acids 180
 number of theoretical plates N 24
 number-average molecular weight 1
 – MW 77

O

oligomers 131–137
3rd-order polynomial 82
overload effect 58

P

partition coefficient 14
peak broadening 23, 26, 90, 93
– variance 23
peptides 175–177, 178–180
pesticides 198
phenol-formaldehyde resins 140
photodiode array 43
poly(arylether ether ketone) 164
poly(2-vinylpyridine) 177
poly(acrylonitrile) 147
poly(ethylene terephthalate) 146
poly(phenylene sulfide) 163
poly(styrene-methyl methacrylate) 186
poly(styrene(S)-acrylonitrile(AN))
 copolymer 187
poly(vinyl acetate) 147
poly(vinyl alcohol) 147
poly(vinyl butyral) 147
poly(vinyl chloride) 142
poly(vinyl pyridine) 147
poly(2-hydroxy methacrylate gel 48
polyacrylamide 174
–, gel 48
–, hydrolysate 177
polyamic acid 148
– ester 148
polyamides 145–146
polydisperse standards 97
polydispersity 1, 78
polyethylene 155–160
–, glycols 131–134
poly(glyceryl methacrylate) gel 47
polyimide 148
polymer solubility 55–57
– standard 62
polynomial 63, 91
polyorganophosphazenes 144
polypropylene 155, 160–161
polysaccharides 180
polystyrene (PS) gel 47
– sulfonate gel 48
poly(vinyl alcohol) gel 48
polyvinylpyrrolidone 174
poor solvent 55, 101
pore size of PS gel 64
– volume 12
preferred sample concentration 62
preparation of mobile phase 69
preparative SEC 189–194

primary standard 102

proteins 172–173, 175–177, 178–180

PS standard 63

pumps 34–37

Q

Q-factor 106–107

R

radius of gyration 18, 103, 104
RALLS 118, 128–129
Rayleigh ratio 115
reciprocal slope 22
recycle SEC 191–194
reduced viscosity 20, 107
refractive index 38, 131–134
–, increments 121–122
–, (RI) detector 38–41
relative viscosity 20, 107, 123
resolution 22, 23, 26
response correction factor 132
retention volume 12, 21
right-angle laser LS 118, 128–129
root-mean-square distance 18
round-robin experiments 82

S

sample concentration 70–71
scattering angle 115
Schulz-Zimm distribution 85
SEC distribution coefficient 12
secondary standard 100–101
selection of columns 64–66
– of mobile phase 68–69
selectivity 22
–, factor 25
semirigid polymer gels 47
separation mechanism 14
– performance 64
sequential U-test 150–152
short-chain branching 157
silica-based packing materials 46
size exclusion chromatography (SEC) 4
slope of the calibration curve 22
sodium azide 69
Sodium poly(acrylate) 177
– poly(styrene sulfonate) 170, 174
soft polymer gels 47
Solomon-Ciuta equation 108
solubility of a polymer sample 55–57
– parameter 56
specific refractive index increment
 121–122, 217
– resolution 26
– viscosity 20, 107, 125

starch hydrolysate 180
Stokes–Einstein equation 104
Stokes' radius 103
structure-selective detectors 43–44
system peaks 13

T
TALLS 118
thermodynamic model 16
theta solvent 55, 59, 60, 108
– temperature 55
third-order polynomial 96
total column volume 22
– mobile phase volume 12
– permeation limit 12
– permeation volume 12
– pore volume 12
triple-angle laser LS 118
Tung's equation 90
ultraviolet (UV) and visible (VIS)
absorption detectors 43
universal calibration curve 109–113, 126
unperturbed root-mean-square end-to-end
distance 20

V
vapor pressure osmometry 3
variances 23
viscosity average MW 78
– effect 60
viscous fingering 58
void volume 11

W
weight-average 77
–, molecular weight 1

X
xanthan 182

Z
($z + 1$)-average MW 78
z-average mean-square radius of gyration
103
– molecular weight 1, 77
Zimm plot 116