

Inspection Data of Rubber Powder

Nitto Kako Co., Ltd.

Trade Name	Rubber Powder 4000	Lot Number			240521	Shipment Day	Sep. 5, 2024
Quality Item		1	2	3	Average	Standardized Values	Success or Failure
Sieve Residue on 500 μ (%)		1	0	0	0.3	3 Max	Success
Sieve Residue on 350 μ (%)		44	42	41	42.3	15 ~ 45	Success
Sieve Residue on 150 μ (%)		54	56	58	56.0	45 ~ 75	Success
Sieve Residue under 150 μ (%)		1	2	1	1.3	20 Max	Success
Bulk Density(g/L)		330	322	335	329.0	270 ~ 350	Success

Test Procedure : Sieve Residue JIS-K-6316

Delivery Quantity: 100kg

ACCEPT

Handwritten signature

By : QA Dept.

Approve

K. Sakata