arXiv:2205.00899v1 [cond-mat.str-el] 2 May 2022

Strange metal dynamics across the phase diagram of $Bi_2Sr_2CuO_{6+\delta}$ cuprates.

Erik van Heumen,[1,2,*] Xuanbo Feng (馮翾博),[1,2] Silvia Cassanelli,[1] Linda Neubrand,[1] Lennart de Jager,[1] Maarten Berben,[1] Yingkai Huang,[1] Takeshi Kondo,[3] Tsunehiro Takeuchi,[4] and Jan Zaanen[5,†]

[1] *van der Waals - Zeeman Institute, University of Amsterdam, Sciencepark 904, 1098 XH Amsterdam, the Netherlands*
[2] *QuSoft, Science Park 123, 1098 XG Amsterdam, The Netherlands*
[3] *Institute for Solid State Physics, University of Tokyo, Kashiwa-no-ha, Kashiwa, Japan*
[4] *Toyota Technological Institute, Nagoya 468-8511, Japan*
[5] *Lorentz institute, Universiteit Leiden, Leiden, the Netherlands*

Unlocking the mystery of the strange metal state has become the focal point of high T_c research, not because of its importance for superconductivity, but because it appears to represent a truly novel phase of matter dubbed 'quantum supreme matter'. Detected originally through high magnetic field, transport experiments, signatures of this phase have now been uncovered with a variety of probes. Our high resolution optical data of the low T_c cuprate superconductor, $Bi_{2-x}Pb_xSr_{2-y}La_yCuO_{6+\delta}$ allows us to probe this phase over a large energy and temperature window. We demonstrate that the optical signatures of the strange metal phase persist throughout the phase diagram. The strange metal signatures in the optical conductivity are two-fold, (i): a low energy Drude response with Drude width on the order of temperature and (ii): a high energy conformal tail with doping dependent power-law exponent. While the Drude weight evolves monotonously throughout the entire doping range studied, the spectral weight contained in the high energy conformal tail appears to be doping and temperature independent. Our analysis further shows that the temperature dependence of the optical conductivity is completely determined by the Drude parameters. Our results indicate that there is no critical doping level inside the superconducting dome where the carrier density starts to change drastically and that the previously observed 'return to normalcy' is a consequence of the increasing importance of the Drude component relative to the conformal tail with doping. Importantly, both the doping and temperature dependence of the resistivity are largely determined by the Drude width.

I. INTRODUCTION

Since the discovery of cuprate high Tc superconductivity thirty-five years ago, numerous studies of the optical properties were published. It may appear as an exhausted affair – everything that could be measured has been measured – and this reflected in the reduced output over the last ten years or so [1–9]. Nevertheless, high T_c superconductivity continues to be a fertile source of surprises [10]. If anything, the profundity of the mystery pointing at a fundamentally different type of physics has become more manifest in recent years. One aspect is that the theoretical view on the physics behind transport phenomena has been on the move. During the early history of the subject it was taken for granted that the transport originates in a very dilute gas of thermally excited quasiparticles as in conventional Fermi-liquid metals. Catalyzed by the understanding of strongly interacting quantum critical states of matter [11] and further elaborated by insights coming from the AdS/CFT correspondence of string theory [12, 13] it was realized that in his regard Fermi-liquids are singularly special. Yet other states of strongly interacting quantum matter may be formed, characterized by dense many body quantum entanglement [14]. Rooted in the advancements in the general understanding of quantum (Eigenstate) thermalization [15] one expects that such non-Fermi-liquids are characterized by extremely rapid thermalization and the absence of quasiparticle excitations [14]. One then expects that the transport in such systems eventually rests on the highly collective flows described by hydrodynamics, or otherwise in the form of 'incoherent' transport. The latter should reflect simple scaling properties related to what is found at thermal phase transitions.

On the experimental side, doubts regarding the Fermi liquid arose early in the form of the famous linear-in-temperature DC electrical resistivity, $\rho(T) \sim T$. This linearity of the resistivity in optimally doped cuprates extends all the way from the superconducting T_c up to the melting point of the crystal, with ρ becoming larger than what is expected from the Mott-Ioffe-Regel minimal conductivity criterium expected in normal metals. Given the high T_c of these materials, one could argue that the normal state is always in the phonon scattering dominated regime. However, this linearity extends to sub-kelvin temperatures when superconductivity is suppressed in high magnetic fields[16]. The problem of principle has been all along to explain why this behaviour is so simple – dealing with quasiparticles the resistivity should be a more interesting function of temperature. Recently the 'Planckian dissipation' [17] came into the limelight [18, 19]. Taking for granted that the DC transport is of the Drude kind it was deduced that the current relaxation (scattering) time $\tau_J \simeq \tau_\hbar$. The Planckian dis-

*Electronic address: e.vanheumen@uva.nl
†Electronic address: jan@lorentz.leidenuiv.nl