arXiv:2311.15791v1 [cond-mat.str-el] 27 Nov 2023

Optical response of the bulk stabilized mosaic phase in Se doped $TaS_{2-x}Se_x$.

Xuanbo Feng (馮翾博),[1,2] Liam Farrar,[3] Charles J. Sayers,[3,4] Simon J. Bending,[3] Enrico Da Como,[3] and Erik van Heumen[1,2,*]

[1] *van der Waals - Zeeman Institute, University of Amsterdam, Sciencepark 904, 1098 XH Amsterdam, the Netherlands*
[2] *QuSoft, Science Park 123, 1098 XG Amsterdam, The Netherlands*
[3] *Centre for Nanoscience and Nanotechnology, Department of Physics, University of Bath, Bath BA2 7AY, United Kingdom*
[4] *Dipartimento di Fisica, Politecnico di Milano, 20133 Milano, Italy*

(Dated: November 28, 2023)

The layered van der Waals material, TaS_2 features a meta-stable mosaic phase on the verge of a nearly commensurate to commensurate charge density wave transition. This meta-stable or 'hidden' phase can be reached by laser pumping the low temperature, commensurate charge density wave phase. Here we report the stabilization of a bulk, equilibrium mosaic phase in 1T-$TaS_{1.2}Se_{0.8}$ single crystals observed with transport and optical spectroscopy experiments. We identify a bulk pseudogap in the mosaic phase of approximately 200 meV at the lowest temperatures, while the CCDW phase can be obtained by heating and instead has a full optical gap of about 100 meV. Surprisingly, a spectral weight analysis shows that Se doping gives rise to an increased charge density despite the fact that this is formally an isovalent substitution. This finding is consistent with the recent observation that the mosaic phase is stabilized as equilibrium phase through the appearance of charged defects.

Transition metal dichalcogenides (TMDCs) provide a rich playground of exotic electronic ordering phenomena such as superconducting or charge density wave phases. 1T-TaS_2 stands out among them due to the observation of a correlated insulating phase, the nature of which is still under debate [1–7]. Disentangling the interplay between structural and electronic order is difficult, but the consensus now appears to be that the equilibrium groundstate is a commensurate charge density wave that originates in dimerization of layer stacking along the c-axis [3, 4]. However, at elevated temperatures [6] or at specific surface terminations [5] signatures of Mott physics reemerge pointing to the interplay of several instabilities. Against this backdrop, a series of experiments employing light or current pulses demonstrated the existence of a 'hidden' or meta-stable state [8–13]. The induced metallicity appears to be tied to the emergence of domain walls in the CCDW phase [14–16] and changes in the interlayer stacking [17]. The meta-stable state has subsequently been dubbed the 'mosaic' phase. The tunability between distinct electronic phases with external control has led to suggestions for applications [18, 19] and consequently stabilising the mosaic phase under equilibrium conditions would be very useful. Recently, an equilibrium version of the mosaic phase was reported to exist as a surface effect on 1T-TaS_2 single crystals [20]. Similar equilibrium states appear to exist as surface structure in doped 1T-$TaS_{2-x}B_x$ crystals where B is Ti [21] or Se [2, 22, 23].

Here we report the existence of a meta-stable, metallic phase in bulk single crystals of Se doped 1T-$TaS_{2-x}Se_x$ ($x = 0.8$) that can be reached under thermal equilibrium conditions. This state is observed in a large temperature window below 130 K and is distinctly different from the insulating CCDW phase. The latter can be realized after heating above 130 K and it remains the equilibrium state if the crystal is subsequently cooled down again. From a detailed analysis of the optical spectra, we conclude that there are two distinct mechanisms that give rise to the mosaic and CCDW phase. The former is characterized by the formation of a pseudogap, while the latter is characterized by a full optical gap.

Single crystals of 1T-$TaS_{2-x}Se_x$ with nominal compositions $x = 0.8$ and $x = 1.0$ are are grown using chemical vapor transport. Typical crystal sizes obtained in this way are approximately 2×3 mm with a somewhat irregular shape. Further details of the growth process are provided in the supplementary material. Transport experiments were carried out using a 4-point method using a Physical Property Measurement System (PPMS) and data was recorded between 3 and 310 K. Infrared reflectivity spectra are collected over the energy range from 6 meV to 4 eV and between 16 K and 400 K for two samples with Se contents $x = 0.8$ and $x = 1.0$. In order to study the hysteresis in this system, a temperature loop is designed to start cooling from 400 K down to 16 K. At base temperature, data is collected for 20 minutes and then the sample is heated to 400 K. Both cooling and warming experiments are carried out with a constant temperature change of 1.7 K/min. Each cycle is repeated several times to verify the reproducibility and reduce the noise in the data. The experiment is repeated right after the *in situ* evaporation of silver or gold on the samples to obtain reference spectra. These allow us to determine the absolute reflectivity of our samples. To obtain the optical conductivity, we use the variational