

2019–
2023



Signatures of the charge density wave collective mode in the infrared optical response of VSe_2

Xuanbo Feng (馮翾博)
QuSoft, Science Park 123, 1098 XG Amsterdam, The Netherlands and
Institute of Physics, University of Amsterdam, Science park 904, 1098 XH Amsterdam, The Netherlands

Jans Henke and Corentin Morice
Institute of Physics, University of Amsterdam, Science park 904, 1098 XH Amsterdam, The Netherlands

Charles J. Sayers
Dipartimento di Fisica, Politecnico di Milano, 20133 Milano, Italy and
Centre for Nanoscience and Nanotechnology, Department of Physics,
University of Bath, Bath BA2 7AY, United Kingdom

Enrico Da Como
Centre for Nanoscience and Nanotechnology, Department of Physics,
University of Bath, Bath BA2 7AY, United Kingdom

Jasper van Wezel
Institute of Physics, University of Amsterdam, Science park 904, 1098 XH Amsterdam, The Netherlands

Erik van Heumen*
QuSoft, Science Park 123, 1098 XG Amsterdam, The Netherlands and
Institute of Physics, University of Amsterdam, Science park 904, 1098 XH Amsterdam, The Netherlands

(Dated: December 6, 2021)

We present a detailed study of the bulk electronic structure of high quality VSe_2 single crystals using optical spectroscopy. Upon entering the charge density wave phase below the critical temperature of 112 K, the optical conductivity of VSe_2 undergoes a significant rearrangement. A Drude response present above the critical temperature is suppressed while a new interband transition appears around 0.07 eV. From our analysis, we estimate that part of the spectral weight of the Drude response is transferred to a collective mode of the CDW phase. The remaining normal state charge dynamics appears to become strongly damped by interactions with the lattice as evidenced by a mass enhancement factor $m^*/m \approx 3$. In addition to the changes taking place in the electronic structure, we observe the emergence of infrared active phonons below the critical temperature associated with the $4a \times 4a$ lattice reconstruction.

arXiv:2101.03048v2 [cond-mat.str-el] 3 Dec 2021

I. INTRODUCTION

Early studies of the transition-metal dichalcogenide (TMDC) VSe_2 focussed on the charge density wave transition [1–6]. The recently renewed interest in TMDCs as a platform for 2D materials research has also rekindled the interest in VSe_2 [7–12], and in particular in monoatomic layers of VSe_2 [13, 14]. Nevertheless, the characteristics of the CDW phase in the bulk compound, such as the collective excitations and size of the CDW gap, remain incomplete and controversial. For example, angle resolved photoemission (ARPES) and scanning tunnelling spectroscopy (STM) experiments report gap sizes varying between 13 to 130 meV [7, 8, 12, 15, 16]. Recently, some of us reported the sensitivity of the CDW properties to defects and overall stoichiometry [17]. It was demonstrated that depending on sample growth conditions the defects and Se deficiencies proliferate, while optimal growth conditions can be achieved to produce stoichiometric, clean crystals with an enhanced critical transition temperature for the CDW phase. This development opens the door to new studies of bulk electronic properties and here we report the first infrared optical spectroscopy study of the CDW transition of VSe_2. In the following we present the absolute reflectivity of high-quality VSe_2 single crystals, and discuss the evolution of the main features across the CDW transition. Our optical data indicates that a significant reorganisation of the electronic structure takes place and we discuss how this compares to earlier experiments that probe the electronic structure.

II. EXPERIMENT

The preparation and characterisation of single crystals of VSe_2 are extensively reported in Ref. [17]. In summary, it was reported that in order to obtain near ideal stoichiometry and to minimise the presence of defects,

* e.vanheumen@uva.nl