

2019–
2023

Optical phonons and magneto-elastic coupling in the ionic conductor $AgCrSe_2$

Jim Groefsema,[1] Xuanbo Feng,[1,2] Corentin Morice,[1] Yingkai. Huang,[1] and Erik van Heumen[1,2,*]

[1] *Institute of Physics, University of Amsterdam, Science park 904, 1098 XH Amsterdam, The Netherlands*
[2] *QuSoft, Science Park 123, 1098 XG Amsterdam, The Netherlands*

$AgCrSe_2$ is an example of a super-ionic conductor that has recently attracted attention for its low thermal conductivity. Here we investigate the optical properties of $AgCrSe_2$ in the ordered phase between 14 K and 374 K using reflectivity experiments. The far infrared optical response is dominated by three phonon modes, while six interband transitions are observed in the visible range. From our analysis we find that the phonon parameters display an interesting temperature dependence around the Néel temperature, pointing to a small magneto-elastic coupling. In addition, the lifetimes of the modes indicate that three-phonon processes dominate and the optical phonons decay into low energy acoustic modes involved in the super- ionic transition. Finally, we detect a small free charge carrier response through the analysis of Fabry-Perot interference fringes in our reflectivity data.

arXiv:2208.14872v1 [cond-mat.mtrl-sci] 31 Aug 2022

I. INTRODUCTION

With an increasing demand for batteries, solid-state ionic conductors have gained in interest due to their higher energy density, a potential for fast charging and increased safety over commonly used Li-ion batteries[1]. Current in solid-state ionic conductors is carried by mobile ions through hopping between vacant sites in the material, which are typically slow processes. This has led to the study of a small group of materials that partially 'melt' above the so-called super-ionic transition. Above this transition, the energy landscape of a sub-lattice of ions in the structure changes such that ions can rapidly diffuse through correlated motion[2]. As it turns out, super-ionic conductors also have excellent thermoelectric response, owing to a very low thermal conductivity resulting from the partially molten sub-lattice of ions[3].

One example of such a super-ionic conductor with excellent thermoelectric figure of merit is $AgCrSe_2$, which consists of a sub-lattice of Ag ions sandwiched between $CrSe_2$ layers[4]. At a temperature of 475 K, $AgCrSe_2$ transitions into its super-ionic phase where Ag ions become disordered[5–7]. The phase transition into the disordered phase is second order[6], but diffusion of Ag ions already seems to start well below the transition[8]. The diffusion of Ag ions is promoted by lowering of the energy barrier for the occupation of a second interstitial site in the Ag lattice and has been proposed to result in the breakdown of certain phonon modes[9]. However, direct imaging of the occupation of interstitial sites by Ag ions with transmission electron microscopy suggests that slow diffusion is a result of disorder[10]. At low temperature, the Cr spins order in a non-collinear anti-ferromagnetic order with anti-ferromagnetic stacking along the c-axis[5] and fluctuations of this order persisting up to 200 K[11]. Recently, short range correlations and the interplay between spin-orbit coupling and magnetic order have been studied at low temperatures[12,13].

The low thermal conductivity is most likely determined by the phonon spectrum and several momentum resolved studies have indeed observed changes in the phonon spectrum with temperature[8,9,11]. An early far-infrared optical study on sintered samples focussed on the high temperature transition and its impact on the phonon spectrum, reporting changes in the TO-LO mode splitting[14]. More recently, indications of the important role played by a 3 meV phonon mode and a possible magneto-elastic coupling between the low energy phonons and anti-ferromagnetic fluctuations have been brought to light[11]. This lead us to revisit $AgCrSe_2$ using high resolution optical spectroscopy reflectivity experiments on single crystalline samples, with a particular focus on the optical phonon modes and their temperature dependence. In this letter, we report reflectivity measurements between 14 K and 374 K, covering the low temperature anti-ferromagnetic state, but not the high temperature super-ionic transition. Three phonon modes are observed in the far infrared region and we find evidence for a weak magneto-elastic coupling through a detailed temperature dependence of the phonon mode parameters. We report the interband optical response and compare these to electronic structure calculations. Finally, we observe Fabry-Perot interference fringes in the reflectivity data. From a detailed analysis of these fringes, we are able to deduce a small free charge contribution to the optical response resulting in a DC resistivity of 0.5 $\Omega\,cm$.

II. EXPERIMENTAL METHODS

Single crystal $AgCrSe_2$ samples were produced using the chemical vapor transport growth method. The resulting $AgCrSe_2$ samples have the approximate dimensions of 3×3 mm with an average thickness between 100 and 200 μm. The crystal is supported by a copper holder, which has the shape of a tapered cone with the flat top surface cut to the shape of the $AgCrSe_2$ sample. In this way, light reflected from the copper holder will not reach the detector. The holder was polished to a smooth finish and cleaned using ultrasonic cleaning with a series of solutions in the order of citric acid, acetone and ethanol. Conducting silver epoxy was used to glue the sample to