


Puddle formation, persistent gaps, and non-mean-field breakdown of superconductivity in overdoped $(Pb,Bi)_2Sr_2CuO_{6+\delta}$

Willem O. Tromp[1*], Tjerk Benschop[1*], Jian-Feng Ge[1], Irene Battisti[1], Koen M. Bastiaans[1,2], Damianos Chatzopoulos[1], Amber Vervloet[1], Steef Smit[3], Erik van Heumen[3,4], Mark S. Golden[3], Yinkai Huang[3], Takeshi Kondo[5], Yi Yin[6,7], Jennifer E. Hoffman[8], Miguel Antonio Sulangi[9], Jan Zaanen[10], Milan P. Allan[1†]

1. Leiden Institute of Physics, Leiden University, 2333 CA Leiden, The Netherlands
2. Department of Quantum Nanoscience, Kavli Institute of Nanoscience, Delft University of Technology, 2628 CJ Delft, The Netherlands
3. Institute of Physics, University of Amsterdam, 1098 XH Amsterdam, The Netherlands
4. QuSoft, 1098 XG Amsterdam, The Netherlands
5. Institute for Solid State Physics, University of Tokyo, Kashiwa, Japan
6. Zhejiang Province Key Laboratory of Quantum Technology and Device, Department of Physics, Zhejiang University, Hangzhou 310058, China
7. Collaborative Innovation Centre of Advanced Microstructures, Nanjing University, Nanjiang 210093, China
8. Department of Physics, Harvard University, Cambridge, Massachusetts 02138, USA
9. Department of Physics, University of Florida, Gainesville, Florida 32611, USA
10. Institute-Lorentz for Theoretical Physics, Leiden University, 2333 CA Leiden, The Netherlands

* These authors contributed equally.

† Corresponding author: milan.allan@gmail.com

The cuprate high-temperature superconductors exhibit many unexplained electronic phases, but it was often thought that the superconductivity at sufficiently high doping is governed by conventional mean-field Bardeen-Cooper-Schrieffer (BCS) theory[1]. However, recent measurements show that the number of paired electrons (the superfluid density) vanishes when the transition temperature T_c goes to zero[2], in contradiction to expectation from BCS theory. The origin of this anomalous vanishing is unknown. Our scanning tunneling spectroscopy measurements in the overdoped regime of the $(Pb,Bi)_2Sr_2CuO_{6+\delta}$ high-temperature superconductor show that it is due to the emergence of puddled superconductivity, featuring nanoscale superconducting islands in a metallic matrix[3,4]. Our measurements further reveal that this puddling is driven by gap filling, while the gap itself persists beyond the breakdown of superconductivity. The important implication is that it is not a diminishing pairing interaction that causes the breakdown of superconductivity. Unexpectedly, the measured gap-to-filling correlation also reveals that pair-breaking by disorder does not play a dominant role and that the mechanism of superconductivity in overdoped cuprate superconductors is qualitatively different from conventional mean-field theory.

The essence of high-temperature superconductivity in the cuprates revolves around doping a Mott insulator. Superconductivity emerges when hole-doping is greater than 5% per lattice site; T_c initially increases through the underdoped (UD) region of the phase diagram, before it decreases again in the overdoped (OD) region[1]. Superconductivity breaks down completely at roughly 27% doping. For the strongly overdoped region (SOD), it is often assumed that screening sufficiently reduces electron-electron correlations for a Fermi liquid to appear[5–7]. The superconducting state is then of the Bardeen-Cooper-Schrieffer (BCS) type, and the suppression of superconductivity is a consequence of a diminishing pairing interaction. Evidence for such conventional behavior in the OD regime comes from photoemission experiments, which suggest the existence of a full Fermi surface with superconductivity, as