

STD-ENG-110 Corrosion Allowance and Material Selection

Revision A - Owner: Technical Services - Classification: Internal

1. Corrosion allowance

Carbon steel in hydrocarbon service: 3 mm corrosion allowance. Sour water and amine service: 6 mm, or upgrade to stainless steel.

2. Material upgrade

Where the measured corrosion rate exceeds 0.25 mm/year for two consecutive inspections, the Inspection Engineer shall propose a material upgrade or chemical treatment review.