

SOP-INS-021 Piping Thickness Monitoring Programme

Revision A · Owner: Technical Services · Classification: Internal

1. Purpose

Defines the thickness monitoring programme for process piping, including CML selection, measurement frequency and data review.

2. CML selection

Select CMLs at elbows, tees, reducers, injection points and dead legs. Injection points require CMLs from 300 mm upstream to 10 pipe diameters downstream.

3. Frequency

Class 1 piping (flammable, toxic or high-consequence service): every 5 years or half remaining life, whichever is less. Class 2 piping: every 10 years or half remaining life. Injection points: every 3 years.

4. Data review

Readings that show a thickness increase of more than 0.5 mm over the previous reading shall be re-measured before use, because they usually indicate a measurement error.