

# HPMC

## Technical Data Sheet

### Introduction

#### Hydroxy propyl methyl cellulose HPMC

HPMC is a high viscosity product for cement-based tile adhesives mortar. It enhances water-retention besides providing well-balanced properties including open time, slip resistance, adhesion, good impact resistance and shear strength.

### Using effect

- Water retention---improved water retention can protect cement and plaster against poor solidification and cracking due to too speedy drying and inefficient mixing with water.
- Workability --mortar plasticizing quality can be improved, which in turn will improve the workability of painting and working efficiency.
- Binding---due to the increased plasticizing quality, mortar can be a better binder.
- Slipping-resistance---Due to the thickening action of Cellulose Ether, the slipping phenomena of mortar from substance to be bound can be prevented more efficiently.

#### Recommend main usage

Coating, Putty powder  
Paint, concrete  
Ceramics, thermal insulation mortar  
Cement additive  
Adhesives

### Properties

|                         |                            |
|-------------------------|----------------------------|
| Appearance              | White powder, free-flowing |
| Methoxyl content        | 19.0-24.0%                 |
| Hydroxyl propyl content | 7.0-12.0%                  |
| Gel temperature         | 70-90°C                    |
| Average particle size   | 120 mesh                   |
| PH Value                | 5.0-8.0                    |
| Gravity                 | 1.26-1.31g/cm              |
| Viscosity               | 20000-200000 mpa.s         |
| (by 2% NDJ-1)           |                            |
| Ash content             | ≤5%                        |
| Moisture                | ≤5%                        |

### Packaging & Storage

25kg multilayer paper bags with polyethylene intermediate layer. Keep it in cool, dry place avoiding direct sunshine.

To avoid caking, HPMC is recommended stacked bags.

### Contact information

The product specification information is based on our present state of knowledge and provide general notes on our products and application. It should therefore not be construed as guaranteeing specific properties of the products of their suitability for specific application. This product specification is not signed. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. If you have any questions, please contact our R&D center of sales people from